

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Specid	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
TYPE R FLUID (Enviro-Blend)	Good	[n/r]	[n/r]	[n/r]			neither	PTFE			Polyester Adipate:Heat to 130 degrees F too viscous to pump at Room Temperature				
(2-) ETHYLHEXYL ACRYLATE	do not use	do not use	do not use	do not use		Best	flammable	PTFE				yes	SDS		
1,1,1,3,3,3 - Hexamethyldisilaxane	[n/r]	Best	[n/r]	[n/r]		Good	Flammable	PTFE							
1,2-PROPANEDIOL	Best	Best	Best	Best			neither	2375 by Tyg	PTFE		also known as Propylene Glycol				yes
110 Ignitor Fuse Race Fuel	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE				yes	sds		
11A Screen Cleaner			Best				Flammable	Tygon2375	PTFE			yes	sds		Feb-17
1205404-1 Mechanical Lubricant	do not use	do not use	do not use	best			flammable	gas grade h	PTFE						
1610 White Wax (water based concrete curing co	Best	Good	Good	Best			neither	2375 by Tyg	PTFE			yes	sds		
17-21% PAA	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best		PTFE				yes	test		
1-Vinyl-2-pyrrolidinone	n/r	best	n/r	n/r			neither	2375 by Tyg	PTFE			yes	test/sds		
2 EHA - Ethyl Hexyl acrylate	[n/r]	[n/r]	[n/r]	[n/r]			neither	PTFE			BASF				
2,4-D Amine 500	Do Not Use	Good	[n/r]	[n/r]			neither	2375 by Tyg	PTFE		Requires Closed Mixing system in California				
2,4-D Ester 800	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE		Requires Closed Mixing System in California				
200224000 Ardrex 295GD (Bulk) (BASF)				Best			neither	PTFE				yes	sds		9/16/2024
2960 Glass Cleaner	n/r	Good	Best	n/r			flammable	2375 by Tyg	PTFE			yes	sds		
2-methyl-4-chlorophenoxyacetic acid, isoctyl (2-ethylhexyl) ester			Best				flammable	2375 by Tyg	PTFE		Herbicide	yes	sds		
35291 Reducer normal (BASF)	do not use	do not use	do not use	do not use		Best	neither	PTFE		Teflon Kalrez		yes	sds + test		
3540 (Chemstation)				Best			combustible	2375 by Tyg	PTFE			yes	sds		Aug-19-20
3566 (ChemStation)		Best	Best				neither	TYGON 2375	PTFE			YES	SDS		4/21/2018
381933 Vanilla Flavor Art	Good	Good	Best	do Not Use				2375 by Tyg	PTFE			yes	sds		
3M Adhesion Promoter 4298UV	[n/r]	[n/r]	[n/r]	Best			flammable	PTFE			fluid path Teflon-Kalrez	yes	sds		
3M FLUORINERT	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE				yes	sds		
3M Novec Engineered Fluid 72DA	[n/r]	[n/r]	[n/r]	Best			neither	PTFE			Must have Teflon Kalrez fluid path upgrade. Consider the System for Vapor Degreasers				
3-METHOXYPROPYLAMINE				Good			flammable	PTFE			6-2019 Waiting on plastic	yes	sds		June 04 2019
42/Auto Refinish	Do Not Use	Do Not Use	Best	Do Not Use			Flammable	PTFE			Requires fluid path Teflon	yes	test and SDS		
421A (MG Chemicals, Liquid Tin)				Best			neither	2375 by Tyg	PTFE			yes	sds		Aug-19-20
50177 (Chemstation)		Best					neither	2375 by Tyg	PTFE			yes	sds		Aug-19-20
5542 (Chemstation)		Best	Best				neither	Tygon2375	PTFE			yes	SES		
601 M-12 Metal Cutting Oi	Best						neither	Gas	PTFE			yes	Questionnaire		
667 Multipurpose WASH thinner	Do Not Use	Best	Do Not Use	Do Not Use			flammable	PTFE				yes	test & sds		
7666 MRC-ALT - Tower Products	Do Not Use	Do Not Use	Do Not Use	Best	required		flammable	PTFE			Celcon Tap required	yes	sds		
9525 (ChemStation)			Good	Best			neither	Tygon 2375	PTFE			yes	sds		Sept 14-19
959T Low Residue no clean Flux	Do Not Use	Do Not Use	Best	Do Not Use			flammable	PTFE				yes	sds & label		
9630 Thinner (Nazdar)	Do Not Use	Caution	Best	Caution			combustible	PTFE			May require tap o-ring change from time to time				
9680 (ChemStation)				best			neither	Tygon 2375	PTFE			yes	sds		Sept 14-19
985140-2 Stamping Lubricant	n/r	n/r	n/r	best			flammable	PTFE				yes	test & sds		
A1011 MultiPurpose Solvent	Do Not Use	Do Not Use	Do Not Use	Best	Recommended		Flammable	PTFE			Celcon tap recommended	yes	zip		
A10652	Do Not Use	Do Not Use	Do Not Use	Good			neither	2375 by Tyg	PTFE						
A10675	Do Not Use	Do Not Use	Do Not Use	Good			neither	2375 by Tyg	PTFE						
A10901	Do Not Use	Do Not Use	Do Not Use	Good			neither	2375 by Tyg	PTFE						
A10990	Do Not Use	Do Not Use	Do Not Use	Good			neither	2375 by Tyg	PTFE		May be too viscous				
A11021	Do Not Use	Do Not Use	Do Not Use	Good			neither	2375 by Tyg	PTFE		May be too viscous				
A11080	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE						
A11246	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE						
A11340	Fair	best	Do Not Use	fair			neither	2375 by Tyg	PTFE						
A11363	Fair	Do Not Use	Do Not Use	fair			neither	2375 by Tyg	PTFE						
A11403	Do Not Use	Do Not Use	Do Not Use	fair			neither	2375 by Tyg	PTFE		May be too viscous				
A12636	Do Not Use	Do Not Use	Do Not Use	Good			neither	2375 by Tyg	PTFE						
A12686	Do Not Use	Do Not Use	Do Not Use	Good			neither	2375 by Tyg	PTFE		May be too viscous				
A12714	Fair	Do Not Use	Do Not Use	Good			neither	2375 by Tyg	PTFE		May be too viscous				
A16228	Do Not Use	Do Not Use	Do Not Use	Good			neither	2375 by Tyg	PTFE						
A-222	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon				yes	zip		zip
A26001A FUNGICIDE (SYNGENTA)				Best			neither	Tygon 2375	PTFE		CHECK VISCOSITY BE	yes	sds MFG recommended		entered may 3
A-300	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE			yes	zip		zip
Abatix ABX1983 Heavy Duty Degreaser			Best				Neither	Tygon2375				SDS			Feb-17

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Abitol E Hydroabietly Alcohol, Hydroabietyl Alcohol	Good	Caution	[n/r]	Best			Flammable	2375 by Tyg	PTFE		Too thick for GT pumps - 6500cP at 50 deg C				
ABOUND FLOWABLE				Best			neither	Tygon 2375	PTFE		CHECK VISCOSITY BE	yes	sds MFG recommended	entered may 3	
AC 333 - LW chemicals				Best			neither	2375 by tygon				yes	sds	Aug-19-20	
AC-103	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tyg	PTFE			yes	zip		
AC-55 5 RED	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE			yes	zip		
AC-55-5				Best			Neither	Tygon2375				SDS		Feb-17	
AC-55-5 RED				Best			Neither	Tygon2375				SDS		Feb-17	
ACB - 30	Best	Best	[n/r]	[n/r]											
Accelerator DY 062 US	[n/r]	[n/r]	[n/r]	Best			neither	PTFE				yes	tested		
Accelguard 80 - Bulk Gallons	Best	Best	Best	Best			neither	2375 by Tyg	PVC		Any pump, PVC or 2375	yes	MFG		
Acculube 6800	Fair	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE		May be too thick for GT				
Acetaldehyde	Do Not Use	Best	[n/r]	Caution			Flammable	PTFE			Wash	no			
Acetamide	Best	Best	[n/r]	Best			neither	2375 by Tyg	PTFE			no	no	yes	
Acetic Acid 10%	Do Not Use	Good	Good	Best			neither	2375 by Tyg	PTFE		Teflon-Kalrez fluid path	yes	tested		
Acetic Acid 20%	Do Not Use	Good	Good	Do Not Use			neither	2375 by Tyg	PTFE		Teflon-Kalrez fluid path	no			
Acetic Acid 50 - 80% - Vinegar Ethanoic by Univar			Good				combustible	2375 by Tyg	PTFE			yes	sds MFG recommended	entered may 3	
Acetic Acid 56%	Do Not Use	Good	Good	Caution			neither	2375 by Tyg	PTFE		Teflon-Kalrez fluid path	no			
Acetic Acid 80%	Do Not Use	Good	Good	Caution			neither	2375 by Tyg	PTFE		Teflon-Kalrez fluid path	no			
Acetic Acid Food/Kosher Grade, 99-100%	Do Not Use	Good	Good	Do Not Use	Best		neither	2375 by Tyg	PTFE		Teflon-Kalrez fluid path	yes			
Acetic Acid Natural 90%	Do Not Use	fair	fair	Do Not Use	Best		neither	2375 by Tyg	PTFE		Teflon-Kalrez fluid path	upgrade recommended			
acetic acid, 100%, Glacial	Do Not Use	Good	Good	Do Not Use	Best		neither	2375 by Tyg	PTFE		Teflon-Kalrez fluid path	yes	email		
Acetic Anhydride	Do Not Use	Good	Good	Do Not Use	Best		neither	2375 by Tyg	PTFE		Wash	yes	no		
Acetone	Do Not Use	Good	Best	Do Not Use			Flammable	2375 by Tyg	PTFE		If you purchase EPDM g	yes	sds		
acetone = propan-2-one			Best				Flammable	Tygon2375	PTFE						
Acetone, technically pure	Do Not Use	Good	Best	Do Not Use			Flammable	2375 by Tyg	PTFE		If you purchase EPDM g	no	no		
Acetone, Traces	Do Not Use	Good	Best	Do Not Use			Flammable	2375 by Tyg	PTFE		If you purchase EPDM g	no	no		
Acetonitrile	[n/r]	Best	Best	[n/r]			Combustible	2375 by Tyg	PTFE			yes			
Acetonitrile Waste Mixture	[n/r]	Good	Best	[n/r]			Combustible	2375 by Tyg	PTFE			yes	yes		
Acetophenone	Do Not Use	Best	Best	Do Not Use			Combustible	2375 by Tyg	PTFE			no	no		
Acetyl Acetone	Caution	Best	[n/r]	Caution			flammable	PTFE				yes	test		
Acetyl Acetone		Best					flammable	PTFE			Teflon-Kalrez upgrade if	yes	SDS		
Acetylene Tetrabromide	[n/r]	Fair	[n/r]	Best			neither	PTFE				no	no		
Acid Blend FP (3124) (Spartan Chemical Company)			Best				neither	2375 by Tygon				yes		June-July 202	
Acid Blend FP (Spartan)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE			yes	sds		
Acid Brite #2 (Birko)	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE			yes	no		
Acid Red 52	Best	Best	Best	Best			neither	2375 by Tyg	PTFE			yes	yes		
Acidic Vinegar 20% (not food grade)	Do Not Use	Fair	Good	Best				Tygon 2375				yes	test		
Acidsafe Degreaser/Neutrilizer	n/r	best	n/r	n/r			neither	2375 by Tyg	PTFE			yes	sds/		
Acrifix 1S 0117	Do Not Use	Do Not Use	Do Not Use	Best	Best		Flammable	PTFE				yes	no		
Acrylic Acid	Do Not Use	Best	Do Not Use	Do Not Use			neither	2375 by Tyg	PTFE						
Acrylic Acid Glacial by Chemstock			Good				combustible	2375 by Tyg	PTFE		Must have Teflon Kalrez	yes		entered may 3	
Acrylonitrile (Vinyl Cyanide)	Do Not Use	Best	[n/r]	Do Not Use			Combustible	2375 by Tyg	PTFE			no	tested		
Acrysol™ RM 8W Rheology Modifier (DOW)			Good				neither	2375 by Tygon				yes		June-July 202	
Acrysol™ RM-2020 NPR Rheology Modifier (DOW)			Good				neither	2375 by Tygon			May be thickish and slow	yes		June-July 202	
ACTICIDE 14	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
ACTICIDE A2	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
ACTICIDE CBM 2 (THOR)				BEST			Neither	Tygon 2375	PTFE			sds	mfg recommended	5/1/2018	
ACTRIL DS	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
Adapt 997	Best	Best	Best	Best			neither	PVC	2375 by Tygo		This liquid is thick and may require heating for satisfactory fluid flow.				
AEROSL OT-75 SURFACTANT (CYTEC)			BEST	BEST			Flammable	Tygon 2375	PTFE			sds		5/1/2018	
AEROSOL OT-75 SURFACTANT by Cytec			Best	Best			Flammable	PTFE				sds	MFG Recommends	April 24 2022	
AeroTron-av Vapor Degreaser				Best			neither	PTFE			Teflon-Kalrez upgrade r	yes	SDS		
AFCO 4312 Vigiliquat	Good	Good	Best	Good			neither	2375 by Tyg	PTFE			yes	sds+test		
AFCO 5262 Rubber DDET II	Do Not Use	Best	Caution	Do Not Use			neither	PTFE				y	MFG Recommends		
AGHRO ULTIMATE (SOLVAY)				Best			neither	2375 by Tyg	PTFE			yes	sds MFG recommended	entered may 3	
AGRITOX	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tyg	PTFE						
AI191066 Sparkling Citrus Fragrance (ARYLESSENCE)				Best			neither	PTFE				yes	SDS		

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
AIKEN CHEMICAL PURPLE POWER INDUSTRIAL Aircraft Soap	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE							
AJ200774 Citrus Sparkle Fragrance (ARYLESSENCE)	Best	Best	Best	Best			neither	2375 by Tyg	PTFE						
AKPEROX CAP33 FR (MEPK) (AKPA)						Best	Flammable	PTFE					yes	SDS	
AL217733 Fresh Breeze Fragrance (ARYLESSENCE)				Best			neither	PTFE					yes	SDS and Test	4/15/2024
ALBAROL	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE				yes	SDS	
Alberdingk @ AC 2538	Best						Neither	Tygon2375					SDS		Feb-17
Alkazene	Caution	Caution	[n/r]	Good			neither	PTFE			Wash				
All Purpose	Do Not Use	Good	Good	Best				Gas Grade H	PTFE				yes	test	
ALLIGARE TRICLOPYR 4				BEST			neither	Tygon 2375	PTFE				yes		June 04 2019
Allyl Alcohol	Caution	Best	n/r	Caution			Flammable	2375 by Tyg	PTFE				no	no	
Almabor TMBX						Best	Flammable	PTFE					yes	SDS	
Alodine 600 RTU	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE				yes	MFG Recommends	
Alpet E3 Plus or SmartSan Fragrance Free	Do not use	Do not use	Best	Do not use			Flammable	2375 by Tyg	PTFE	Flamm	Tygon 2375 hose is recy	yes	sds/questionnaire		
Alpha Cypermethryn	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
Alpha EF-6000 Flux	Do Not Use	Best	Good	Best			Flammable	2375 by Tyg	PTFE				yes	tested	
Alpha Neutral Flux 373	Do Not Use	Best	Do Not Use	Do Not Use			Flammable	2375 by Tyg	PTFE				yes	MFG Recommends	
Aluma Brite	Do not use	Good	Good				neither	2375 by Tyg	PTFE				yes	SDS + Test	
ALUMAL Bright C393				Best			neither	PTFE					yes	SDS	
ALUMAL DEOX 444				Best			neither	PTFE					yes	SDS	
ALUMAL ELOX 557		Best					neither	PTFE					yes	SDS	
ALUMAL ETCH 235		Best		Best			neither	PTFE					yes	SDS	
ALUMAL SEAL MTS 909	Good	Good		Best			neither	PVC	PTFE				yes	SDS	
Aluminium Acetate	Good	Best	Best	Good			neither	2375 by Tyg	PTFE				no	no	
Aluminium Bromide	Good	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
Aluminium Chloride 20%	Best	Best	Good	Good			neither	2375 by Tyg	PTFE				no	no	
Aluminium Fluoride 20%	Best	Good	Best	Good			neither	2375 by Tyg	PTFE				no	no	
Aluminium Nitrate	Good	Best	best	Good			neither	2375 by Tyg	PTFE						
Aluminium Salts	Best	Best	Good	Good			neither	2375 by Tyg	PTFE						
Aluminium Sulfate 10%	Best	Best	Good	Good			neither	2375 by Tyg	PTFE						
Aluminum chloride hydroxide	Best	Best	Good	Good			neither	2375 by Tyg	PTFE						
Aluminum Chloride Hydroxide Sulphate	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE				yes	sds	
Aluminum chloride, basic	Best	Best	Good	Good			neither	2375 by Tyg	PTFE						
Aluminum chlorohydrate	Best	Best	Good	Good			neither	2375 by Tyg	PTFE						
Aluminum hydroxychloride	Best	Best	Good	Good			neither	2375 by Tyg	PTFE						
Aluminum oxychloride	Best	Best	Good	Good			neither	2375 by Tyg	PTFE						
Alumon EN (Surpass Cleaning Solution)	Good	Best	Best	Good			neither	2375 by Tyg	PTFE	All pumps work			yes	SDS + Test	
Alums- NH3-Cr-K	Best	Best	Good	Caution			neither	2375 by Tyg	PTFE						
America's Choice Diesel Motor Oil 10W, 20W, 30W	Do Not Use	Do Not Use	Do Not Use	Best									yes	sds	
AMERZINE (Drew Marine)		BEST					neither	Tygon 2375	PTFE				yes	sds+mfg recommends	Sept 14-19
Ammonia	Good	Best	Best	Do Not Use			neither	2375 by Tyg	PTFE						
Ammonium Acetate	Good	Good	Best	Best			neither	2375 by Tyg	PTFE						
Ammonium Carbonate 10%	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Ammonium Chloride	Good	Best	Best	Good			neither	2375 by Tyg	PTFE		Test				
Ammonium Dibasic	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Ammonium Hydroxide / Aqua Ammonia	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Ammonium Monobasic	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Ammonium Nitrate	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Ammonium Persulfate	Do Not Use	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
Ammonium Phosphate(Di, Tri, & Mono)	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Ammonium Salts	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Ammonium Sulfate	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Ammonium Sulphide	Best	Best	[n/r]	Good			neither	2375 by Tyg	PTFE						
AMP - Ultra PC 2000 Neutralizing Amine	Do Not Use	Best	Do Not Use	Do Not Use			Combustible	2375 by Tyg	PTFE		Teflon Kalrez fluid path	yes	sds + manufacturer letter		
Amp-95	fair	Good	fair	Good			Flammable	2375 by Tyg	PTFE				yes	SDS + Test	June-July 202
Amyl- Acetate	Do Not Use	Good	Best	Do Not Use		Best	neither	PTFE			Teflon-Kalrez fluid path upgrade recommended				
Amyl -Alcohol	Good	Best	fair	Caution			Flammable	2375 by Tyg	PTFE						
Amyl- Borate	Best	Good	[n/r]	Best			neither	PTFE							

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Amyl -Chloride	Good	Do Not Use	[n/r]	Good			neither	PTFE							
Amyl Naphthalene	Do Not Use	Caution	[n/r]	Best		Best	flammable	PTFE							
AN241285 Lemon Sparkle Fragrance (ARYLESSENCE)				Best			Flammable	PTFE					yes	SDS	
Ancamine ® K54 Curing Agent	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	neither	PTFE					yes	sds+ test	
Andisil 1891 Silane				Best			Combustible	Tygon2375	Vitob				SDS		Feb-17
Anhydrous Ammonia	Good	Best	Best	Do Not Use			neither	2375 by Tyg	PTFE						
Anhydrous Hydrazine	Good	Best	Best	Caution			neither	PTFE							
Anhydrous Hydrogen Fluoride	[n/r]	Caution	[n/r]	[n/r]		Best	neither	PTFE							
ANHYDROUS SODIUM METASILICATE		Best					neither								Aug-19-20
Aniline	Do Not Use	Best	Good	Fair			neither	PTFE							
Aniline Dyes	Do Not Use	Best	Good	Fair			neither	PTFE							
Aniline Hydrochloride 20%	Good	Good	Best	Best			neither	PTFE							
Aniline Oil	Do Not Use	Best	Good	Best			neither	PTFE							
Animal Fats	Best	Good	Good	Best			neither	2375 by Tyg	PTFE						
ANSULEX Low pH	Best	Best	Good	Do Not Use			neither	2375 by Tyg	PTFE				yes	MFG Recommended	
Anti Freeze (glycol)	Best	Best	Good	Do Not Use			neither	2375 by Tyg	PTFE						
Anti Static Liquid	Do Not Use	Best	Do Not Use	Do Not Use			Combustible	Tygon 2375	PTFE				yes	sds	
Antifreeze (Ethylene Glyco, Diethylene Glycol)	Do Not Use	Best	Best	Do Not Use			neither	2375 by Tyg	PTFE						
AntiFreeze Alcohol Based	Do Not Use	Best	Best	Do Not Use			Flammable	2375 by Tyg	PTFE						
AP-5	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE				yes	MFG Recommended	
APROVIA FUNGICIDE				Best			neither	Tygon 2375	PTFE				yes	sds MFG recommended	entered may 4
Aqua Ammonia	Good	Best	Good	Best			neither	2375 by Tyg	PTFE				yes		
Aqua Regia	Do Not Use	do Not Use	[n/r]	Do Not Use			neither								Polypropylene does not like this liquid
AQUA ROOT	Do Not Use	Best	[n/r]	Do Not Use			neither	2375 by Tyg	PTFE						
Aqualine R110	Good	Good	Best	Best			neither	2375 by Tyg	PTFE						
AQUAMAID LIQUID PENETRATING WETTING	Do Not Use	Best	Good	Do Not Use			neither	2375 by Tyg	PTFE						
AQUAMASTER	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tyg	PTFE						
Aquanox A4615			Best				neither	Tygon2375	PTFE				yes	SDS and MFG recommended	
Aquanox A4625B	Good	Best	Best	Good			neither	2375 by Tyg	PTFE				yes	no	
AQUA-SOL 20/20 wetting agent	Do Not Use	Best	Best	Do Not Use			neither	2375 by Tyg	PTFE				yes	MFG Recommended	
Aquathol - K herbicide (Endothall)	[n/r]	Good	[n/r]	Best			neither	2375 by Tyg	PTFE						
AquaVantage 815 GD / Formula 815 GD			Best				neither	2375 by tygon					yes	sds	Aug-19-20
AQUIFER LIQUID (AQUA AID)	Do Not Use	Best	[n/r]	Do Not Use			neither	2375 by Tyg	PTFE						
Arcot 9739 Brake Clean							Flammable						yes	SDS	
Ardeca Antifreeze Plus	Do Not Use	Best	Do Not Use	Do Not Use			neither	Tygon 2375	PTFE				yes	sds	
ARDOX 2871 (CHEMETALL)															Too thick for GT Pumps
ARDROX 295GD (Bulk) (BASF)				Best			neither	PTFE					yes	sds	9/16/2024
Ardrox 6333 A		Best					Neither	Tygon2375					SDS		Feb-17
ARMOR ALL PROTECTANT	Do Not Use	Best	Do Not Use	Do Not Use			neither	2375 by Tyg	PTFE				yes	MFG Recommended	
Armor Si		Best	Best				neither	Tygon2375	PTFE				yes	SDS	
Aromatic 100: Solvent 100 (UNIVAR)				Best			Flammable	PTFE					yes	SDS	
ARQUAD 2C-75 (AkzoNobel)			Best				Flammable	Tygon2375	PTFE				yes	Mfg recommended	
Arsenic Acid	Best	Best	Good	Good			neither	2375 by Tyg	PTFE						
ART BLASTER (JJ Chem)	Do Not Use	Best	Good	Do Not Use			neither	2375 by Tyg	PTFE						
ASafa	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE					yes		
ASAHIKLIN AK-225	[n/r]	Best	[n/r]	[n/r]			neither	PTFE					yes	MFG Recommended	
ASE-60	Best	[n/r]	[n/r]	[n/r]			neither	PTFE							
ASSAULT - Astec Chemical	Best	Do Not Use	Do Not Use	Best			neither	PTFE					yes	MFG Recommended	
ASTRO	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE							
Automate Blue 8AHF Liquid Dye				Best			Flammable	PTFE					yes	SDS	
Automatic Dish Gel (Biokleen)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE				yes	sds	entered May 4
Automatic Transmission Fluid	Best	Caution	[n/r]	Best			neither	Gas Grade H	PTFE						
Automotive Brake Fluid	Caution	Best	Best	Caution			neither	2375 by Tyg	PTFE						
AVANTOR PROPRIETARY SOLVENT III-1, ANH	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE							
Ax0441 Alcohol, Reagent Anhdrous GR ACS (Millipore Sigma)			Best				flammable	Tygon2375							Pennsylvania Growing
Axarel 1000	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE	Gas Grade Hose				yes		
AXL-General Purpose Degreaser AXAREL 2200 (MICROCARE)			Best				Flammable	PTFE					yes	SDS	
Axe Broadpectrum Herbicide		good		Best			neither	2375 by Tyg	PTFE				yes	SDS and Mfg recommed	3/10/2015

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
AZ 300 MIF Developer			Best				neither	PTFE			TEFLON KALREZ UPD		SDS		3/21/2018
Azadiractin	Good	Best	Caution	Best			neither	2375 by Tyg	PVC				yes	test	
B&B M34H ; BRIGHTENER B&B TRITECH				Best			neither	2375 by Tyg	PTFE		thickish		yes		entered may 3
B-17 Industrial Paint Remover				Best			neither	PTFE			Teflon-Kalrez upgrade r		yes	SDS	
B4 INDUSTRIAL PAINT REMOVER (Benko Sales)				Best			neither	PTFE					yes	sds	5/21/2025
B-750	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tyg	PTFE				yes		
BAC STOP 3A			Best				flammable	2375 by Tygon					yes	sds	Aug-19-20
BADGE				Best			neither	Tygon 2375	PTFE		CHECK VISCOSITY BE		yes	sds MFG recommended	entered may 3
Baking Soda	Best	Best	Good	Good			neither	PVC	2375 by Tygon						
Balsamic Vinegar of Modena PGI			Best				neither	Tygon 2375	PTFE				yes	sds	8/16/2024
BAND-ADE Sawing Fluid	Best	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
BANISH				Best			Flammable	2378 by tygon					yes	sds	Aug-19-20
BANNER - fungicide	Do Not Use	Good	Do Not Use	Do Not Use			neither	2375 by Tyg	PTFE						
BANNER MAXX	Do Not Use	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
Barcroft MG HYD Dried Gel, Aluminum Hydroxid	Good	Good	[n/r]	Best			neither	2375 by Tyg	PTFE		May be too thick for GT		yes	test	
Barcroft MG HYD Paste, Water/Magnesium Hydr	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tyg	PTFE		May be too thick for GT		yes	test	
Barium Chloride	Best	Best	[n/r]	Good			neither	2375 by Tyg	PTFE						
Barium Hydroxide	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Barium Salts	Best	Best	[n/r]	Good			neither	2375 by Tyg	PTFE						
Barium Sulfide	Good	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
Bark Oil Red LT	n/r	n/r	n/r	best			neither	viton	PTFE				yes	sds	
BARREL	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
BARRICADE	Do Not Use	Best	[n/r]	Best			neither	2375 by Tyg	PTFE		This flowable liquid may		yes	MFG Recommended	
Barsol A22710				Best			Flammable	PTFE					yes	SDS	
Barsol A-4165	Do Not Use	Good	Do Not Use	Do Not Use			neither	2375 by Tyg	PTFE				yes	MFG Recommended	
BARSOL A-4498				Best		Best	Flammable	PTFE					yes	sds	7/30/2024
BASF 352-91 IL Reducer Normal	do not use	do not use	do not use	do not use		Best	neither	PTFE							
Basonat® HW 1000 (old Basonat® HW 100 BASF)		Good		Best		Good	neither	PTFE					yes	SDS, MFG Recommended	June-July 202
BAYCOR 300	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tyg	PTFE						
BAYFIDAN 250 EC	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tyg	PTFE						
BAYLETON 125 EC	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
Baymedix AP501 (covestro)							neither				Dry air Best		SDS		3/15/2017
BAYTAN C Flowable seed dressing	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tyg	PTFE		This flowable liquid may be too thick				
BEEMR Blanke/ Roller Wash for UV & EB Inks	do not use	do not use	do not use	best			combustible	Viton hose	PTFE				yes	sds	
Beer	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Beet Sugar Liquors	Best	Good	[n/r]	Best			neither	2375 by Tyg	PTFE						
BELPOL 240	Good	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
BELPOL 280	Best	[n/r]	[n/r]	Good			neither	2375 by Tyg	PTFE						
BELPOL Ardeca Antifreeze Plus	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
BELPOL HDR	Caution	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
BELPOL Omnium	Best	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
BELPOL Traffic	Caution	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
BELPOL Transclean	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
Benefit Phosphate Free Liquid Chlorinated Clea	n/r	best	n/r	n/r			neither	2375 by Tyg	PTFE						
Benzaldehyde 10%	Do Not Use	Best	[n/r]	Caution		Best	neither	PTFE			Needs nylon housing and PTFE o-rings				
Benzene	Do Not Use	Do Not Use	Do Not Use	Good		Best	Flammable	PTFE							
Benzenesulfonic Acid 10%	Do Not Use	Caution	[n/r]	Best			neither	PTFE							
Benzine( Gasoline)	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	Gas Grade H	PTFE						
Benzoic Acid	Fair	Caution	Caution	Best			neither	PTFE							
Benzoyl chloride	[n/r]	n/r	[n/r]	[n/r]		Best	neither	PTFE			Test				
Benzyl Alcohol	Do Not Use	Good	[n/r]	Best			neither	PTFE							
Benzyl Benzoate	Do Not Use	Good	[n/r]	Best			neither	PTFE							
Benzyl Chloride	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE							
Bergamot Oil CE-618-352-4(GIVAUDAN)				Best			neither	PTFE			Teflon-Kalrez fluid path		yes	SDS	
Berryman B-12 Chemtool Fuel Injector Cleanei					require	Best	Flammable	PTFE			Teflon-Kalrez pump with		yes	SDS	
BestSolve Sierra				Best			neither	PTFE			Teflon-Kalrez upgrade r		yes	SDS	
Betaseal 43555 Primer	Best	Do Not Use	Do Not Use	Do not Use			neither	PTFE			May need regular replac		yes	test	

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Bevro-Sheen by Ecolab		Best					neither	2375 by Tygon	PTFE				yes	SDS and Mfg recommended	3/10/2015
BG Non-Chlorinated Brake Cleaner				Best	required		flammable	PTFE					yes	SDS	
Big Blue by TRC				Best			neither	2375 by Tygon	PTFE				yes	sds	3/10/2015
BIOACT EC-7R	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE	2375 by Tygon				yes	SDS	
Bioact® EC-7R™ Original Formula	Do Not Use	Do Not Use	Do Not Use	Best	Required		Flammable	Viton hose	PTFE				yes	SDS + notes from customer	9/13/2015
BioAer SC-10 Cleaner	Do Not Use	Do Not Use	Do Not Use	Best			neither						yes	test	
Biocide HS 15%	Do Not Use	Do Not Use	Do Not Use	Do Not Use		BEST	neither	PTFE					yes	sds	entered May 2024
Biocide HS 15%	Do Not Use	Do Not Use	Do Not Use	Do Not Use		BEST	neither	PTFE					yes	sds	entered May 2024
Bio-Circle L	[n/r]	Best	Best	[n/r]			neither	PVC	2375 by Tygon				yes	MFG Recommended	
Biodiesel: also B5, B10, B20, B50, B95, B100	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE						
BioFoamer (BIOSAFE)				Best			neither	Tygon2375	PTFE				yes	SDS	
Biokut HD 20	[n/r]	[n/r]	[n/r]	best			neither	2375 by Tygon	PTFE				yes	sds label and mfg recommendation	
BIOPREP	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE							
BIOSIDE HS-15 (Perasan)	Do Not Use	Do Not Use	Do Not Use	Do Not Use		BEST	neither	PTFE					yes	SDS	Sept 14-19
BIO-SOLV	do not use	best	do not use	do not use			flammable	PTFE					yes	sds	
BioVantage	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon							3/10/2015
BIRKO-OX				Best			Flammable	Tygon 2375	PTFE				yes	sds	11/11/2024
Bis (2-ethylhexyl) adipate	[n/r]	[n/r]	[n/r]	Best			neither	PTFE					yes	sds+test	
Bismuth Nitrate Solution 22.5% (2927)	Do Not Use	Do Not Use	Do Not Use	Best			neither						yes	sds	
Bitter Almond Oil	[n/r]	Fair	Best	[n/r]			neither	PVC	2375 by Tygon				yes	test	
Black Dip and Spray Primer	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE					yes	Manufacturer Recommended	
Black Dye #D1972 (French Color)	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
Black Sulphate Liquors	Best	Best	[n/r]	Best			neither	PTFE							
BLAZER	Best	[n/r]	[n/r]	[n/r]			neither	PTFE							
BLOCKER 4F	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE							
Blue Coral Hi pH 3692 Pre-soak	[n/r]	Best	[n/r]	[n/r]			neither	PTFE					yes	Manufacturer Recommended	
Blue Coral Lo pH 140 Presoak	[n/r]	[n/r]	[n/r]	Best			neither	PTFE					yes	Manufacturer Recommended	
BLUE DRESSING	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
Blue Dye #D878 (French Color)	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
Bonderite C-AK 1036 Alkaline	Do not use	Best	Do not use	Do not use			neither	2375 by Tygon	PTFE				yes	sds	
Bonderite C-IC 2520	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE				yes	SDS	
Bonderite C-IC Alrem Aero; Turco Alumifilm Remover L; TPV-R	Best						neither	2375 by Tygon	PTFE				yes	sds MFG recommended	entered may 2024
Bonderite C-IC Scalegon 5 Aero	Best	Best	Good	Good			neither	PTFE					yes	Manufacturer Recommended	
Bonderite C-SO 4460-BK Bulk	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	Flammable	PTFE					yes	Manufacturer Recommended	
Bonderite M_CR 407 Chromate	Do not use	Do not use	Do not use	Best			neither	2375 by Tygon	PTFE				yes	sds	
BONDERITE M-CR-ACCELAGOLD BULK (ALODINE)				Best			neither	2375 by Tygon	PTFE				yes	sds MFG recommended	entered may 2024
Boost 3200	[n/r]	[n/r]	[n/r]	[n/r]		Best	neither	2375 by Tygon	PTFE				yes	Manufacturer Recommended	
Boost 3201	[n/r]	[n/r]	[n/r]	[n/r]			Flammable	2375 by Tygon	PTFE				yes	Manufacturer Recommended	
Boost O2				Best			flammable	Tygon2375	PTFE				yes	SDS	
Borax (Sodium Borate)	Good	Best	Best	Good			neither	2375 by Tygon	PTFE						
Bordeaux Mixture (Copper Sulfate Salt)	Good	Best	[n/r]	Best			neither	2375 by Tygon	PTFE						
Boric Acid	Best	Good	Good	Best			neither	2375 by Tygon	PTFE						
Boron Fluids	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
BORON TRIFLUORIDE-DIETHYL ETHER COMPLEX						yes	flammable	PTFE TEFLON					yes	sds	Aug-19-20
Botanisil GB-40	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE				yes	sds	
Brake & Parts Clean CA 10% VOC (by Cyclo Ind)	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	Flammable	PTFE			Teflon-Kalrez		yes		
Brake & Parts Cleaner (SOLUTIONS PLUS)				Best	required		flammable	PTFE					yes	SDS	
Brake Clean Plus VOC (Crystal Clean)						Best	Flammable	PTFE					yes	sds	7/31/2024
Brake Cleaner (QUALITY BLENDING)				Best			flammable	PTFE			Teflon-Kalrez fluid path		yes	SDS	
BRAKE CLEANER (Radiator Specialty of Canada)				Best	required		Flammable	PTFE					SDS		
Brake Cleaner/NON Chlorinated (Keller-Heardt)				Best			flammable	PTFE	Gas Grade				SDS		3/15/2017
Brake Fluid (non petroleum)	Do Not Use	Best	[n/r]	Caution							Test				
Brake Wash by ZEP	Do Not Use	Do Not Use	Do Not Use	Best	Required		Flammable	PTFE					yes		
Brakeparts Cleaner (DEERE)						Best	flammable	PTFE					yes	SDS	
Brakleen 0503 (CRC)			Best				flammable	PTFE			Teflon-Kalrez fluid path		yes	SDS	
Brakleen 05053 (Acetone 90% + some hexanes)	do Not Use	Best	Good				Flammable	PTFE			TEFLON KALREZ FLUID		yes	SDS AND TEST	Nov-22
Brakleen 05090 ( Tetrachloroethylene 100%) (CRC) 1 gallon				Best	Required			PTFE					yes	SDS AND TEST	Jun-21
Brakleen 05091 (CRC)				Best			neither	PTFE					yes	SDS	

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Brakleen 05093 ( Tetrachloroethylene 90 - 100%) (CRC) 55 gallon				Best		Required		PTFE			Celcon tap required		SDS		Apr-18
Brakleen® 05051 Brake parts cleaner non-chlorinated - 1 Gallon	Best					Best	Flammable	PTFE			TEFLON KALREZ FLU		yes	SDS AND TEST	Jan-22
Brakleen® 05087 Brake parts cleaner non chlorinated - 55 Gallon (CRC) (Toluene - Methanol)						Best	Flammable	PTFE					yes	SDS AND TEST	Mar-21
Brayco 922				Best			Flammable	PTFE					yes	tested	
BRC Brake Clean Non-Chlorinated				Best		required	flammable	PTFE			Celcon Tap Required		yes	SDS	
Bright Nickel Adjuster	Best	Best	Good	Good			neither	2375 by Tyg	PTFE				yes	tested	
Brine	Best	Best	[n/r]	Good			neither	PVC	2375 by Tygon	Test					
BRODAL	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tyg	PTFE						
Bromine	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE							
Bromine- Water	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE							
Bromobenzene	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE							
BromochloroTrifluoroethane	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
Brown Dye #D883 (French Color)	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
Bruilin 1375	[n/r]	[n/r]	[n/r]	Best			Flammable	Viton	PTFE				yes	MFG	
Bruilin 850	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE							
Bruilin MP 1793	Good	Do Not Use	Do Not Use	Best			Flammable	Viton	PTFE				yes	MFG	
BRYTOFA	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tyg	PTFE						
BUCTRIL 200	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
BUCTRIL MA	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
BUENA 6	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tyg	PTFE						
BUGMASTER FLO	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tyg	PTFE						
Bulk Eucalyptus Oil (FBG)				Best			flammable	PTFE					yes	SDS	
BULLDOCK 25 EC	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
BULLDOCK 8 UL	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
Bunker Oil	Best	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE						
BUSAN 1060				Best			neither	2375 by Tygon					yes	sds	Aug-19-20
Busch R 590 Vacuum Pump Oil	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	mfg	
Butadiene	fair	Do Not Use	Do Not Use	Best			Flammable	2375 by Tyg	PTFE						
Butadiene-Styrene Copolymer	n/r	n/r	n/r	Best			Neither						yes		
Butane (LPG)	Best	Good	Fair	Fair			Flammable	Gas Grade H	2375 by Tygon						
Butanol	Good	Best	Fair	Good			Flammable	2375 by Tyg	PTFE				yes	sds	
Butanone (MEK)	Do not use	Good	Best	Do not use			Flammable	PTFE					yes	note	
Butter	Best	Best	[n/r]	Good			neither	2375 by Tyg	PTFE						
Butyl Acetate	Do Not Use	Best	Best	Do Not Use			Flammable	PTFE							
BUTYL ACETYL RICINOLEATE	fair	Caution	caution	Best			neither	PTFE							
Butyl Acrylate	[n/r]	Best	Good	[n/r]			neither	PTFE							
Butyl Alcohol	Good	Good	[n/r]	Best			Flammable	2375 by Tyg	PTFE				s		
Butyl Amine	Best	Do Not Use	[n/r]	Best			neither	PTFE							
Butyl Carbitol	Good	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
Butyl Cellosolve	Do Not Use	Best	[n/r]	Do Not Use			Combustible	PTFE							
Butyl Cellosolve Adipate	Caution	Best	[n/r]	Caution			neither	PTFE							
Butyl Oleate	Good	Caution	[n/r]	Best			neither	PTFE							
Butyl Stearate	Good	Caution	[n/r]	Best			neither	PTFE							
Butylene	Best	Do Not Use	Do Not Use	Best			neither	PTFE							
Butyraldehyde	Caution	Caution	[n/r]	Caution			neither	PTFE							
Butyric Acid	Do Not Use	Best	Best	Best			neither	PTFE					s		
BVA 2	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE							
BW-17	Do Not Use	Best	Good	Do Not Use			neither	Tygon 2375	PTFE				yes	product data sheet	
BW-48	Good	Good	Good	Best			neither	Tygon 2375					yes	product data sheet + test	
BW-52 and BW-64	Do Not Use	Good	Good	Best			neither	Tygon 2375	PTFE				yes	product data sheet + test	
B-Webb Non Chlor Brake Cleaner							Flammable	PTFE					yes	SDS	
BYK-016 (BYK)				BEST			Neither	Tygon 2375	PTFE				sds	mfg recommended	5/1/2018
BYK-323	Do Not Use	Best	Fair	Do Not Use			neither	2375 by Tyg	PVC				yes	MFG	
BYK-354	n/r	n/r	n/r	Best			Flammable	PTFE					yes	MFG	
BYK-A 555				Best			Flammable	PTFE	Viton				yes	SDS	
BYK-A 560				Best			Flammable	PTFE	Viton				yes	SDS	
BYK-R 605				Best			Flammable	PTFE	Viton				yes	SDS	

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
BYK-UV 3530	n/r	Best	n/r	Best			neither	PTFE					yes	both	
BYK-W 9010	n/r	Best	n/r	Best			neither	PTFE					yes	both	
C K Neut Pair A		Best					neither	Tygon 2375	PTFE						Sept 14-19
C K Neut Pair B		Best					neither	Tygon 2375	PTFE						Sept 14-19
C&H RADIANCE Cooling Water Treatment		Best					neither	Tygon 2375	PTFE				yes		Sept 14-19
C134	n/r	n/r	n/r	Best			neither	2375 by Tygon	PVC				yes	MFG	
C4U Hand Sanitizer (GULF COAST)			Best				flammable	Tygon2375	PTFE				yes	SDS	
C6 Fluorinated Chemical	Good	Best	Good	Do Not Use			neither	PTFE					yes	test	
Cage Klenz 100		Best					neither	Tygon 2375	PTFE				yes	MFG	Sept 14-19
Cage Klenz 150		Best					neither	Tygon 2375	PTFE				yes	MFG	Sept 14-19
Cage Klenz 180		Best					neither	Tygon 2375	PTFE				yes	MFG	Sept 14-19
Cage Klenz 200				Best			neither	Tygon 2375	PTFE				yes	MFG	Sept 14-19
Cage Klenz 220		Best					neither	Tygon 2375	PTFE				yes	MFG	Sept 14-19
Cage Klenz 250		Best					neither	Tygon 2375	PTFE				yes	MFG	Sept 14-19
Cage Klenz 280				Best			neither	Tygon 2375	PTFE				yes	MFG	Sept 14-19
Cage2Wash 5	do Not Use	fair	Fair	Best			neither	2375 by Tygon	PTFE				yes	sds	
Calcine Liquors	Good	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
Calcium Acetate	Good	Best	[n/r]	Good			neither	2375 by Tygon	PTFE						
Calcium Bisulfide	Best	Do Not Use	[n/r]	Best			neither	PVC			2375 by Tygon				
Calcium Carbonate (Chalk)	Best	Best	[n/r]	Good			neither	PVC			2375 by Tygon		s		
Calcium Chloride (Brine)	Best	Best	Good	Good			neither	PVC			2375 by Tygon		s		
Calcium Cyanide	Best	Best	[n/r]	[n/r]			neither	PTFE					s		
Calcium Hydroxide	Good	Best	Best	Good			neither	PVC			2375 by Tygon		s		
Calcium Hypochlorite	Caution	Good	Best	Best			neither	PVC			2375 by Tygon		s		
Calcium Nitrate	Best	Best	[n/r]	Good			neither	PVC			2375 by Tygon		s	yes	MFG
Calcium Phosphate	Best	Best	[n/r]	[n/r]			neither	2375 by Tygon	PVC				s		
Calcium Salts	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PVC				s		
Calcium Silicate	Best	Best	[n/r]	[n/r]			neither	2375 by Tygon	PVC				s		
Calcium Sulfide	Good	Best	[n/r]	Best			neither	2375 by Tygon	PVC				s		
Calcium Sulphite	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PVC				s		
Calcium Thiosulphate	Good	Best	[n/r]	Best			neither	PTFE					s		
Calfoam SLS 30	n/r	n/r	n/r	Best			neither	PTFE					s	yes	SDS
Calibration Fluid	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE					s		
CALIBRATION FLUID 4113	Best	[n/r]	[n/r]	[n/r]			neither	PTFE					s		
CAM2 D/M ATF (automatic transmission fluid)	Good	do not use	n/r	Best			neither	Gas Grade Hose					yes	SDS + Test	
Cane Sugar Liquors	Best	Good	[n/r]	Best			neither	PVC			2375 by Tygon		s		
Capric Acid	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						entered May
Caproic Aldehyde	[n/r]	Good	[n/r]	[n/r]			neither	PTFE			Wash		s		
Capstone FS-31	Do Not Use	Best	Do Not Use	Best			neither	PTFE			May be too viscous		s	yes	SDS + MFG
Capstone FS-3100	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither	PTFE			May be too viscous		s	yes	
Capstone FS-34	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			May be viscous		s	yes	
Capstone FS-35	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			May be viscous		s	yes	
Capstone FS-50 Fluorosurfactant	Do Not Use	fair	Best	Do Not Use			Flammable	PTFE					s	yes	SDS
Capstone ST-100HS	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			Liquid is viscous		s	yes	SDS
Capstone ST-500	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			No compatible pump		s		
CAPTAN 50WP				Best			neither	Tygon 2375	PTFE				yes	sds MFG recommended	entered may
Car Brite White Lightning Acid Based Wheel Cleaner	[n/r]	[n/r]	[n/r]	Best			neither	PTFE					yes	MFG	
CARB X	Do Not Use	Do Not Use	Do Not Use	Do Not Use	Recomm	Best	Flammable	PTFE			Teflon	Groundable Pump Reco	yes	MFG	
Carbamate	Caution	Caution	[n/r]	Best			Flammable	PTFE							
Carbitol	Good	Best	[n/r]	Best			Combustible	PTFE			Wash				
Carbolic Acid	Caution	Good	Good	Fair			neither	PTFE							
Carbon Bisulfide	Caution	Caution	[n/r]	Best			neither	PTFE			Test				
Carbon Dioxide	Best	Do Not Use	Do Not Use	Best			neither	PVC			2375 by Tygon				
Carbon Disulphide	Caution	Do Not Use	Do Not Use	Best			neither	PVC			2375 by Tygon				
Carbon Monoxide	Good	Best	Good	Best			neither	PVC			2375 by Tygon				
Carbon Tetrachloride	Caution	Do Not Use	Do Not Use	Good			neither	PTFE							
Carbonic Acid	Fair	Best	[n/r]	Best			neither	PVC			2375 by Tygon				



Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Carus 3180 Water Treatment				Best			neither	Tygon2375	PTFE				yes	SDS	
CAS 103-23-1 BIS...Adipate	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
CASCADE PLUS DEEPER ROOTS	Do Not Use	Best	[n/r]	Do Not Use			neither	2375 by Tyg	PTFE						
Castor Oil	Best	Good	Good	Best			neither	PVC	2375 by Tygon				yes	SDS	
Castrol Kleen 3212	[n/r]	Best	Best	[n/r]			neither	2375 by Tyg	PTFE				yes	SDS	
Catalyst 23Lv	Caution	Best	Good	Best			neither	2375 by Tyg	PTFE				y	Test	
Caustic Potash	Fair	Best	Best	Fair			neither	2375 by Tyg	PTFE						
Caustic Potash Lye	Fair	Best	Best	Fair			neither	2375 by Tyg	PTFE						
Caustic Soda Liquid, Sodium Hydroxide	Fair	Best	Best	Fair			neither	2375 by Tyg	PTFE						
Caustic Soda Up to 40%	Fair	Best	Best	Fair			neither	2375 by Tyg	PTFE						
Caustic Soda up to 60%	Fair	Best	Best	Fair			neither	2375 by Tyg	PTFE						
CB 100 ALU						BEST	neither	PTFE					yes	sds+mfg recommends	Sept 14-19
CDA 19-3/19 OPF/ MIBK RHS/ 150103	Fair	Best	Best	Fair			Flammable	PTFE					y	MFG	
Cedarwood Oil Virginiana	n/r	n/r	n/r	Best			neither	PTFE					y	MFG	
CEE-BEE A-882 ( CEE-BEE)		Best	Best				Neither	Tygon 2375	PTFE				yes	SDS + mfg recommended	5/1/2018
CEE-BEE A-882 ; ALK CLEANER TURCO		Best	Best				neither	2375 by Tyg	PTFE				y	SDS + mfg recommended	
Cee-Bee C-623				Best			neither	Tygon 2375	PTFE				yes	SDS	4/29/2024
CEE-BEE J-84AL	Do Not Use	Best	Best	Do Not Use			neither	2375 by Tyg	PTFE				y	SDS	
Cellosolve	Caution	Good	[n/r]	Caution			neither	PTFE							
Cellosolve Acetate	Do Not Use	Good	[n/r]	Best		Best	neither	PTFE							
Cellosolve Butyl	[n/r]	Best	[n/r]	[n/r]			neither	PTFE							
Cellugard	[n/r]	Best	[n/r]	[n/r]			neither	PTFE							
Centron Diesel Fuel Saver	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE							
Cetane (Hexadecane)	Best	[n/r]	[n/r]	Best			neither	PTFE							
CFT Legumine	Do Not Use	Best	Best	Do Not Use			neither	PTFE					yes	test	
Chain and Cable:chain and cable Heavy (Lubripla	[n/r]	[n/r]	[n/r]	best			neither	PTFE					yes	sds	
Chairside Monomer for Hard Reliner	Good	best	n/r	n/r			Flammable	PTFE					yes	SDS + Test	
CHARSOL SUPREME HICKORY	do not use	best	best	Good			neither	2375 by Tyg	PTFE				yes	SDS + Test	
Cheetah Pro (NEWFARM)	Good			Best			flammable	Tygon2375	PTFE				yes	SDS & Vendor Recommended	
Chelate Additive			Best				neither	2375 by Tygon					yes	SDS	
CHEM AQUA 15000MT	Do Not Use	Best	Do Not Use	Do Not Use			neither	2375 by Tyg	PTFE				yes	MFG	
CHEM AQUA 900	Good	Good	Best	Best			neither	2375 by Tyg	PTFE						
CHEM AQUA NA-104C	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE						
Chem Cote 3010 (BASF)				Best			neither	2375 by Tygon					yes	SDS	June-July 202
CHEMCOA Solvent Blend 44				Best			flammable	PTFE TEFLON					yes	sds	Aug-19-20
Chem-Crest SolvaClean (Crest Ultrasonics)				Best			neither	PTFE					yes	sds	7/29/2024
Chemlok 218	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither						yes	sds	
Chemlube 800	n/r	n/r	n/r	best			neither	Gas Grade H	PTFE		This is a coating liquid a		yes	sds	
Chemtrol Scrub-Mate	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE		may be too thick		yes	sds	
Chevron Hydraulic Oil AW	Best	[n/r]	[n/r]	Best			neither	Gas Grade H	PTFE				yes	mfg	
Chevron Rando HD Premium Oil MV	Best	[n/r]	[n/r]	Best			neither	Gas Grade H	PTFE				yes	mfg	
Chevron Super Plus 15W-40 Motor Oil	Best	[n/r]	[n/r]	Best			neither	Gas Grade H	PTFE				yes	mfg	
China Wood Oil	Best	[n/r]	[n/r]	[n/r]			Combustible	PTFE			A coating liquid				
CHIPCO 26GT	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tyg	PTFE						
CHLORDANE	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
Chlorextol	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
Chlorine	Caution	Caution	Caution	Best			neither	PTFE							
Chlorine (Wet)	Caution	Caution	Caution	Best			neither	PTFE							
Chlorine Dioxide	Do Not Use	Caution	[n/r]	Best			neither	PTFE							
Chloroacetone	Do Not Use	Best	Best	Do Not Use			neither	PTFE							
Chlorobenzene (Mono)	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE			Test				
Chlorobromo-Methane	Caution	Good	[n/r]	Do Not Use			Flammable	PTFE			Test				
Chlorobutadiene	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE			Test				
Chlorododecane	Do Not Use	Caution	[n/r]	Best			neither	PTFE			Test				
Chloroform	Do Not Use	Do Not Use	Do Not Use	Best			neither	Viton	PTFE						
Chlorotoluene	Do Not Use	Caution	[n/r]	Best			Flammable	PTFE			Test				
Chrisal All Purpose	Fair	Good	Best	[n/r]			neither	PTFE							

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Chrisal Floor Cleaner	Do Not Use	Do Not Use	[n/r]	Good			neither	PTFE							
Chrisal Sanitary	Best	Do Not Use	[n/r]	Fair			neither	PTFE							
Chrome Alum	Good	Good	Best	Best			neither	PVC			2375 by Tygon				
Chrome Plating Solutions	Fair	Good	[n/r]	Best			neither	PTFE							
Chromic Acid 5%	Do Not Use	Best	[n/r]	Best			neither	PTFE			2375 by Tygon				
Chromic Oxide .88 WT.%,aqueous	Best	[n/r]	[n/r]	Best			neither	PTFE			2375 by Tygon				
Chromium Nitrate Solution	Do Not Use	Do Not Use	Do Not Use	Best			neither	Tygon 2375	PTFE						
Chute Lube ®				Best			flammable	PTFE	gas				yes	SDS	
CIMPERIAL 1070 (Millicron)	Best	Do Not Use	Do Not Use	Best			neither	PTFE			2375 by Tygon		yes	SDS + MFG	
CIMSTAR 3890 (Milacron)	Best	Do Not Use	Do Not Use	Best			neither	PTFE			2375 by Tygon		yes	SDS + MFG	
CIMTECH 320Z with INSOL Technology (SIMCOOL)			Best				neither	PTFE					yes	SDS	
CIMTECH 95 (Millicron)	Best	Do Not Use	Do Not Use	Best			neither	PTFE			2375 by Tygon		yes	SDS + MFG	
CIP 100		Best					neither	Tygon 2375	PTFE						Sept 14-19
CIP 130		Best					neither	Tygon 2375	PTFE						Sept 14-19
CIP 150		Best	Best				neither	2375 by Tyg	PTFE				yes	SDS	
CIP 200				Best			neither	Tygon 2375	PTFE				yes	SDS	Sept 14-19
CIP 220		Best					neither	Tygon 2375	PTFE						Sept 14-19
CIP Acid	n/r	n/r	n/r	Best			neither	2375 by Tyg	PTFE				yes	sds	
CIP Neutralizer		Best					neither	Tygon 2375	PTFE						Sept 14-19
Circulator 1645 (STONE LEIGH)			Best				neither	Tygon2375	PTFE				yes	SDS	
Cir-Q-Late			Best				neither	Tygon 2375	PTFE				yes	sds	11/11/2024
CITGO 19540	[n/r]	[n/r]	[n/r]	Best			neither	Gas Grade H	PTFE				yes	SDS	
CITRA CLEAN				best			neither								Aug-19-20
Citra-O	Do Not Use	Do Not Use	Do Not Use	best			neither	PTFE					yes	sds	
Citric Acid	Best	Good	Good	Best			neither	PVC			2375 by Tygon		s		
CitriSurf 2250	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE				yes	SDS + MFG	
Citrobio 55	fair	best	Good	Good			neither	2375 by Tyg	PTFE				yes	letter + test	
Citrus Assault (MULTI-CLEAN)			Best				neither						yes	SDS	
Citrus Burst 2	Do not use	Do not use	Do not use	Best			Flammable	2375 by Tyg	PTFE				yes	SDS + Test	
Citrus Foggers, MGK	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE							
CITRUS SOLVENT	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE					yes	mfg	
CLAY CUTTER	Best	Good	Good	Best			neither	2375 by Tyg	PTFE				yes	test	
CLEAN MIST				Best			neither	2375 by Tygon					yes	SDS	Aug-19-20
Cleangrow		Best	Best				neither	Tygon2375	PTFE				yes	SDS	
Clear Coat	Best	Do Not Use	Good	Best			neither	2375 by Tyg	PTFE				yes	test	
CLEARYS 3336	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE							
Coatosil MP 200	Good	Good	Good	Best			neither	2375 by Tyg	PTFE				yes	SDS + Test	
Cobalt Catalyst 510 12% (BORCHERS)				Best			neither	PTFE	Viton				yes	SDS & Mfg recommended	
Cobalt Chloride	Best	Caution	[n/r]	Best			neither	2375 by Tyg	PTFE						
Cobalt Hex-Cem 12%	Best	Do Not Use	Do Not Use	Best			neither	Gas Grade Hose							
Cobalt Nap-All 6% (BORCHERS)				Best			Combustible	PTFE	Viton				yes	SDS & Mfg recommended	
Cobalt Nitrate Solution 15%	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE						
Cobalt Solution 12% (Interplastic Corporation)				Best			neither	PTFE					yes	SDS-Customer Specified	
Cocamidopropyl Betaine	Do Not Use	Best	Do Not Use	Do Not Use			neither	2375 by Tyg	PTFE				yes	test	
Coco-Glucoside	do not use	Best	Good	Do Not Use									yes	test	
Coconut Oil	Best	Good	[n/r]	Best			neither	PVC			2375 by Tygon				
Cod Liver Oil	Best	Good	[n/r]	Best			neither	PVC			2375 by Tygon				
Coffee	Best	Good	[n/r]	Best			neither	PVC			2375 by Tygon				
Cola Det EQ-18	do not use	good	best	do Not Use			neither	2375 by Tyg	PTFE				yes	sds	
COLDSTRIP 900				Best	Recommended		neither	PTFE					yes	SDS	Feb-10
Coliche Liqueurs	Good	Best	[n/r]	Caution			neither	PTFE							
Compro XL-S 46	Do not use	Do not use	Do not use	Best			neither	Gas Grade Hose					yes	SDS + Test	
Concrobium Broad Spectrum Disinfectant 11				Best			neither	2375 by Tygon							Aug-19-20
CONDUITE 90	Do Not Use	Best	[n/r]	Do Not Use			neither	PTFE							
CONFRONT	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE							
Conn./Hazelnut flavoring	Do Not Use	Good	Best	Best			neither	2375 by Tyg	PTFE				yes	test	
Conosol C-200 (Calumet)	Do not use	Do not use	Do not use	Best			neither	PTFE					yes	according to mfg	
Conquest (ECOLAB)	do not use	good	good	do Not Use			neither	2375 by Tyg	PTFE				yes	sds	

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Specia	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
CONTEMPO STAT	best	Good	Good	best			neither	2375 by Tygon	PTFE				yes	sds + test	
Conventional Automotive Antifreeze/Coolant (Crystal Clean)				Best			neither	Tygon 2375	PTFE				yes	sds	8/5/2024
COOL POWER	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
COOLANOL	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
Coolant 32	fair	Do Not Use	Do Not Use	Best			neither	Tygon 2375	PTFE				yes	sds	
Coolant Conditioner 122			Best				neither	2375 by Tygon	PTFE				yes	sds	
Copper Acetate	Good	Best	[n/r]	Best			neither	2375 by Tygon	PTFE						
Copper Chloride	Best	Best	Good	Best			neither	2375 by Tygon	PTFE						
Copper Cyanide	Best	Good	[n/r]	Best			neither	2375 by Tygon	PTFE						
Copper Nap-All 8% (BORCHERS)				Best			Flammable	PTFE	Viton				yes	SDS & Mfg recommended	
Copper Nitrate Solution 18%	Do Not Use	Do Not Use	Do Not Use	Best			neither	Tygon 2375	PTFE				yes	sds	
Copper Salts	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Copper Sulfate 5% Solution	Best	Good	Good	Best			neither	2375 by Tygon	PTFE						
Cor Jewelry Cleaner	Caution	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE				yes	test	
Corn Oil	Best	Good	[n/r]	Best			neither	PVC	2375 by Tygon						
Coron 28-0-0 T&O (CODE 70) (Helena)		Best					neither	2375 by Tygon					yes	sds	June-July 202
CORRECT 100 EC	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
Cottonseed Oil	Best	Good	Good	Best			neither	PVC	2375 by Tygon						
CP 310		Best					neither	Tygon 2375	PTFE						Sept 14-19
CP PERSAN						Best	flammable	PTFE					yes	SDS	
Creasil ID CG	do not use	do not use	do not use	Best			Flammable	PTFE					yes	sds	
Creosote, Coal Tar	Best	Do Not Use	[n/r]	Best			neither	PTFE							
Cresol	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE							
Cresylic Acid	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE			Test				
Crosslinker CX-100	Do Not Use	Best	Do Not Use	Do Not Use			neither	PTFE					yes	sds + mfg letter	
Crude Oil	Good	Do Not Use	[n/r]	Best			neither	Gas Grade H	PTFE						
CSPW1 Buffer	Best	Good	Good	Best			Flammable	PTFE					yes	SDS + Test	
CS-R	Best	Good	Good	Best			neither	PVC	2375 by Tygon				yes	test	
CU Stabilizer (Polynt Composites)	Best						Flammable	PTFE					yes	SDS & Customer Specified	
Cumene (isopropyl benzene)	[n/r]	Do Not Use	[n/r]	Best			Flammable	PTFE							
Cumyl Hydroperoxide / Acetal Acetone Peroxide						Best	Flammable	PTFE					yes	SDS	
Cutek Extreme	Best	Do Not Use	[n/r]	Best			Flammable	PTFE					yes	test	
Cutek Green	Best	[n/r]	[n/r]	Best			Flammable	PTFE					yes	test	
Cutting Oil	Best	[n/r]	[n/r]	Best			neither	PTFE							
CX-590CU (Millicron)	Best	Do Not Use	Do Not Use	Best			neither	PTFE					yes	sds	
Cybersolv	Do Not Use	Do Not Use	Do Not Use	Do Not Use							Needs				
Cyclo Breakthrou Carb Cleaner (NITO)					require	Best	Flammable	PTFE			Teflon-Kalrez pump with		yes	SDS	
Cyclohexane	Good	Do Not Use	Do Not Use	Best			Flammable	PTFE							
Cyclohexanol	Caution	Good	[n/r]	Best			Flammable	PTFE							
Cyclohexanone	Do Not Use	Good	Caution	Do Not Use			Flammable	PTFE			Celcon Tap recommended				9/13/2015
Cyclomethicone	[n/r]	[n/r]	Good	[n/r]			Flammable	PTFE					yes	sds	
Cyclopentanone	Do Not Use	Do Not Use	Do Not Use	Do Not Use			Flammable	PTFE			No compatible pumps, f		yes	mfg	
D101	[n/r]	Best	[n/r]	[n/r]			neither	PTFE							
D105	[n/r]	Best	[n/r]	[n/r]			neither	PTFE							
D108	[n/r]	Best	[n/r]	[n/r]			neither	PTFE							
D111	[n/r]	Best	[n/r]	[n/r]			neither	PTFE							
D120	Best	[n/r]	[n/r]	[n/r]			neither	PTFE							
D140	Best	[n/r]	[n/r]	[n/r]			neither	PTFE							
D155	[n/r]	Best	[n/r]	[n/r]			neither	PTFE							
D160	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
DA-7645		Best					neither	Tygon 2375	PTFE						Sept 14-19
Dapro® DF 975	Best	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	sds	
Dart 371-RP	n/r	best	n/r	n/r			neither	2375 by Tygon	PTFE				yes	sds	
DAUBERT CHEMICAL NOX-RUST 241AA	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE							
Dawn Ultra	Best	Caution	Caution	Best			neither	2375 by Tygon	PTFE				yes	test	
DDDS Pine	Do Not Use	Good	Do Not Use	Best			neither	Tygon 2375	PTFE				yes	sds	
Decalin (Deklin)	Do Not Use	Do Not Use	[n/r]	Best			Combustible	PTFE							

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Decane	Do Not Use	Do Not Use	[n/r]	Best			Combustible	Viton	PTFE						
Decanoic Acid (CAPRIC ACID)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE				yes	sds	entered May
Decyl Glucoside (PLANTACARE 2000UP)	[n/r]	good	n/r	Best			neither				Too thick for GT at room		yes	sds+ test	
DEF	[n/r]	Best	Best	[n/r]			neither	2375 by Tyg	PTFE						
De-icing Fluid	Good	Best	Best	Good			Flammable	2375 by Tyg	PTFE						
deionized water			Best				neither	Tygon2375	PTFE						
Delo ELC PG Antifreeze Coolant- Concentrate		Best		Good			neither	2375 by Tyg	PTFE				yes	SDS and Mfg recommended	3/10/2015
DELO XLC Antifreeze / Coolant- Premixed 50/50		Best	Best				neither	Tygon2375	PTFE				yes	SDS	
Demeton-S-Methyl	[n/r]	[n/r]	[n/r]	Best			flammable	PTFE							
Denatured Alcohol 3C	fair	good	best	good			Flammable	2375 by Tyg	PTFE						
Denatured Ethanol (SDA 3C, 200 PROOF)	do not use	fair	best	do not use			Flammable	2375 by Tyg	PTFE				yes	SDS + Test	
Denco Non-Chlorinated Brake Cleaner						Best	Flammable	PTFE					yes	SDS	
Dermol 99	do not use	do not use	do not use	Best			neither	2375 by Tyg	PTFE				yes	SDS + Test	
Desmodurh				Best			neither	PTFE					yes	SDS and Test	
Destroyer 115	Do Not Use	Best	Best	Do Not Use			neither	2375 by Tyg	PTFE						
DESTROYER Series (JJ Chem)	Caution	Do Not Use	Do Not Use	Best			combustible	2375 by Tyg	PTFE				yes	sds	
DESTROYER SX SERIES	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
DETER	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
Detergents	Good	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
Developing Fluids (photo)	Best	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
Dextron	Best	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
DGP HIGH PERFORMANCE HAND SANITIZER			Best				flammable	2375 by Tygon					yes	sds	Aug-19-20
D-Greeze 500-LO	n/r	n/r	n/r	best			neither	Viton	PTFE				yes	sds	
Diacetone	Best	Good	[n/r]	Do Not Use			Flammable	PTFE			Test				
Diacetone Alcohol	Good	Best	[n/r]	Do Not Use			Flammable	PTFE							
DIAMOND GROW - HUMI (K) Powder in Water	Best						neither	Tygon 2375	PTFE				yes	sds MFG recommended	entered may
DIAZINON 800	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
Dibasic Ester	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE					yes	SDS	
Dibenzyl Ether	Do Not Use	Caution	[n/r]	Caution		Best	Flammable	PTFE			do not leave pump on container - PP a problem for extended use				
Dibenzyl Sebacate	Caution	Caution	[n/r]	Good			neither	PTFE							
Dibromomethyl Benzene	[n/r]	[n/r]	[n/r]	Best			Flammable	PTFE							
Dibutyl Phthalate	Do Not Use	Best	Best	Good			neither	2375 by Tyg	PTFE						
Dibutyl Sebacate	Do Not Use	Good	[n/r]	Caution			neither	PTFE							
DicaSan (DuBois)				Best			neither	2375 by Tygon					yes	SDS	June-July 202
Dichloro Butane	[n/r]	[n/r]	[n/r]	Best			Flammable	PTFE							
Dichloroacetic Acid	Good	Fair	Fair	Good			neither	PTFE							
Dichlorobenzene	Do Not Use	Do Not Use	[n/r]	Good			Flammable	PTFE							
Dichloromethane - also known as Methylene Chloride	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE			Flammable liquid, use a grounded pump for best safety				
Dielectric Tough Gel Kit 3-4207 part A Dow Corning	Best						neither	PTFE			Thickish, need single siphon tube.				
Dielectric Tough Gel Kit 3-4207 part B Dow Corning	Best						neither	PTFE			Thickish, needs single siphon tube				
Diesel Exhaust Fluid (DEF)	[n/r]	Good	Good	Do Not Use			neither	2375 by Tyg	PTFE		Meets PEI ISO standards ; clean tap of grease before use, use approved hosing to meetin				
Diesel Fuel	Good	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE						
Di-ester Synthetic Lubricants	[n/r]	[n/r]	[n/r]	Best			Flammable	Gas Grade H	PTFE						
Diethyl Ether				Best			Flammable	PTFE			Teflon-Kalrez upgrade r	yes		SDS	
DIETHYL ETHER	best	best	do not use	best			Flammable	Flammable	PTFE	Tygon	Testing needed - PP cou	yes		SDS + Test	
Diethyl Sebacate	Do Not Use	Caution	Caution	Good			neither	PTFE			Test/Wash				
Diethylamine	Do Not Use	Best	[n/r]	Do Not Use			neither	2375 by Tyg	PTFE		Wash			nothing... came with the business in 2000	
Diethylene Glycol	Best	Good	[n/r]	Best			neither	2375 by Tyg	PTFE						
Difluordibromomethane	[n/r]	Good	[n/r]	[n/r]			Flammable	PTFE			Wash				
Diisobutyl Carbinol, Technical Grade		Best					neither	PTFE			Teflon-Kalrez upgrade r	yes		SDS and MFG recommended	
Diisobutyl Ketone	Good	Do Not Use	[n/r]	Do Not Use		Best	neither	PTFE							
Diisobutylene	Good	Do Not Use	[n/r]	Best			Flammable	PTFE							
Diisooctyl Sebacate	[n/r]	[n/r]	[n/r]	Good			neither	PTFE			Wash				
Diisopropanolamine	[n/r]	Good	[n/r]	[n/r]			neither	PTFE			Wash				
Diisopropyl Dimer Dilinoleate	do not use	do not use	do not use	Best				Tygon 2375	PTFE				yes	sds	
Diisopropyl Ketone	Do Not Use	Best	[n/r]	Do Not Use			flammable	PTFE							
Diisopropylamine	[n/r]	Best	[n/r]	[n/r]			neither	PTFE							

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
DILUTED PROKLENZ® NPH HIGH PERFORMANCE	Best						neither	2375 by tygon					yes	sds	Aug-19-20
DIMENSION EC	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon							
DIMENSION EW	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon							
Dimethicone	[n/r]	[n/r]	Good	[n/r]			neither	2375 by Tygon	PTFE						
Dimethyl Formamide	Do Not Use	Good	Best	Do Not Use			Combustible	2375 by Tygon	PTFE						
dimethyl ketone, acetone, 2-propanone			best				flammable	2375 by Tygon	PTFE				yes		entered may
Dimethyl Phthalate	Do Not Use	Good	[n/r]	Good			neither	PTFE			Wash				
Dimethylethanolamine	Do Not Use	Good	Best	Do Not Use			flammable	Tygon 2375	PTFE				yes	sds + test	
Dimethylisopropylamine	[n/r]	Best	[n/r]	[n/r]			neither	PTFE							
Diocetyl Phthalate	Good	Best	Good	Best			neither	2375 by Tygon	PTFE		Wash				
Diocetyl Sebacate	Do Not Use	Caution	[n/r]	Caution		Best	neither	PTFE							
Dioxalane	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	flammable	PTFE					yes	sds and MFG recommend	3/10/2015
Dipentene (limonene)	Caution	Caution	[n/r]	Best			Flammable	PTFE							
Diphenyl	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE							
Diphenyl Oxide	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE							
Dipropyl Methane - Heptane	Do Not Use	Do Not Use	Do Not Use	Good	Required		Flammable	PTFE			Celcon tap required	yes	test		
DIPROPYLENE GLYCOL FRAGRANCE	Good	Best	Best	Good			neither	PTFE				yes	MFG		
DIPTEREX 500 SL	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
Dishwasher HD7 VC24	n/r	Best	n/r	n/r				PTFE							
Disinfectant Betco Fight Bac RTU		Best					neither	2375 by Tygon				yes	SDS		June-July 202
DISSOLVE	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Dissolvine D-39	n/r	Best	n/r	n/r			neither	PTFE				yes	sds		
Distilled CBD in Hemp Oil (NEW LEAF)				Best			neither	PTFE				yes	SDS		
Distilled Water	Best	Best	Best	Best			neither	PVC	2375 by Tygon						
DIURON FLOWABLE	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE		May be too thick to work with GT Pumps				
Diverwash HD7 VC24	do not use	Best	Do Not Use	Do not use			neither	2375 by Tygon	PTFE			yes	sds		
Divinylbenzene 63	n-r	n-r	n-r	Best			flammable	PTFE				yes	sds + test		
Divinyltetramethyl-DSO, HP	[n/r]	[n/r]	[n/r]	Best			Flammable	PTFE				yes	sds		
D-Limonene	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE							
DMSO (Dimethyl Sulfoxide)		Good					neither	PTFE				yes	sds + MFG		
DODINE FLOWABLE	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE		May be too thick to work with GT Pumps				
DODINE FLOWABLE	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE			yes	MFG		
Dormex	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE			yes	MFG		
DOT Brake Fluid	Best	Good	Good	Best			neither	Gas Grade H	PTFE						
DOUBLE NICKEL LC				Best			neither	Tygon 2375	PTFE		CHECK VISCOSITY BEFORE	yes	sds MFG recommended	entered may	
Dow Corning (R ) 3-4207 Dielectric Tough Gel kit	Best						neither	PTFE			Thickish, need single siphon tube.				
Dow Corning (R ) 3-4207 Dielectric Tough Gel kit	Best						neither	PTFE			Thickish, needs single siphone tube				
Dow Corning® 360 Medical Fluid, 12,500 CST	do not use	do not use	do not use	do not use							too thick for GT				
Dow Corning 200® Fluid, 1 CST ( Octamethyltrisiloxane)			Best				neither	2375 by Tygon				yes	SDS		June-July 202
Dow Corning 345 Fluid	do not use	do not use	do not use	Good			neither	PTFE				yes	sds		
DOW CORNING High Vacuum Grease	Best	Good	Good	Good			neither	Tygon2375	PTFE		Possibly too thick	yes	SDS		
Dow Corning Silane	Good	Best	Best	Caution			neither	PTFE				yes	test		
Dow Corning® 365, 35% Dimethicone NF Emulsion	Caution	Best	[n/r]	Best			neither	PTFE							
DOW FROST Heat Transfer Fluid		Best	Best				neither	Tygon2375	PTFE			yes	SDS		
Dowanol DPMA Glycol Ether Acetate	good			Best			Combustible	PTFE				yes	SDS and MFG recommended		
Dowanol PM Glycol Ether	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE				yes	MFG		
DowFax™ 2A1 Solution Surfactant	[n/r]	[n/r]	[n/r]	Best			neither	PTFE				yes	sds		
DPG	Best	Good	Good	Best			neither	2375 by Tygon	PTFE						
DRAGNET	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
DREWPLUS L-768 FOAM CONTROL AGENT	Do Not Use	Best	Best	Best			neither	2375 by Tygon	PTFE		may need single siphon tube due to viscosity				
Drexel Damoil™ Dormant & Summer Spray Oil	Best			Best			neither	Gas Grade Hose				yes	sds		
DRI-IT C	Do Not Use	fair	Do Not Use	Best			neither	Tygon 2375	PTFE			yes	sds		
DRILL TERGE	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE			yes	Test		
DRIVE 75DE	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Dry Cleaning Fluids	Caution	Caution	[n/r]	Best			Flammable	PTFE							
DRYSAN DUO	do not use	Good	best	do not use			combustible	PTFE				yes	sds		
DS-9-333	Do Not Use	Do Not Use	Do Not Use	Best			neither				Good at 68 deg F or low	yes	sds		

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
DTE Light oil	Best	[n/r]	[n/r]	[n/r]			neither	Gas Grade H	PTFE						
DTM EPOXY SEALER	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither				Too thick for GT Pumps	yes			June 04 2019
DTM Epoxy Sealer Part A	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither				Too thick for GT Pumps	yes			Sept 14-19
DUBOIS DRI-IT C	Do Not Use	Fair	Fair	Best			neither	2375 by Tyg	PTFE						
Dumasín	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither	PTFE			No compatible pumps, PP may be a problem				
DUPONT 105 LACQUER THINNER	Do Not Use	Best	Do Not Use	Fair			Flammable	PTFE							
DURA DUROCT ZIRCONIUM 24%	[n/r]	[n/r]	[n/r]	[n/r]			neither	PTFE							
DURA DUROCT Zirconium 24% 14024	Best	Do Not Use	Do Not Use	Do Not Use			neither	PTFE							
DYBP-85-WO	[n/r]	[n/r]	[n/r]	Best			Flammable	PTFE				yes			SDS - and factory recommendation
Dyna-Solv 101	Fair	Good	Good	Best			neither	PTFE				yes			test
Dynasolve 180	n/r	Best					neither	PTFE				yes			MFG
Dynasolve CU-9	Do Not Use	Good	Best	Do Not Use			neither	PTFE				yes			MFG
Dynasylan 9165	[n/r]	[n/r]	[n/r]	Best			Flammable	PTFE				yes			MFG
Dynasylan HMDS	[n/r]	Best	[n/r]	[n/r]			Flammable	PTFE				yes			sds
EA810	Do Not Use	Good	Good	Do Not Use			neither	PTFE				yes			test
EA854	Best	Do Not Use	Do Not Use	best			neither	PTFE				yes			mfg
Earth Force Clear Choice	n/r	best	n/r	n/r			neither	2375 by Tyg	PTFE			yes			sds
Earth Force Ultra Brite	n/r	n/r	n/r	best			neither	2375 by Tyg	PTFE			yes			sds
Earthworks Cal-Vantage		Best	Best				neither	2375 by Tyg	PTFE			yes			sds
EASISOLV 120	Do Not Use	Best	Best	Do Not Use			Combustible	PTFE							
EasiSolv 140 Solvent Cleaner	n/r	Best	n/r	Do not use		BEST	neither	PTFE				yes			MFG
EASISOLV 701	Do Not Use	Best	Best	Do Not Use			neither	PTFE			May need to change tap o-rings from time to time				
Eastman DMAA 80%				Best			neither	PTFE	Viton			yes			SDS & Mfg recommended
Eastman DMAA 95%				Best			neither	PTFE	Viton			yes			SDS & Mfg recommended
Eastman DOA PLASTICIZER	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither	PTFE			Stainless Steel and FEP	yes			sds
Eastman EastaPure TM Ethyl Acetate	Do Not Use	Good	Do Not Use	Do Not Use			combustible	PTFE			Build with all Tef/Kal pa	yes			SDS
Eastman EB Acetate	Do Not Use	Best	Good	Do Not Use			neither	PTFE							
EASTMAN TM PROPIONIC ANHYDRIDE				Best			flammable	PTFE TEFLON				yes			sds
Eastman™ Glacial Acetic Acid	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	Flammable	PVC Hose			hastelloy springs/ teflon coated screws				Aug-19-20
E-BRITE 200 RXW	Best						Neither	Tygon2375				yes			Feb-17
E-BRITE 200-M	Best						neither	Tygon2375				yes			Aug-19-20
ECO DRAW HVE 1 RP	[n/r]	[n/r]	Best	[n/r]			neither	2375 by Tygon				yes			sds
ECO GREEN	[n/r]	[n/r]	[n/r]	Best			neither	PTFE				yes			sds
ECOLAB FOAM FORCE	Do Not Use	Best	Best	Do Not Use			neither	PTFE							
Ecolo Clean 650	Do Not Use	Do Not Use	Do Not Use	Best			combustible	PTFE				yes			sds
EDTA Na4, 39% Tech Liq			Best				neither	Tygon2375	PTFE			yes			SDS
Egg Nog Flavoring	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE			yes			test
EKFA PX4701 (BASF)				Best			neither	Tygon2375	PTFE			yes			SDS & MFG Recommended
Element™ 4 Herbicide	Do Not Use	Do Not Use	Do Not Use	Best			neither	Tygon 2375	PTFE			yes			sds
ELETTA-WT	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE				yes			sds
Elevance Clean™ 1000FM	Do Not Use	Do Not Use	Do Not Use	Do Not Use							PP a problem	yes			sds + MFG recommend
Emersol 221	Do Not Use	Do Not Use	Do Not Use	Best			neither	PVC	2375 by Tygon			yes			sds
EMPOWER Fragrance Free			Best				neither	Tygon2375	PTFE			yes			SDS
Encor 379G	Good	Best	Best	Good			neither	2375 by Tyg	PTFE			yes			test
ENDICARE EPT-305 (CoastSouthwest)				Best			neither	PTFE				yes			sds
ENDOSULFAN	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
ENDOSULFAN ULV	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
Enforce (Cleaner)		Best					neither	2375 by Tyg	PTFE			yes			MFG
Enforce LP	[n/r]	best	[n/r]	[n/r]			neither	2375 by Tyg	PTFE			yes			SDS
Engen Dynamic 95 Unleaded Petrol(ULP)	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE				yes			SDS
Engine Oil	Best	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE						
Enova EF-583CM	n/r	Good	Good	n/r			neither	2375 by Tygon				Yes			SDS
Enplate EN-623A	Good	Good	Best	Good			neither	2375 by Tygon				yes			SDS
Enplate EN-623C	n/r	Good	best	n/r			neither	2375 by Tygon				yes			SDS
EnSolv Next		Best	Best				neither	2375 by Tygon			Teflon Kalrez fluid path	yes			SDS
EnSolv® A Precision Cleaning Solvent	do not use	Good	Best	Good			Flammable	2375 by Tyg	PTFE						
EnSolve 5408		Do Not Use		Best			neither	PTFE				yes			MFG

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Environ LpH se Phenolic Disinfectant	n/r	Best	n/r	n/r			combustible	PTFE					yes	sds	
ENVIRONALL	Caution	Caution	[n/r]	Best			neither	PTFE							
Enviro-San (EcoLab)						Best	flammable	PTFE					yes	SDS	June-July 202
ENVIRO-SCRUB LM	Good	best	Good	best			neither	PTFE					Yes	SDS + Test	
ENVOY	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE							
EPICHLOROHYDRIN	fair	best	Good	best			flammable	PTFE						SDS + Test	
Epoxy Resins	[n/r]	Best	[n/r]	[n/r]			neither	PTFE			May be too thick for GT Pumps				
EPS 4000 Electropolish				Best			neither	Tygon2375	PTFE				yes	SDS	
Equipment Sanitizer (Ecolab)	do not use	Do Not Use	Do Not Use	Best			Flammable	2375 by Tygon	PTFE				yes	sds	
ESI-CRYL 11	Best	[n/r]	[n/r]	[n/r]			neither	PTFE							
Ethane	Best	Do Not Use	[n/r]	Best			flammable	PTFE							
Ethanol	Fair	Good	Best	Best			Flammable	2375 by Tygon	PTFE				yes	sds + test	
Ethanol 95%	Fair	Good	Best	Best			Flammable	2375 by Tygon	PTFE				yes	sds + test	
Ethanol 100%	Fair	Good	Best	Best			Flammable	2375 by Tygon	PTFE		Tef-Kal Tap upgrade str		yes	sds + test	27-Nov-24
Ethanol A2-200 (Superior)			Best				Flammable	2375 by Tygon	PTFE				yes	sds	
Ethanolamine	Fair	Fair	Best	Do Not Use			Flammable	2375 by Tygon	PTFE		Test				
ETHOXYLATED ALCOHOL - Meyer Labs	Do Not Use	Best	Best	Do Not Use			neither	PTFE					yes	SDS	
ETHREL	Good	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE		Wash				
Ethyl Acetate	do not use	Good	Good	Do Not Use			flammable	PTFE			Build with all teflon/kal		yes-customer review		
Ethyl Acetoacetate	Do Not Use	Good	[n/r]	Do Not Use			neither	PTFE			Wash				
Ethyl Acrylate	Do Not Use	Good	[n/r]	Do Not Use			flammable	PTFE			Wash				
Ethyl Alcohol	fair	good	Best	fair			Flammable	2375 by Tygon	PTFE				yes	test	
Ethyl Benzene	Caution	Do Not Use	Do Not Use	Best			Flammable	PTFE			Test				
Ethyl Benzoate	Caution	Caution	[n/r]	Best			neither	PTFE							
Ethyl Bromide	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
Ethyl Cellosolve	Fair	Good	Good	Do Not Use			Combustible	PTFE							
Ethyl Chloride	Best	Good	Fair	Best			neither	PTFE							
Ethyl Chlorocarbonate	[n/r]	Do Not Use	[n/r]	Best			flammable	PTFE							
Ethyl Chloroformate	Do Not Use	Good	Good	Do Not Use			flammable	PTFE			Test/Wash				
Ethyl Cyclopentane	Best	[n/r]	[n/r]	Good			flammable	PTFE							
Ethyl Ether	Do Not Use	Do Not Use	Do Not Use	BEST			flammable	PTFE			Polypropylene a problem		yes-		Sept 14-19
Ethyl Formate	Do Not Use	Caution	Fair	Best			flammable	PTFE							
Ethyl Lactate 100%	Do Not Use	Best	Best	Do Not Use			Combustible	PTFE			Remote tap should use Tygon 2075 tubing				
Ethyl Oxalate	Do Not Use	Best	Good	Do Not Use			Combustible	PTFE							
Ethyl Pentochlorobenzene	Caution	Caution	[n/r]	Best			Flammable	PTFE			Test				
Ethyl Silicate	Good	Best	[n/r]	Best			flammable	PTFE							
Ethylacrylic Acid	[n/r]	Good	[n/r]	[n/r]			neither	PTFE			Wash				
Ethylene Chloride	Good	Do Not Use	Do Not Use	Good			flammable	PTFE			Wash				
Ethylene Chlorohydrin	Do Not Use	Best	Good	Do Not Use			flammable	2375 by Tygon	PTFE						
Ethylene Diamine	Good	Best	Good	Do Not Use			flammable	PTFE					yes	sds	
Ethylene Dibromide	[n/r]	Fair	[n/r]	Best			neither	PTFE			Test				
Ethylene Dichloride	Do Not Use	Do Not Use	Do Not Use	Best			flammable	2375 by Tygon	PTFE						
Ethylene Glycol	Best	Best	Good	Good			neither	2375 by Tygon							
Ethylene Glycol - Propyl Ether	Good	Best	Good	Best			neither	2375 by Tygon	PTFE						
ETHYLENE GLYCOL MONOBUTYL ETHER - Meyer	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE					yes	SDS	
Ethylene Oxide, Liquid	Do Not Use	Best	Good	Best			neither	2375 by Tygon							
Ethylhexyl Stearate (CETIOL 868)	do not use	do not use	do not use	Best			neither	viton	PTFE				Yes	SDS + Test	
Ethylmorpholine Stannous Octotate	[n/r]	Best	[n/r]	[n/r]			neither	PTFE							
Evac-571	n/r	n/r	n/r	best			Flammable	2375 by Tygon					Yes	SDS	
Evac-571T	do not use	do not use	do not use	best			neither	2375 by Tygon					Yes	SDS	
Evergreen Crop Protection	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE				yes	sds	
Everite II (30 - 60% HCL)	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither						yes	sds	
EVERPRO LIQUID (JJ Chem)	Caution	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
EVOLUTION 1 - Meyer Labs	Do Not Use	Best	Best	Do Not Use			neither	PTFE					yes	SDS	
EXCEL CLEANER DEGREASER				Best			neither	PTFE					yes	sds	Aug-19-20
Extended Life Premium (OAT) Glabal Antifreeze/Coolant (Crystal Clean)				Best			neither	Tygon 2375	PTFE				yes	sds	8/5/2024
Extreme Simple Green Aircraft & Precision Cleaner			Best				neither	Tygon2375	PTFE				yes	SDS	

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
EXXPRIINT 274A (Flash Oil) by FLINT GROUP	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	sds	
E-Z BRITE				Best			neither	PTFE			Must have Teflon coating		yes	SDS and Test	
Fascat @ 2003 Catalyst				Best			neither	2375 by Tygon					yes	sds	Feb-17
Fascat @ 4202 Catalyst				Best			neither	2375 by Tygon	PTFE				yes	mfg	
Fascat 4102 Catalyst (PMC)				Best			neither	PTFE	Viton				yes	SDS & Mfg recommended	
Fast & Easy		Best					neither	2375 by Tygon	PTFE				yes	sds + Mfg	
Fatty Acids	Good	Do Not Use	Do Not Use	Best			neither	PVC	2375 by Tygon						
FD by Biosafe Systems	n/r	n/r	n/r	n/r		BEST	Flammable	PTFE					Yes	Test	
FD&C Blue #1 (PYLAM)			Best				neither	Tygon2375	PTFE				yes	SDS & Test	
FD&C RED No# 40 (ROHA)			Best				neither	Tygon2375	PTFE				yes	SDS & MFG Recommended	
Fenamiphos	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Ferric Chloride	Best	Good	Good	Best			neither	PVC	2375 by Tygon				yes	mfg	
Ferric Nitrate	Best	Good	[n/r]	Best			neither	PVC	2375 by Tygon				yes	mfg	
Ferric Nitrate Solution 10.5% Fe (1718)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 By Tygon	PTFE				yes	sds	
Ferric Sulfate 50%				Best			neither	Tygon2375	PTFE				yes	SDS	
Ferromec Ac 15-0-0	Best	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Fiber ProTector PRO Textile Protector			Best				Flammable	Tygon 2375	PTFE				yes	sds	4/21/2024
Fibre Zone	n/r	best	n/r	n/r			neither	2375 by Tygon	PTFE				Yes	SDS	
FIRMENICH INC ORANGE ESS FRAC 1141-EB ARR	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	2375 by Tygon	PTFE						
FIRMENICH LIMONENE 1 X DIST FAB 955430	Do Not Use		Do Not Use	Best			Flammable	2375 by Tygon	PTFE						
Fleet Charge Heavy Duty Collant-Antifreeze	Do Not Use	Best	Good	Do Not Use			neither	2375 By Tygon	PTFE				yes	sds	
Flexigraphic Inks (Water Based)	n/r	best	n/r	n/r			neither	2375 by Tygon	PTFE				Yes	email	
FLEXMOR (Chemtronics)		Fair	Fair	Fair			neither	Tygon 2375	PTFE				yes		June 04 2019
Flexstar GT3.5	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE				yes	mfg	
Florasurf NPE MOL9, Tech Liq			Best				neither	PTFE					yes	SDS	
FLUOBORIC ACID 48%, ELECTROPURE											testing needed				Aug-19-20
FLUOMETURON FLOWABLE	Best	[n/r]	[n/r]	[n/r]			neither	Gas Grade H	PTFE		May be too thick to used with GT Pumps				
Fluorinert (NOVEC™)	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE					yes	mfg	
Fluorolube	Fair	Best	[n/r]	Good			neither	PTFE							
Fluosolv TEN-X				Best			neither	PTFE					yes	SDS	3/10/2015
FLUOSOLV AP	Good	Do Not Use	Good	BEST			neither	Tygon 2375	PTFE				yes	sds+TEST	Sept 14-19
FluoSolve NPX (Non-PFAS) (NuGenTec)		good	Best				neither	PTFE			EPDM Vapor Degrease		yes	SDS and Test AND Tech	11/11/2024
Flux 263UR	fair	best	best	fair			flammable	2375 by Tygon	PTFE				Yes	SDS + Test	
Flux-Off Tri-V				Best			neither	PTFE			Teflon-Kalrez fluid path		yes	SDS	
Foam 140		Best					neither	Tygon 2375	PTFE						Sept 14-19
Foam 240				Best			neither	Tygon 2375	PTFE						Sept 14-19
Foam Chlor 535 (BIR-009 Birko)		Good	Good				neither	2375 by Tygon					yes	SDS	June-July 202
Foam Force (Ecolab)	Do Not Use	Best	Good	Do Not Use			neither	2375 By Tygon	PTFE				yes	sds	
Foam Nox	[n/r]	Best	[n/r]	[n/r]			neither	PTFE					yes	sds	
Foamaster® MO 2133 (BASF)				Best			neither	2375 by Tygon					yes	sds	June-July 202
Foaming Caustic Cleaner FP	Do not use	Best	Do not use	Do not use			neither	2375 by Tygon					yes	sds	
Foam-Shine	Do not use	Do not use	Do not use	best			neither	2375 by Tygon	PTFE				yes	sds	
FoamStream Alkylpolyglycoside	do not use	do not use	do not use	best			neither	2375 by Tygon	PTFE				Yes	SDS	
FOLICUR 250 EC	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
FOLICUR 250 EW	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
FOLICUR 430 SC	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
FOLIDOL M500	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
FOLIMAT 800	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
Formaldehyde - 40%				Best			neither	PTFE							
Formalin	Caution	Good	[n/r]	Best			neither	PTFE			This is also known as 40% formaldehyde in water				
Formic Acid 95%	do not use	do not use	do not use	Best			flammable	PTFE					Yes	SDS	
Formula 1020	Fair	Good	Good	Best			neither	2375 by Tygon	PTFE				yes	SDS + Test	
Formula 1151	Do not use	Fair	Fair	Best			neither	2375 by Tygon	PTFE				yes	SDS + Test	
Formula 1200	Best	good	good	Best			neither	2375 by Tygon	PTFE				yes	SDS + Test	
FORMULA 517	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
FORMULA 520	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
FORMULA 537	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						



Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
FORMULA 538	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
FORMULA 540	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
FORMULA 560	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
FORMULA 570	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
FORMULA 575	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Formula 815 GD	Do not use	Do not use	Do not use	Best			neither	PTFE				yes	sds		
Foster 40-80 (H.B Fuller)		Best					neither	2375 by Tygon				yes	SDS		June-July 202
FOSTROL FUNGICIDE				Best			neither	Tygon 2375	PTFE						entered may
Fountain Solution 201 by Saphira	Good	Good	Good	Best			neither					yes	test		
Fractionated Oil	Good	Best	Do Not Use	Good			neither					yes	test		
FRACTURE FUNGICIDE				Best			neither	Tygon 2375	PTFE					sds MFG recommended	entered may
FRAGRANCE SPRAY AND WASHDOWN (Walex)				Best			neither	Tygon 2375				yes	sds		Aug-19-20
Frekote Aqualine R-110	Good	Best	Best	Good			neither	2375 by Tygon	PTFE			yes	MFG		
Frekote FMS GA CN	Best			Do not use			neither	PTFE				yes	MFG		
Fremont 419 Paintstripper	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE							
French Color Blue Dye, D878	Do Not Use	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
French Color Red Dye D 858	Caution	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
FRESH MIST				Best			neither	2375 by Tygon				yes	sds		Aug-19-20
FRESHWATER XT (JJ Chem)	Do Not Use	Best	Good	Do Not Use			neither	2375 by Tygon	PTFE						
FS FORMULA 10184	Good	Best	Best	[n/r]			neither	2375 by Tygon	PTFE						
FS FORMULA 4089	Do Not Use	Good	Good	Do Not Use			neither	2375 by Tygon	PTFE					Monthly O-Ring Change required	
FS Process Cleaner X-4490 55GL	[n/r]	best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE			yes	factory recommended		
FT19	n/r	n/r	n/r	Best			neither	Gas Grade Hose				yes	sds		
FUCHS LUBRICATION RENOLIN WL 68 NE	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
FUEL DOCTOR	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Fuel Oil	Best	Do Not Use	[n/r]	Best			neither	Gas Grade H	PTFE						
Fumaric Acid	Fair	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Furfural	Do Not Use	Good	Best	Fair			neither	2375 by Tygon	PTFE			yes	mfg		
Furfuraldehyde (same as furfural)	[n/r]	Best	[n/r]	[n/r]			Combustible	PTFE							
Furfuryl Alcohol			Best				flammable	2375 by Tygon				No	No SDS		June-July 202
Furyl Carbinol	[n/r]	Best	[n/r]	[n/r]			Combustible	PTFE							
FVC ORG APL Cider VNGR 50GR 55GL K (Kerry)			Best				neither	Tygon 2375	PTFE			yes	sds		8/16/2024
FW UV / AQUA Cleaner	Do Not Use	Best	[n/r]	Do Not Use			neither	2375 by Tygon	PTFE						
FWY-ISP LIQUID INJECTABLE SOIL PENETRANT	Do Not Use	Best	[n/r]	Do Not Use			neither	2375 by Tygon	PTFE						
G Force Degreaser	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE							
G1500 Thinner by Glyptal Inc	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE				yes	sds		
Gallic Acid	Best	Fair	[n/r]	Best			neither	2375 by Tygon	PTFE						
GARDABOND (Phosphoric Acid)						BEST	neither	PTFE				yes	sds+mfg recommends		Sept 14-19
Gardoclean S 5219 ( BASF)				Best			neither	2375 by Tygon				yes	SDS		June-July 202
Gardolene D 6800/6 (BASF)				Best			neither	2375 by Tygon				yes	SDS + test		June-July 202
GARLON	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Gasoline Leaded	Good	Caution	Do Not Use	Best			flammable	Gas Grade H	PTFE						
GB Foam (BEAVER RESEARCH)		Best	Best				neither	Tygon2375	PTFE			yes	SDS		
GC 6-B	[n/r]	[n/r]	[n/r]	Best			neither	PTFE				yes	sds		
GE WATER OPTISPERSE PQ4262	Do Not Use	Best	Best	Do Not Use			neither	2375 by Tygon	PTFE						
GEAR-LUBE 150 FG (GARDENER DENVER)				Best			neither	Tygon2375	PTFE			yes	SDS		
Gelatin	Best	Good	[n/r]	Best			neither	PVC	PTFE						
Geniosil GF 56	Do Not Use	Do not use	best	Do Not Use			flammable	Tygon 2375	PTFE			yes	mfg		
GENOSIL GF 31			best				neither	Tygon 2375	PTFE			yes	sds+mfg recommends		Sept 14-19
Gettysolve - C Heptane	Do Not Use	Do Not Use	Do Not Use	Good	Required		Flammable	PTFE							
Glacial Acetic Acid	Do Not Use	good	Good	Good			neither	PTFE							Get the teflon and kalrez upgrade in the fluid path
GLACIAL CLEAN-5.6% peroxyacetic acid	do not use	do not use	do not use	Best			flammable	PTFE				Yes	SDS		
Glass AW 32,46,68 Hydraulic Fluids (Hubert)	Best			Best			neither	Gas Grade Hose				yes	sds		5/9/2024
Glass Klenz		Best					neither	Tygon 2375	PTFE						Sept 14-19
Glaubers Salt	Do Not Use	good	n/r	Best			neither	2375 by Tygon	PTFE						
Glucose	Best	Good	Good	Best			neither	2375 by Tygon	PTFE						
Glutaraldehyde 50% Solution	Do Not Use	Best	Do Not Use	Do Not Use			neither	2375 by Tygon	PTFE			yes	mfg		

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Glycerine	Best	Best	Good	Good			neither	PVC	2375 by Tygon		Vegetable glycerin at 70 degrees F will flow slowly, however if warmed to 85, it will provide				
Glycerol	Best	Best	Good	Good			neither	PVC	2375 by Tygon		Vegetable glycerin at 70 degrees F will flow slowly, however if warmed to 85, it will provide				
Glycic Alcohol (Glycerol; Glycerine)	Best	Best	Good	Good			neither	PVC	2375 by Tygon		Vegetable glycerin at 70 degrees F will flow slowly, however if warmed to 85, it will provide				
Glycol Ether DE Acetate				Best			Flammable	PTFE				yes	MFG		
Glycol Ether EB (Butyl Cellosolve)	Do Not Use	Best	Good	Do Not Use			combustible	PTFE				yes	sds		
Glycolic Acid LS				Best			neither	Tygon2375	PTFE			yes	SDS		
Glycols	Good	Best	Best	Good			neither	PVC	PTFE						
GLYFOS AQUATIC	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
GLYFOS X-TRA	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
GLYPHOS	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
GLYPHOS PRO	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Glyphosate	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
GLYPTAL G 1500 THINNER	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE							
GOAL 2XL	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
GOLDEN BEAR 1111	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE						
GOOF OFF	Do Not Use	Do Not Use	Do Not Use	Good			Flammable	PTFE				yes	test		
Gourmet Gardens® 1-6-6 (Gourmet Gardens)	Best						neither	2375 by Tygon				yes	SDS		June-July 202
Gourmet Gardens® 7-0-5 (Gourmet Gardens)	Best						neither	2375 by Tygon				yes	SDS		June-July 202
GP Solvent Blend	Do Not Use	Good	best	Do Not Use			Flammable	PTFE				yes	test		
GRAMOXONE	Do Not Use	Good	Do Not Use	Best			neither	2375 by Tygon	PTFE		Requires Closed System in US				
Grape Seed Oil	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE			yes	sds		
Green Clean Liquid Algaecide	Do Not Use	Caution	Caution	Best			neither	2375 by Tygon	PTFE						
GREEN SENSE FRAGRANCE	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Green Shield disinfectant and Algicide - Prescript	Do not use	Do not use	Do not use	Best			2375 by Tygon	PTFE				yes	sds		
Green Sulfate Liquor	Good	Best	[n/r]	Best			neither	2375 by Tygon	PTFE						
GREENCLEAN ACID CLEANER				Best			neither	2375 by Tygon				yes	sds		Aug-19-20
GREENCLEAN Alkaline Cleaner				Best			neither	2375 by Tygon							Aug-19-20
GREENSHIELD	[n/r]	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE			yes	MFG		
GREENSHIELD CA	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Green-Shield II Disinfectant		Good	Best				Flammable	Tygon2375	PTFE			yes	SDS		
GROTAN	Do Not Use	Caution	Caution	Best			neither	2375 by Tygon	PTFE			yes	sds		
Gun Wash TX-6172 (Dupont Canada)	do Not Use	do Not Use	Do Not Use	Do Not Use		BEST	flammable	PTFE				Yes	SDS		
GUSATHION 200 SC	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
GUSATHION A LIQUID	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
GX 2630				Best			neither	Viton	PTFE						
GX Clean 5502	Do Not Use	Best	Do Not Use	Do Not Use			neither	PTFE				yes	sds		
GX-AA (Sakata Inx Corp)	Good	Best	Do Not Use	Do Not Use			neither	2375 by Tygon	PTFE			yes	sds		entered May
H Klenz II		Best					neither	Tygon 2375	PTFE						Sept 14-19
H-550 (Nalco) (Glutar Aldehyde)			Best				neither	2375 by Tygon				yes	SDS		June-July 202
Halothane	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
Halowax Oil	Caution	Caution	[n/r]	Best			neither	Viton	PTFE						
Hammer Oil ISO 320	Good	Fair	Do Not Use	best			neither	Gas Grade H	PTFE			yes	SDS and Test		
Hand Soap (1189) (Satellite)			Best				neither	2375 by Tygon				yes	SDS		June-July 202
Haps Fee Lacquer Thinner	Best	Best	do not use	Fair			Flammable	PTFE		FEP	Get the teflon and kalre	yes	test		
Harima Binder	Do Not Use	Good	good	Do Not Use			neither	PTFE			Too thick for GT Pumps	yes	test		
Hazelnut Flavoring	Do Not Use	good	Best	Best			neither	2375 by Tygon	PTFE			yes	test		
HEATBATH DS-9-333	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither	PTFE							
HEATBATH EVERITE II (Hydrochloric Acid 30-60%)	Do Not Use	Do Not Use	Do Not Use	Do Not use			neither	2375 by Tygon	PTFE						
Heavy Duty Acid LC-30 by Ecolab				Best			neither	2375 by Tygon	PTFE			yes	SDS and Mfg recommenda	3/10/2015	
Heavy Duty Flux Remover - Supr Clean, Bull				Best			neither	PTFE				yes	SDS		
Heavy Water	Best	Best	[n/r]	good			neither	2375 by Tygon	PTFE						
HELOTHION EC	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Heptane (N-Heptane) (Dipropyl Methane)	Do Not Use	Do Not Use	Do Not Use	Good	Required		Flammable	PTFE			Must have Celcon tap, r	yes	test		
Heptane (Whitaker)	Do Not Use	Do Not Use	Do Not Use	Good	Required		Flammable	PTFE			Must have Celcon tap, r	yes	test		
Heptyl Hydride - Heptane	Do Not Use	Do Not Use	Do Not Use	Good	Required		Flammable	PTFE			Must have Celcon tap				
Hexamethyldisilaxane	[n/r]	Best	[n/r]	[n/r]		Good	Flammable	PTFE				yes	SDS and Test		
Hexamethyldisiloxane	Good	Best	Do Not Use	Good			flammable	2375 by Tygon	PTFE			yes	sds and test		entered May

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Hexane				Best			FLAMMABLE	PTFE			Must have Tef-kal upgrade in Tap				updated 11-2
Hexanes				Best			flammable	PTFE				yes	SDS		
Hexyl Alcohol	Best	Good	[n/r]	Best			Flammable	2375 by Tygon	PTFE						
HFE 73 DE (NOVEC™)				Good		Best	neither	PTFE			Required Teflon Kalrez	no	Recommendation From	June-July 202	
HFE Fluids Azeotropes [3M/Novac]	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
HFE Novac 1230		Best		Best			neither	PTFE			Consider the System for Vapor Degreasers - <a href="https://www.goatthroat.com/product/vapor-degreaser">https://www.goatthroat.com/product/vapor-degreaser</a>				
HFE Novac 649		Best		Best			neither	PTFE			Consider the System for Vapor Degreasers - <a href="https://www.goatthroat.com/product/vapor-degreaser">https://www.goatthroat.com/product/vapor-degreaser</a>				
HFE-71DA (NOVEC™)				Good			neither	PTFE			Required Teflon Kalrez	no	Recommendation From	June-July 202	
HFE-71DE (NOVEC™)	[n/r]	[n/r]	[n/r]	Best			neither	PTFE			Consider the System for Vapor Degreasers - <a href="http://goatthroat.com/goatthroat-vsp-6800">http://goatthroat.com/goatthroat-vsp-6800</a>				
HFE-71PA (NOVEC™)	[n/r]	[n/r]	[n/r]	Best			neither	PTFE			Required Teflon Kalrez Fluid path upgrade				
HFE-72DA	[n/r]	[n/r]	[n/r]	Best			neither	PTFE			Required Teflon Kalrez Fluid path upgrade				
HFE-72DE	[n/r]	[n/r]	[n/r]	Best			neither	PTFE			Required Teflon Kalrez Fluid path upgrade				9/13/2015
HG-V/D909 Thinner (SUN CHEMICAL)						Best	flammable	PTFE				yes	SDS		
High Performance Alkaline FP (3126 Spartan Chemical Company)		Best					neither	2375 by Tygon				yes	SDS		June-July 202
Histo-Clear	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE				yes	sds		
Histo-Clear HS-200	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
HOME RUN (JJ Chem)	Do Not Use	Best	Good	Do Not Use			neither	2375 by Tygon	PTFE						
HONCHO	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
HOTRICALURAL OIL	Best	Do Not Use	[n/r]	Do Not Use			neither	Gas Grade H	PTFE						
HQ Inhibitor Solution (Polynt Composites)				Best			Combustible	PTFE	Viton			yes	SDS & Customer Specified		
Humates	Best	Good	Good	Best			neither	2375 by Tygon	PTFE			yes	test		
HumiSeal Thinner 521 (HumiSeal)				Best			flammable	PTFE				yes	SDS		June-July 202
Husquavarna HiperGuard	n/r	n/r	n/r	Best			neither	2375 by Tygon	PTFE		May be too thick for GT	Yes	SDS		
HV 490 Emulsion, Silicone Emulsion	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
HYBRID WASH 625			Best				flammable	2375 by Tygon				yes	sds		Aug-19-20
Hydraulic Fluid	Best	Good	Good	Do Not Use			neither	Gas Grade H	PTFE						
Hydraulic Oils (Petroleum)	Best	Do Not Use	[n/r]	Best			neither	Gas Grade H	PTFE			yes	MFG		
Hydraulic Oils (Synthetic)	Good	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE						
Hydrazine	Fair	Best	Best	good			neither	PTFE			PP plastic may be a problem; looking for customer to test				
Hydro 204 (Hydrochem) (Silphamic Acid)	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Do Not	neither				NO PUMP IS SUITABLE	Yes	SDS		June-July 202
Hydrobromic Acid up to 50%	Do Not Use	Best	Good	Best			neither	Gas Grade H	PTFE						
Hydrochloric Acid (5%)	Do Not Use	Do Not Use	Do Not Use	Good			neither	2375 by Tygon	PTFE		Requires Teflon screws, Hatelloys springs and teflon-kalrez fluid path upgrade				
Hydrochloric Acid (6% +)	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither	2375 by Tygon	PTFE		No GT Pump will work				
Hydrochloric Acid 4 - 6% in Methanol (26219)	Do Not Use	Best	n/r	Best			Flammable	2375 by Tygon				Yes	Test		
Hydrochloric Acid 7% (Brenntag)				Best		Best	neither	Tygon 2375	PTFE		REQUIRED: tef/kal fluid	yes	sds and test		5/9/2024
Hydrochloric Acid 30 - 37%				Best with very specific conditi			neither	Tygon 2375	PTFE		REQUIRED: MAXIMUM Temperature: 68Deg F; tef/kal fluid path upgrade				11/12/2024
Hydrocyanic Acid	Good	Best	Good	Best			neither	2375 by Tygon	PTFE						
Hydrofluoric Acid	do not use	do not use	do not use	do not use							No GT Pump will work				
Hydrofluosilicic Acid (20%)	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE			Specialty Pump: Use Stainless 316 and Hasteloy Springs with Teflon Coated screws				
Hydrogen Peroxide 35%	Do Not Use	Fair	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Hydrogen Peroxide 90%	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Hydrogen Sulfide (Wet) (Cold)	Good	Best	Best	Fair			neither	PVC	2375 by Tygon						
Hydrogen Sulfide (Wet) (Hot)	Caution	Best	[n/r]	Fair			neither	PVC	2375 by Tygon						
Hydroquinone (MEHQ)	Fair	Best	Best	Fair			neither	2375 by Tygon	PTFE		Wash between uses				
Hydroxyethyl Methacrylate	Good	Good	Good	Best			neither	PTFE				yes	test		
Hypochlorous Acid 10%	Caution	Good	[n/r]	Good			neither	PVC	Gas Grade Hose						
Hypophosphorous Acid 50%	Best	Good	Good	Best			neither	2375 by Tygon	PTFE			yes	test		
Hyspin Aws 46 (CASTROL)				Best			neither	PTFE				yes	SDS		
HYVAR	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
I.D. Red (ZEP)	[n/r]	[n/r]	[n/r]	Best		Required	flammable	PTFE			Celcon Tap required	yes	mfg		
IC Clean 2600 Premium Wash			Best				Flammable	PTFE				yes	SDS		
IC Clean 3600 UV Wash			Best				Combustible	Tygon2375	PTFE			yes	SDS		
ICC 8266- Ink Degradent				Best			neither	2375 by Tygon	PTFE			yes	sds MFG recommended	entered may	
ICC 930- Ink Degradent				Best			neither	2375 by Tygon	PTFE			yes	sds MFG recommended	entered may	
Igepal CO 630 (Solve)				Best			neither	PTFE				yes	SDS		
IM7417 CAT-L-INK Thinner	Do Not Use	Good	Best	Do Not Use			Flammable	PTFE				yes	SDS + Test		
Immunol Regular	Do not use	Fair	Fair	Best			neither	2375 by Tygon	PTFE			Yes	SDS		
Impact 256	n/r	best	n/r	n/r			neither	2375 by Tygon	PTFE			Yes	SDS		

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
IND Recycling Non-Chlor Brake Clnr	Do Not Use	Do Not Use	Do Not Use	Do Not Use	Required	Best	Flammable	PTFE			Celcon Tap required		yes	sds + mfg	
Infantry 4L	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE				yes	mfg	
INGERSOL EXTEND FOOD GRADE, FG-46	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE							
Inhibitor A	Do Not Use	Best	Best	Do Not Use			Flammable	PTFE					yes	mfg + test	
Inhibitor Solution (STYPOL) (Polynt Composites)		Good	Best				Combustible	PTFE					yes	SDS & Customer Specified	
Inhibitor Solution in DBE (STYPOL) (Polynt Composites)				Best			neither	PTFE	Viton				yes	SDS & Customer Specified	
INSPIRE SUPER (FUNGICIDE)				Best			neither	2375 by Tygon					yes	sds	
INT-EQ6 (AXEL)				Best			neither	PTFE					yes	SDS & MFG Recommended	
INTERSOL 24 , 190 PROOF (Interstate)	Do Not Use	Fair	Best	Do Not Use			Flammable	PTFE					yes	sds	
INTRICUT 217	Good	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Iodine (in Alcohol)	Good	Caution	[n/r]	Best			Flammable	2375 by Tygon	PTFE						
Ionox 13419	Do not use	Fair	Best	Do not use			neither	2375 by Tygon	PTFE				yes	sds + test	
IONOX I3302	Do Not Use	Best	Good	Do Not Use			neither	PTFE					yes	test	
IPA up to 99%	Do Not Use	Good	Best	Fair			Flammable	2375 by Tygon	PTFE		Flammable Liquid, use with SCP		yes	sds + test	
Irganox 1135	Do Not Use	Good	Best	Best			neither	2375 by Tygon	PTFE				yes	sds + test	
IRON MAX 6% 15-0-0	Best	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Iselux LQ CLR SB	Good	Good	Best	Best			neither	2375 by Tygon					yes	sds + test	
ISO 198/3 Isocyanate Component (BASF)	[n/r]	[n/r]	[n/r]	Best			neither	PTFE					yes	sds	
Isobutyl Alcohol	Good	Best	[n/r]	Best			Flammable	2375 by Tygon	PTFE						
Isobutyl-n-Butyrate	[n/r]	Best	[n/r]	Good			Flammable	PTFE							
Isocyanate (LaPolla)				Best			neither	PTFE					yes	sds	
Isodecyl Pelargonate CAS 109-32-0	[n/r]	[n/r]	[n/r]	Best			neither	PTFE					yes	sds + test	
Isododecane	Best	[n/r]	[n/r]	Best			Flammable	PTFE							
Isooctane	Best	Do Not Use	Do Not Use	Best			Flammable	Gas Grade H	PTFE						
Isopar G Fluid (Naptha) ( Fisher Scientific)				Best			flammable	PTFE					yes	SDS	June-July 202
Isopar H Fluid	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE					yes	mfg	
Isopar L				Best			neither	PTFE					yes	sds	5/1/2024
Isopar M Fluid	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE					yes	sds + test	
Isopropanol /IPA/ Isopropyl Alcohol, up to 99%	Do Not Use	Good	Best	Fair			Flammable	2375 by Tygon	PTFE		Flammable Liquid, use with SCP Pump				
Isopropanol Refined (Kodak)	Do Not Use	Good	Best	Fair			Flammable	2375 by Tygon	PTFE		Flammable Liquid, use with SCP Pump				
Isopropyl Acetate	Do Not Use	Good	Good	Do Not Use			Flammable	PTFE			Wash				
Isopropyl Chloride	Good	Do Not Use	[n/r]	Best			Flammable	PTFE							
Isopropyl Ether	Best	Caution	Caution	Caution			Flammable	PTFE			Polypropylene a possible problem, remove from container after use.				
Isopropylamine (Ispropyl Amine)	[n/r]	Good	[n/r]	[n/r]			Flammable	PTFE			Wash between uses				
Isothiozol	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE							
J Spray (JJ Chem)	Do Not Use	Best	Good	Do Not Use			neither	2375 by Tygon	PTFE				yes	sds	
Jayflex DNP	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE					yes	sds	
Jeechem CTG	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE		According to Chemical N		yes	SDS + test	
Jeechem OP	Best	n/r	n/r	n/r			neither	2375 by Tygon	PTFE		According to Chemical N		yes	sds MFG recommended	
Jeffamine ® T 403	[n/r]	[n/r]	[n/r]	Best			neither	PTFE					yes	Test	
Jet Fuel	[n/r]	[n/r]	[n/r]	Best			Flammable	PTFE					yes	Test	
Jet-AG® 5% Peracetic Acid (AKA Paraclean 5-E)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE		70 mm Adapter- 462-B		yes	sds MFG recommended	entered may 3
JMS STYLET OIL	Best			Best			neither	gas grade hd	PTFE				yes	sds MFG recommended	entered may 3
Johnsen's Non-Chlorinated Brake Parts Cleaner	Do Not Use	Do Not Use	Do Not Use	Do Not Use	Recom	BEST	Flammable	PTFE			Celcon Tap Recommend		yes	mfg	
JOHNSEN'S Non-Chlorinated Brake Parts Cleaner 14 Oz						Best	flammable	PTFE					yes	SDS	
JOKISH LB-100 (Intercon)	Do Not Use	Best	Best	Do Not Use			neither	2375 by Tygon	PTFE				yes	sds	
J-SPRAY	[n/r]	Best	[n/r]	Best			neither	PTFE							
KALIGREEN	Best	Best	[n/r]	Best			neither	2375 by Tygon	PTFE						
Kalwal Blend #2	Do not use	Good	Good	Do not use			Flammable	2375 by Tygon	PTFE						
Kapow (L-569)	n/r	n/r	n/r	best			neither	2375 by Tygon	PTFE				yes	SDS	
Kathon CG/ICP Preservative	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE		must have teflon coated		yes	sds + mfg	
Kathon™ LX 1.5% Biocide (DOW)				Best			neither	2375 by Tygon					yes	SDS	June-July 202
KELTHANE	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Kent Fast Drying Non-Chlorinated Brakes Clean				Best			Flammable	PTFE			Teflon-Kalrez Tap upgr		yes	SDS	
Kerosene - see notes	Good	Do Not Use	Do Not Use	Best	Required		combustible	Gas Grade H	PTFE		celcon tap required				
Ketocyclopentane	Do Not Use	Do Not Use	Do Not Use	Do Not Use							No compatible pumps, PP may be a problem				
Ketopentamethylene	Do Not Use	Do Not Use	Do Not Use	Do Not Use							No compatible pumps, PP may be a problem				
Keynote	Do Not Use	Best	Do Not Use	Do Not Use			neither	PTFE					yes	sds	

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
KFO 402 Polyglycol Food Grade General Purpose	Do Not Use	Do Not Use	Do Not Use	Best			neither	PVC	PTFE		May be too thick for GT		yes	mfg	
KFO 7070 Food Grade General Purpose Process	Good			Best			neither	Tygon 2375	PTFE				yes	sds + mfg recommendation	
KIDDE ANTIFREEZE SOLUTION		Best					neither	Tygon 2375	PTFE				yes	sds	June 04 2019
KILVAL	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Klean Strip Paint Thinner	n/r	n/r	n/r	Best			flammable	gas grad hos	PTFE				Yes	SDS	
Kleen Rite 799NB Phosphoric Acid				Best			neither	2375 by Tygon					yes	SDS	June-July 202
Kleengrow	[n/r]	[n/r]	[n/r]	Best			flammable	2375 by Tygon	PTFE				yes	sds	
Kleer View Glass Concentrate- L-50	n/r	good	best	n/r			flammable	2375 by Tygon	PTFE				yes	SDS	
KLUBERSYNTH UH1 14-151	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
KOCIDE	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
KONTROL 2%	Do Not Use	Caution	Do Not Use	Best			neither	2375 by Tygon	PTFE						
KONTROL 30%	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
KONTROL 4%	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Kordek 50C	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Kordex MLX	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE				yes	mfg	
KOVAR BRIGHT DIP						BEST	neither	PTFE					YES	TESTED	Sept 14-19
Kwik Dri 66	[n/r]	[n/r]	[n/r]	Best			combustible	Gas Grade H	PTFE						
L-44 ECD	Do not use	Good	Best	Good			neither	2375 by Tygon	PTFE				yes	SDS + Test	
LA12294-PAX XL6 85%	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE				yes	sds	
Lab Klenz 100		Best					neither	Tygon 2375	PTFE				yes	mfg	Sept 14-19
Lab Klenz 110		Best					neither	Tygon 2375	PTFE				yes	mfg	Sept 14-19
Lab Klenz 120		Best					neither	Tygon 2375	PTFE				yes	mfg	Sept 14-19
Lab Klenz 200				Best			neither	Tygon 2375	PTFE				yes	mfg	Sept 14-19
Lab Klenz 250		Best					neither	Tygon 2375	PTFE				yes	mfg	Sept 14-19
Lacquer thinner											Please send SDS for advise - there are dozens of different ones				
Lacquer thinner	Best	Do Not Use	Do Not Use	Do Not Use	Recommended		Flammable	PTFE			Celcon tap recommend	yes	test		
Lacquer Thinner - Mansfield Paint Company	Best	Do Not Use	Do Not Use	Do Not Use	Recommended		Flammable	PTFE			Celcon tap recommend	yes	sds + test		
Lacquer Thinner (FINISHMASTER, INC)						Best	flammable	PTFE					yes	SDS	
Lacquer Thinner (Rexall)						Best	Flammable	PTFE					yes	SDS	
Lacquer Thinner -Sheboygan Paint	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	Flammable	PTFE					yes	test	
LACQUER THINNER/SW (Sherwin Williams)	Do Not Use	Do Not Use	Do Not Use	Do Not Use		BEST	flammable	PTFE					yes	TEST	entered may
Lactams- Amino Acids	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
Lactic Acid Cold	Good	Best	Best	Best			neither	PVC	2375 by Tygon						
Lactones	[n/r]	Good	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
LANAWET D-70 PG				BEST			neither	Tygon 2375	PTFE				yes	SDS	Sept 14-19
Lancer 5% (HERITAGE SYSTEMS) (Periacetic Acid)				Best			flammable	Tygon2375	PTFE				yes	SDS	
Lancer 5% (Peroxiacetic Acid)	[n/r]	[n/r]	[n/r]	Best			Flammable	2375 by Tygon	PTFE				yes	sds	
LaPolla Isocyanate	[n/r]	[n/r]	[n/r]	Best			neither	PTFE					yes	sds - See Isocyanate	
Lard	Best	Good	[n/r]	Best			neither	PVC	2375 by Tygon		May be too thick unless heated to 130 Deg F.				
Laromer TMPTA	Do Not Use	Best	Best	Do Not Use			neither	PTFE					yes	test	
LARVIN 375	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
LARVIN LV	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
LASER™ FE REPLENISHER				best			neither	2375 by Tygon					yes	sds	Aug-19-20
Latex Paint	Best	Best	Best	Best			neither	2375 by Tygon	PTFE		Thick liquid - use single	yes	test		
Lavender Oil	Good	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
LDC-02 Activator & Etch	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE		Teflon screws and haste	yes	sds		
LE - MAT	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
Lead Acetate	Good	Best	Best	Do Not Use			neither	PVC	2375 by Tygon						
Lead Nitrate	Good	Best	[n/r]	Best			neither	PVC	2375 by Tygon						
Lead Sulfamate	Good	Best	[n/r]	Best			neither	2375 by Tygon	PTFE						
Leaf It Green Bathroom Cleaner	n/r	n/r	best	n/r			neither	2375 by Tygon	PTFE				yes	sds	
LEAFEX	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
LEBAYCID	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
LEGUMEX	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
LENIUM ES	Do Not Use	Best	Best	Fair			flammable	PTFE			Teflon/ kalrez fluid Path	yes	test		
Lenium FHD		Best					neither	PTFE			Teflon-Kalrez fluid path	yes	SDS and Test		
Lesco Momentum FX(2) Herbicide (Lesco inc.)				Best			neither	2375 by Tygon					yes	SDS	June-July 202

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Lesco Spreader Sticker	Do Not Use	Fair	Do Not Use	Best			neither	2375 by Tygon	PTFE		May be too thick		yes	test	
LESCO THREE-WAY SELECTIVE HERBACIDE	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE		May be too thick		yes	sds	
Lesco Wet Plus	Fair	Do Not Use	Do Not Use	Fair			neither	2375 by Tygon	PTFE		May be too thick		yes	test	
Lexar EZ	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE				yes	label	
LFCF EN A Component	[n/r]	[n/r]	[n/r]	Best			neither	PVC	2375 by Tygon		Consider a silicon Free P		yes	MFG	
LFCF EN Replenisher	[n/r]	[n/r]	[n/r]	Best			neither	PVC	2375 by Tygon		Consider a silicon Free P		yes	sds	
LFI Sanitizer (WestAgro)				Best			neither	2375 by Tygon			Chem Station		yes	SDS	June-July 202
Lift RT	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE					yes	sds	
Light Grease	Best	[n/r]	[n/r]	[n/r]			neither	Gas Grade H	PTFE						
Lime Bleach	Best	Best	[n/r]	Best			neither	PVC	2375 by Tygon						
Lime Sulpur	Do Not Use	Best	[n/r]	Best			neither	2375 by Tygon	PVC						
Limonene 1 X Dist Fab (955430)	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE					yes	sds	
Linoleic Acid	Good	Do Not Use	[n/r]	Best			neither	PTFE	Gas Grade Hose						
Linseed Oil	Good	Fair	Fair	Best			neither	Gas Grade H	PTFE						
LIQUICHLOR 10-16% (SODIUM HYPOCHLORITE)				Best			neither	2375 by Tygon							Aug-19-20
Liquid 90	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE				yes	mfg	
Liquid Descaler				Best			neither	Tygon 2375	PTFE						Sept 14-19
Lloyd's Stainless Steel Flux, 03-00	Do Not Use	Do Not Use	Do Not Use	Best			Combustible	PTFE			Please use Teflon-Kalrez upgrade in the fluid path for best results				
Loctite CAT (23 LV)	Do Not Use	good	Best	Best			neither	PTFE					yes	test	
Loctite CAT (24 LV)	Do Not Use	Good	Good	Best			neither	PTFE					yes	test	
Loctite CAT (9)	Fair	Good	Best	Best			neither	PTFE					yes	test	
Loctite Frekote 55NC				Best			flammable	PTFE					yes	sds and MFG recommend	3/10/2015
LONTREL	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Lord 7650 Adhesive		Best					FLAMMABLE	PTFE			TEFLON KALREZ TAP UP		yes	TESTED BY CUSTOMER	Sept 14-19
LORD CORP CHEMLOK 218 ADHESIVE	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither	PTFE			A coating liquid that will adhere to the inside of the pump-				
Louis Econo Lacquer Thinner C189	Good	Best	[n/r]	[n/r]	Recommended		flammable	PTFE			Celcon tap recommend		yes	test	
Low VOC Brake and Metal Cleaner (1 Ayd Corporation)					yes	Best	Flammable	PTFE					yes	sds	11/11/2024
Low VOC SuperClean	Caution	Fair	Good	Best			neither	2375 by Tygon	Gas Grade Hose				yes	test	
LPS 2	[n/r]	[n/r]	[n/r]	Best			flammable	PTFE					yes	sds	
LPS HDX    Heavy-Duty Degreaser	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE					yes	sds	
LPS Instant Super Degreaser 2.0 (ITW PRO BRANDS)				Best			neither	PTFE			Teflon-Kalrez fluid path		yes	SDS	
LPS LABS T-91 DEGREASER	Good	Best	Best	Good			neither	2375 by Tygon	PTFE				yes	sds	
LU™ 103L RUST BREAKER Penetrant (Sprayon)				Best			flammable	PTFE					yes	sds	Aug-19-20
LU™ 700L FOOD GRADE MACHINERY OIL				Best			neither	PTFE					yes	sds	Aug-19-20
LU™ 708 HIGH PERFORMANCE DRY LUBRICANT (Sprayon)				Best			flammable	PTFE					yes	sds	Aug-19-20
LU™ 711L THE PROTECTOR™ ALL PURPOSE LUBRICANT				Best			flammable	PTFE					YES	SDS	Aug-19-20
LU™ 777L OUTDOOR METAL PROTECTANT (Sprayon)				Best			flammable	PTFE					yes	sds	Aug-19-20
Lubeze Omni	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	sds	
Lubricating Oils (Petroleum)	Best	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE						
Lubriplate HO-0, HO-1, HO-2 & HO-2A Hydraulic	n/r	n/r	n/r	Best			neither	Gas Grade H	PTFE				yes	product data sheet	
Lubriplate PGO-FGL Synthetic Gear Oils ISO Visco	n/r	n/r	n/r	Best			neither	Gas Grade H	PTFE		Too thick for GT at room		yes	product data sheet	
Lubriplate Syn Lube 46	n/r	n/r	n/r	Best			neither						yes	sds	
LUBRIPLATE SYNLUBE KLUB 22, 32, 46, 68, 100	Good	[n/r]	[n/r]	Best			neither	Gas Grade H	PTFE				yes	sds	
Luddox HS-30 Colloidal Silica	Good	Best	Best	Good			neither	2375 by Tygon	PTFE				yes	sds and MFG recommend	3/10/2015
LUNA EXPERIENCE				Best			neither	Tygon 2375	PTFE		may be too thick for GT		yes	sds MFG recommended	entered may
LUNA EXPERIENCE	n/r	n/r	n/r				neither	Gas Grade H	PTFE		Too thick for GT at room		yes	product data sheet	
LU™ 103L Rust Breaker® Penetrant (Sprayon Products Group)							neither						SDS		3/15/2017
LU™ 512 Food Grade - High Temperature Synthetic Grease (Sprayon Products Group)				Best			neither	PTFE					SDS		3/15/2017
LU™ 700L Food Grade Machinery Oil (Sprayon Products Group)				Best			flammable	PTFE			CELCON TAP		SDS		3/15/2017
LU™ 708 High Performance Dry Lubricant (Sprayon Products Group)				Best			flammable	PTFE					SDS		3/15/2017
LU™ 711L The Proctor™ All-Purpose Lubricant (Sprayon Products Group)				Best			flammable	Gas	PTFE				SDS		3/15/2017
LU™ 777L Outdoor Metal Protectant (Sprayon P	Fair	Best	best	Good			neither	2375 by Tygon	PTFE						
Lye (KOH)	Fair	Best	best	Good			neither	2375 by Tygon	PTFE						
Lyme Go Green (BEAVER RESEARCH)				Best			neither	Tygon2375	PTFE				yes	SDS	
Lyme Gone Red Delymer (BEAVER RESEARCH)				Best			neither	Tygon2375	PTFE		Must have Teflon coat		yes	SDS	
Mackkanate EL P	n/r	n/r	Best	Best			neither	2375 by Tygon	PTFE				yes	sds + test	
Macro-Sorb	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
MADISAN 75		Best					neither	2375 by Tygon					yes	sds	Aug-19-20

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Magnesium Chloride	Best	Best	Best	Best			neither	PVC	2375 by Tygon						
Magnesium Hydroxide	Good	Best	Good	Best			neither	PVC	2375 by Tygon						
Magnesium Nitrate Solution 50% Mg - Shepard	do Not Use	Do Not Use	do not use	Best			neither	viton	PTFE				yes	sds	
Magnesium Nitrate Solution 6.3% Mg - Shepard	do Not Use	Do Not Use	do not use	Best			neither	viton	PTFE				yes	sds	
Magnesium Salts	Good	Best	Good	Best			neither	PVC	2375 by Tygon						
Magnesium Sulfate	Good	Best	best	Good			neither	PVC	2375 by Tygon						
Magnesium Sulphite	Good	[n/r]	[n/r]	[n/r]			neither	PVC	2375 by Tygon						
Maguard 5626 (Mason)				Best			Flammable	Tygon2375	PTFE				yes	SDS	
MAGUARD® 5626				Best			neither	2375 by Tygon					yes	sds	Aug-19-20
MALATHION	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
MALDISON 500	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Maleic Acid	Good	Do Not Use	Fair	Best			neither	PVC	2375 by Tygon						
Maleic Anhydride	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Malic Acid	Good	Fair	[n/r]	Best			neither	PVC	2375 by Tygon						
MANAGE	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Mandate Plus (ECO LAB)	[n/r]	[n/r]	[n/r]	[n/r]		Best	neither	PTFE			Teflon-Kalrez Pump		yes	sds	
Manganese Nitrate Solution 50%	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
Manganese Sulfate	Best	Good	Good	Best			neither	PVC	2375 by Tygon		Flush tap between uses				
Manzate Pro-Stick				Best			neither	Tygon 2375	PTFE				yes	sds MFG recommended	entered may
Marathon Petroleum Gasoline - All Grades	[n/r]	[n/r]	[n/r]	Best			flammable	PTFE							
MARLIN	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
MASTELINE TRIPLET	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Master STAGES CLEAN F2	Fair	n/r	n/r	Good			neither	PTFE					yes	sds	
Master Stages RPO 12	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE					yes	sds	entered May
Master STAGES RPO 2L	n/r	n/r	n/r	Best			neither	PTFE					yes	sds	
MAX FORCE FAST FILL	Do Not Use	Best	Good	Do Not Use			neither	2375 by Tygon					yes	sds	
Maxi Guard 700 Lance and Soak	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon					yes	sds	
Maxim Facility + (Midlab)		Good		Best			neither	2375 by Tygon					yes	SDS	June-July 202
MaxSol 230, MaxSol 250, MaxSol 280	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon					yes	sds	
MC-1	[n/r]	Best	[n/r]	[n/r]			neither	PTFE					yes	sds	
MCPA	Best	Good	[n/r]	Best			neither	2375 by Tygon	PTFE						
MCPA 375 SALT	Best	Good	[n/r]	Best			neither	2375 by Tygon	PTFE						
MCPA LVE 500	Best	Good	[n/r]	Best			neither	2375 by Tygon	PTFE						
MCPPE	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
McShine HF	n/r	n/r	n/r	Best			neither	2375 by Tygon	PTFE				yes	sds	
MCT OIL				Best			neither	Tygon 2375	PTFE				yes	sds	11/11/2024
Mean Green	[n/r]	good	best	[n/r]			neither	2375 by Tygon	PTFE				yes	sds	
Mechanical Lubricant - Harry Miller Corp	do Not Use	Do Not Use	Do Not Use	Best			Flammable	Viton	PTFE				yes	sds + test	
MECOMECE 2.5	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
MECOMECE 4	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Megaflow AW Hydraulic Oil (PHILLIPS 66)				Best			neither	Gas	PTFE				yes	SDS	
Megaposit-24A Developer (30670 Shipley)	do not use	do not use	Do Not Use	BEST			flammable	PTFE							
MEHQ - GMAA 250 ppm	do not use	do not use	Do Not Use	BEST			flammable	PTFE							
MEK			Best				Flammable	PTFE			Use with SCP200S groundable		yes	sds	
Mercuric Chloride (Dilute Solu)	Best	Good	Good	Best			neither	2375 by Tygon	PTFE						
Mercurous Nitrate 10%	Do Not Use		fair	Best			neither	2375 by Tygon	PTFE				yes	test	
Mergal CM1.5		n/r	n/r	best			neither	2375 by Tygon	PTFE				yes	sds + Mfg	
Mesityl Oxide	Do Not Use	Good	[n/r]	Do Not Use			neither	2375 by Tygon	PTFE						
METAL RESCUE RUST REMOVER BATH	Fair	Good	Best	Fair			neither	2375 by Tygon	PTFE				yes	test	
Metal Rescue Rust Remover Bath (BLASTER)			Best				neither	Tygon2375	PTFE				yes	SDS	
METALERJ #256	Do Not Use	Fair	Good	Best			neither	2375 by Tygon	PTFE				yes	test	
Metalnox M6321			Best				neither	Tygon2375	PTFE				yes	SDS	
Metalnox M644C		Best	Best				neither	PTFE					yes	SDS & MFG Recommended	
METALNOX M6900	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE					yes	sds	
Met-Drill 740	n/r	n/r	n/r	Best			neither	Viton	PTFE				yes	sds	
Metering Roller Wash	Best	Best	Caution	Do Not Use			neither	2375 by Tygon	PTFE				yes	test	
Methalated Spirits	[n/r]	Best	[n/r]	[n/r]			Flammable	PTFE							
Methane	Best	Fair	[n/r]	Best			Flammable	PTFE							

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Methane Sulfonic Acid 70%	[n/r]	[n/r]	[n/r]	Best			neither	PTFE					yes	SDS + Test	
Methanol	Do Not Use	Good	Best	Good			flammable	2375 by Tygon	PTFE						
Methyl Methacrylate - Stabilized by Lucite; 2-propionic acid-2-methyl; MMM; N			Good			best	Flammable	PTFE			Must have Teflon Kalrez		yes	sds	entered may
Methyl Acetate	Do Not Use	Good	[n/r]	Do Not Use			flammable	PTFE							
Methyl Acrylate	Do Not Use	Good	Good	Do Not Use			neither	PTFE							
Methyl Alcohol	Do Not Use	Good	Best	Caution			flammable	2375 by Tygon	PTFE						
Methyl Amine	Fair	Good	[n/r]	Best			flammable	PTFE							
Methyl Bromide	Fair	Do Not Use	Do Not Use	Best			neither	PTFE							
Methyl Butyl Ketone	Do Not Use	Good	Best	Do Not Use			Flammable	2375 by Tygon	PTFE						
Methyl Cellosolve	Do Not Use	Good	Best	Fair			Combustible	PTFE							
Methyl Cellulose	Do Not Use	Good	[n/r]	Do Not Use			Combustible	PVC	2375 by Tygon						
Methyl Chloride	Good	Fair	Do Not Use	Best				PTFE				yes	test		
Methyl Chloroformate	[n/r]	[n/r]	[n/r]	Best			Flammable	PTFE							
Methyl Cyanide (acetonitrile)	[n/r]	Best	[n/r]	[n/r]				PTFE				yes	letter		
Methyl Dichloride	Do Not Use	Do Not Use	[n/r]	Good			Flammable	PTFE							
Methyl Ether	Good	Do Not Use	[n/r]	Do Not Use			flammable	PTFE			Polypropylene a possible problem, remove from container after use.				
Methyl Ethyl Ketone (MEK)	Do Not Use		Best	Do Not Use			flammable	PTFE			Use with SCP200S groundable	yes	sds		
METHYL ETHYL KETONE MEK (Jasco)			Best				flammable	PTFE				yes	sds		Aug-19-20
Methyl Isopropyl Ketone	Do Not Use	Do Not Use	[n/r]	Do Not Use		Best	flammable	PTFE							
Methyl Mercaptan (Methanethiol)	[n/r]	Best	[n/r]	[n/r]			flammable	PTFE							
Methyl methacrylate (Lucite)	Caution	Good	Good	Do Not Use		BEST	Flammable	PTFE				yes	SDS + Test		
Methyl Methacrylate (Sigma Aldrich)	Caution	Good	Good	Do Not Use		BEST	Flammable	PTFE				yes	SDS + Test		
Methyl Methacrylate Monomer	n/r	best	n/r	n/r			Flammable	PTFE				yes	SDS		
Methyl Methacrylate Monomer Inhibited (ESSCH)	n/r	best	n/r	n/r			Flammable	PTFE				yes	SDS + Test		
Methyl Oleate	Do Not Use	Caution	[n/r]	Best			neither	PTFE							
Methyl Salicylate (betula oil)	Caution	Caution	Best	Good			neither	PTFE							
Methyl Silicate 51			Best				neither	Tygon 2375	PTFE			yes	sds and quote		8/14/2024
Methylacrylic Acid	[n/r]	Good	Best	Fair			neither	2375 by Tygon	PTFE						
Methylcyclopentane	Do Not Use	Do Not Use	[n/r]	Best			flammable	PTFE							
Methylene Chloride also known as Dichloromethane	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE							
Metkote 1178	Good	Do Not Use	Do Not Use	Best			neither	PTFE				yes	SDS		
METTLE 125 ME FUNGICIDE				Best			neither	Tygon 2375	PTFE		CHECK VISCOSITY BEFORE USE	yes	sds + MFG recommended		entered may
Micro Dip 9000	Do not use	Do not use	Do not use	Best			neither	2375 by Tygon	PTFE			yes	SDS		
MicroBlaze	Do Not Use	Do Not Use	Good	Best			neither	2375 by Tygon	PTFE			yes	test		
Micro-chem plus detergent disinfectant cleaner (0255 National)	Good	Good	Best				neither	2375 by Tygon				yes	SDS		June-July 202
Micronox MX2302DT	Do Not Use	Best	Do Not Use	Do Not Use			flammable	PTFE			Use groundable pump	yes	SDS		
Micronox MX2501	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE				yes	SDS		
Mictreat (Tolcide P570A)	Good	Good	best	Best			neither	2375 by Tygon	PTFE			yes	sds + test		
Mighty Mike	n/r	Good	n/r	n/r			neither	2375 by Tygon	PTFE			yes	SDS		
Mikro Quat	Do Not Use	Good	best	Do Not Use			neither	2375 by Tygon	PTFE			yes	sds		
Mild R362	Best	Do Not Use	Do Not Use	Good			neither	Gas Grade H	PTFE			yes	test		
Milestone Herbicide	n/r	n/r	n/r	best			neither	2375 by Tygon	PTFE			yes	SDS		
Mil-G-832820 (Technolube)	Best	Caution	Caution	Do Not Use			neither	Gas Grade h	2375 by Tygon			yes	test		
Milk	Good	Best	Best	best			neither	PVC	2375 by Tygon						
Milk and Honey	Good	Best	Best	best			neither	PVC	2375 by Tygon						
MILLENNIUM ULTRA	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
MIN #Q99R6 (60% Hydrogen) (Nalco)			Best				neither	PTFE				yes	SDS		June-July 202
Mineral Oil	Best	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE						
mineral spirits	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE	Gas Grade Hose						
MINNCARE Cold Sterilant MINNCARE Liquid Sanit	Do not use	Do not use	Do not use	Best			flammable	2375 by Tygon	PTFE			yes	SDS		Aug-19-20
Mirachem Commercial Alkaline Cabinet Wash	Best	n/r	n/r	n/r			neither	2375 by Tygon	PTFE			yes	sds		
Mirachem QX-490 Paint Stripper	Do Not Use	Best	Do Not Use	Do Not Use			neither	PTFE				yes	SDS		
MK-20 (Solvent) (Cleaning Fluid)			Best				Flammable	PTFE			Teflon-Kalrez upgrade r	yes	SDS		
MMA Solvent (Methyl Methacrylate)	Caution	Good	Best	Do Not Use		Best	Flammable	PTFE				yes	SDS + Test		
MMEHQ Inhibitor Solution (Polynt Composites)				Best			Combustible	PTFE	Viton			yes	SDS & Customer Specified		
MMF AGNIQUE	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
MNB 55 (Plastic Process) Non-Chlorinated Bulk Mold Clean						Best	flammable	PTFE				yes	SDS		



Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Mobil 1 5W-30	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	SDS	
Mobil DTE Oil Heavy Medium	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	SDS	
Mobil DTE Oil Light	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	SDS	
Mobil Pegasus 805	fair	do not use	Good	Best			neither	Gas Grade H	PTFE				yes	SDS + Test	
Mobil Vactra Oil No. 2	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	SDS	
Mobile 1 10W-30				Best			neither	Gas	PTFE				yes	SDS	
Mobile Lube HD Plus 80W-9C				Best			neither	Gas	PTFE				yes	SDS	
MoldWiz INT-DLP-22E				Best			neither	PTFE	Viton				yes	SDS & Mfg recommended	
MOMENTUM	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Monobromobenzene	[n/r]	[n/r]	[n/r]	Best			Flammable	PTFE							
Monochlorobenzene	Do Not Use	Do Not Use	[n/r]	Best			Flammable	PTFE							
Monoethanolamine	Fair	Good	Best	Do Not Use			neither	PTFE					yes	sds + customer	
Monoethylene Glycol (ethylene glycol)	Best	Best	Good	Good			neither	PVC	2375 by Tygon				yes	sds	
Monoleox 2059	Good	Do Not Use	Do Not Use	Best			neither	PVC	Gas Grade Hose				yes	test	
Monomethyl Aniline	Do Not Use	Fair	[n/r]	Best			neither	PTFE							
Monovinyl Acetylene	Best	Good	[n/r]	Best			neither	PTFE							
MPK (Methyl Normal Propyl Ketone)	Do Not Use	Do Not Use	Do Not Use	Do Not Use	Best		flammable	PTFE					yes	SDS + Test	
MR-515-H (naphtha)	[n/r]	[n/r]	[n/r]	best			flammable	PTFE					yes	sds	
MTBHQ Inhibitor Solution (Polynt Composites)				Best			Combustible	PTFE	Viton				yes	SDS & Customer Specified	
Multi-Purpose Solvent (PPG) (MS251)						Best	flammable	PTFE					yes	SDS	
Mustang MAX EW Insecticide				Best			neither	Tygon 2375	PTFE				yes	sds MFG recommended	entered may
N Heptane	Do Not Use	Do Not Use	Do Not Use	Best	Required		Flammable	PTFE			Must have Celcon tap		yes	document	
N & A Vanilla 557239 T	fair	Good	best	best			flammable	2375 by Tygon	PTFE				yes	SDS + Test	
N, N-Dimethylacetamide (SIGMA-ALDRICH)				Best			neither	Tygon2375	PTFE				yes	SDS	
N,N-Diethyl Aniline (ACETO)				Best			neither	PTFE	Viton				yes	SDS & Customer Specified	
N,N-Dimethylacetamide				Best			Flammable	PTFE					yes	SDS	
N,N-Dimethylalaniline				Best			Flammable	PTFE					yes	SDS	
N,N-Dimethylformamide	Do Not Use	Good	Best	Do Not Use			flammable	PTFE					yes	sds	
N,N-DIMETHYL-P-TOLUIDINE (ACETO)				Best			neither	PTFE	Viton				yes	SDS & Customer Specified	
NA-104C	Do Not Use	Do Not Use	Do Not Use	Best			flammable	2375 by Tygon	PTFE				yes	sds & mfg	
NAIL PROTEIN (Nailtiques)		Best					Flammable	PTFE			Required teflon fluid pa		yes	sds	Sept 14-19
Nalco 71D5 Plus Antifoam	Good	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE				yes	sds & mfg	
Nalco® 7330				Best			neither	2375 by Tygon					yes	sds & mfg	June-July 202
Naphtha	good	Do Not Use	Do Not Use	Best			Flammable	PTFE	Gas Grade Hose						
Naphthalene	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE	Gas Grade Hose						
Napthenic Acid	Good	Do Not Use	[n/r]	Best			neither	PTFE	Gas Grade Hose						
NAUTIQUE	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
NAXCAT MOD ACID	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE				yes	sds	
Nazdar Thinner	[n/r]	Good	Best	[n/r]			Flammable	PTFE					yes	sds	
N-Beta-gamma-aminopropyltrimethoxysilane	Best	[n/r]	[n/r]	Best			neither	PTFE							
N-Butyl Acetate	[n/r]	Good	Good	[n/r]	Recommended		flammable	PTFE			Looking for someone to test; FEP hose required, PP might be a problem. Celcon Acetal is				
N-BUTYL ALCOHOL			Best				Flammable	2375 by Tygon					yes	sds	Aug-19-20
N-Butyl Benzoate	[n/r]	Good	[n/r]	Best			neither	PTFE							
N-Butyl Butyrate	[n/r]	Good	[n/r]	Best			neither	PTFE							
NC BRAKE CLEAN (WESTMAR)				Best			flammable	PTFE			Teflon-Kalrez fluid path		yes	SDS	
NC110 No Clean Flux	Good	Good	Best	fair			Flammable	PTFE					yes	TEST + SDS	
N-Dodecane 95%				Best			neither	PTFE			Teflon-Kalrez upgrade r		yes	SDS	
n-Dodecyl Mercaptan (CHEVRON PHILLIPS)				Best			neither	PTFE					yes	SDS & MFG Recommended	
Neatsfoot Oil	Best	Caution	[n/r]	Best			neither	Gas Grade H	PTFE						
Nel-Sol	Caution	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE				yes	Test	
NEMACUR 400 EC	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Neon	Best	[n/r]	[n/r]	[n/r]			neither	PTFE							
Neutral Flux 373	[n/r]	Good	Best	[n/r]			Flammable	2375 by Tygon	PTFE				yes	sds	
Neutral Fresh	n/r	best	n/r	n/r			neither	2375 by Tygon	PTFE				yes	sds & mfg	
Neutral Lemon	n/r	best	n/r	n/r			neither	2375 by Tygon	PTFE				yes	sds & mfg	
NEVADA ALL PURPOSE CI/DEGREASER	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
NEVADA BLUE DRESSING	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
NEVADA PINK SOAP	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
NEVADA RED DEGREASER	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
NEVADA YELLOW DEGREASER	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
Neville Acid	Caution	Fair	Best	Best			neither	2375 by Tygon	PTFE						
N-EXT AIR-8 LIQUID AERATION			Good	Best			neither	2375 by Tygon	PTFE			yes	test		Aug-19-20
N-EXT RGS SOIL & PLANT FORMULA			Good	good			neither	2375 by Tygon				yes	test		Aug-19-20
NF372-TB Soldering Flux / NF372-TB Flux Pen	Good	Best	do not use	Best			Flammable					yes	SDS + Test		
Nickel Acetate	Good	Best	[n/r]	Caution			neither	2375 by Tygon	PTFE						
Nickel Bromide 18%	Good	Best	Best	Good			neither	2375 by Tygon	PTFE			yes	sds & tes		
Nickel Chloride	Good	Best	Best	Good			neither	PVC	2375 by Tygon			yes	SDS + Test		
Nickel Nitrate solution, 14% (1726)	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE			yes	sds		
Nickel Sulfate	Best	Best	Best	Best			neither	PVC	2375 by Tygon						
Nicotine	Best	Do Not Use	Do Not Use	Best			neither	PTFE			Toxic or fatal if in contact	yes	SDS + Test		
NITOFOL	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
Nitric Acid 20-50% Solution	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Nitric Acid 41 DEG	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Nitric Acid 5-10% Solution	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Nitric Acid 60-68% Solution	Do Not Use	Do Not Use	Do Not Use	Best			flammable	2375 by Tygon	PTFE					Strongly recommend a Tef-Kal Tap upgrade. At temperatures above 90deg F, Teflon-Kalr	
Nitric Acid 70%+ Solution	Do Not Use	Do Not Use	Do Not Use	Best			flammable	2375 by Tygon	PTFE					Strongly recommend a Tef-Kal Tap upgrade. At temperatures above 90deg F, Teflon-Kalr	
Nitric Acid in Water 3 - 5 %	Good	Best	Best	Best			neither	2375 by Tygon	PTFE			yes	Test + Mfg		
NITRO-30 SNR 30-0-0	Best	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Nitrobenzene	Do Not Use	Good	Best	Best			Flammable	PTFE							
Nitromethane	Do Not Use	Good	good	Do Not Use	Recommended		Flammable	PTFE			Celcon-Acetal tap record	sort of	see cole parmer chart	11/12/2024	
N-Methyl-2-pyrrolidone	Do Not Use	Best	Best	Do Not Use			Flammable	PTFE							
N-Methylpyrrolidone 0-11055169		Best					Flammable	PTFE				yes	sds		
NMP (N-Methyl-2-pyrrolidone)	Do Not Use	Best	Best	Do Not Use			Flammable	PTFE							
N-Octane	Good	Caution	[n/r]	Best			Flammable	Gas Grade H	PTFE						
NOK BLEND (EMTECH Labs)			Best				neither	Teflon Hose				yes	sds		Aug-19-20
No-Mow	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Nonionic Surfactants	Do Not Use	Best	Best	Do Not Use			neither	2375 by Tygon	PTFE						
Nonylphenoxy Poly Ethanol	[n/r]	Best	[n/r]	[n/r]			Flammable	PTFE							
Norbond 2301A	Best	Do Not Use	Do Not Use	Do Not Use			Flammable	PTFE				yes	SDS + Test		
Normal Propyl Alcohol (N-Propyl Alcohol)		Best	Best				flammable	PTFE			Teflon Kalrez fluid Path	yes	sds		
Norox TBPB	n/r	n/r	n/r	Best			Flammable	PTFE				yes	sds		
Novac 1230	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M	June-July 202	
Novac 649	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M	June-July 202	
Novac HFE 71DA	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M		
Novac HFE 71DE	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M		
Novac HFE 72DE	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M	June 04 2019	
Novac HFE 73DE	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M	June 04 2019	
Novac HFE 7600	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M		
Novac HFE 7800	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M		
Novac HFE-7000	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M		
Novac HFE-7100	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M		
Novac HFE-7200	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M		
Novac HFE-72DA	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M		
Novac HFE-7300	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M		
Novac HFE-7500	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			requires Tef Kal fluid path	yes	Recommendation From 3M		
Noxfish Fish Toxicant II (Wellmark)				Best			neither	Tygon2375			closed system required	yes	sds		Feb-17
Nox-rust 241AA	[n/r]	n/r	[n/r]	Best			neither	PTFE			Teflon Kalrez fluid path	yes	sds		
Nox-Rust VCI 1100	[n/r]	n/r	[n/r]	Best			neither	PTFE			Teflon Kalrez fluid path	yes	sds		
N-Pentane		[n/r]	[n/r]	Best			Flammable	PTFE			NOT RECOMMENDED for	yes	sds		
N-Propyl Acetone	[n/r]	Best	[n/r]	[n/r]			Flammable	PTFE			Teflon-Kalrez fluid path upgrade recommended				
n-Propyl Alcohol (propanol)	Do Not Use	Good	Best	fair			Flammable	2375 by Tygon	PTFE		Teflon-Kalrez fluid path	yes	SDS		
n-Propyl Bromide	Do Not Use	Best	Best	Best			Flammable	PTFE			Teflon-Kalrez fluid path	yes	Test		
NR330 VOC Free No Clean	[n/r]	[n/r]	[n/r]	Good			neither	2375 by Tygon	PTFE			yes	sds		
N-SURE (fertilizer)	Best	Good	Good	Best			neither	2375 by Tygon	PTFE			yes	sds		
N-Triethoxysilylpropyl-N,N,N-Trimethylammonium	Do Not Use	Best	Best	Do Not Use			neither	PTFE				yes	sds		

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Oakite Aluminum Cleaner NST	Do Not Use	Best	Do Not Use	Do Not Use			neither	PTFE					yes	sds	
O-Chlorophenol	[n/r]	[n/r]	[n/r]	Best			Combustible	PTFE					yes	sds	
Octachlorotoluene	Caution	Caution	[n/r]	Best			Combustible	PTFE			Test				
Octadecane	Best	Caution	[n/r]	Best			Combustible	PTFE							
Octagon PD 680	Good	Do Not Use	Do Not Use	Best			Combustible	PTFE							
Octyl-Alcohol	Good	Best	Best	[n/r]			Combustible	PTFE							
O-Dichlorobenzene (Methylene Chloride)	Good	Caution	[n/r]	Best			Combustible	PTFE							
Odor-Pro Body Wash	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE		Need Drum Warmer be		yes	sds	
OFTANOL TURF	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Oil Eater (Kafco)	Good	best	Good	Good			neither	2375 by Tygon	PTFE				yes	sds	
Oleic Acid	Do Not Use	Do Not Use	Do Not Use	Best			neither	PVC	2375 by Tygon						
Olive Oil	Best	Good	[n/r]	Best			neither	PVC	2375 by Tygon						
Omacide® IPBC 30 Industrial Fungicide	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE				yes	sds	
OMALA OIL 220	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
OMG AMERICA 12% COBALT HEX-CEM 115086	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Omnilube 300	Best	Do not use	Do not use	Best			neither	2375 by Tygon	PTFE		may be too thick for GT		yes	SDS + Test	
Omnirad 73	Do Not Use	Good	Good	Best			neither	2375 by Tygon	PTFE				yes	SDS + Test	
OMS ( isoparaffinic hydrocarbon)	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE					yes	SDS	
OMS (EXXON MOBILE) (Naphtha)				Best			flammable	PTFE					yes	SDS	
Opteon™ SF79	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	neither	PTFE					yes	SDS	
Opticut	Best	Good	Best	Good			neither	2375 by Tygon	PTFE				yes	test	
Optimum™ Pro Surface Defense (Proguardium)		Best					neither	PVC					yes	SDS	June-July 202
Optisperse ADJ5150		Best					neither	2375 by Tygon	PTFE				yes	sds	
Optisperse PQ 4262		Best					neither	2375 by Tygon	PTFE				yes	sds	
Orange ESS Frac 114-EB ARR	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE					yes	sds	
Orange Extract Natural (NIELSE) (FLAVORCHEM)			Best				flammable	Tygon2375	PTFE				yes	SDS	
Orange Power Plus	Good	[n/r]	[n/r]	Best			Flammable	Gas grad hos	PTFE				yes	SDS + Test	
Orange Power Supreme	Good	[n/r]	[n/r]	Best			Flammable	PTFE	gas grade hose				yes	SDS + Test	
Organic Peppermint Extract (DOEHLER)			Best				flammable	Tygon2375	PTFE				yes	SDS	
Organic Rice Vinegar, 90 grain, 55 gallon drum			Best				neither	Tygon 2375	PTFE				yes	sds	8/16/2024
Original Krud Kutter	Best	good	Good	Best			neither	PVC	2375 by Tygon				yes	SDS	
Orthochloro Ethyl Benzene	[n/r]	[n/r]	[n/r]	Best			flammable	PTFE							
OTRK Lysis Buffer	Best	Good	Good	Good			neither	PTFE					yes	SDS + Test	
Oxalic Acid (Cold)	Good	Best	Best	fair			neither	PVC	2375 by Tygon						
OXAMIN LO	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
OxiDate 2.0	Do Not Use	Caution	Caution	Best			Flammable	2375 by Tygon	PTFE		May require closed system		yes	sds MFG recommended	entered may
OxiDate Bactericide	Do Not Use	Caution	Caution	Best			Flammable	2375 by Tygon	PTFE		In California, may require closed system - see our CCS-8605				
OxiDate Fungicide	Do Not Use	Caution	Caution	Best			Flammable	2375 by Tygon	PTFE		In California, may require closed system - see our CCS-8605				
Oxidite C 14 (MACDERMID ENTHONE)				Best			neither	PTFE					yes	SDS	
OXONIA ACTIVE 150						Best	flammable	PTFE					yes	sds	Aug-19-20
Oxyquest	n/r	n/r	n/r	best			Combustible	2375 by Tygon	PTFE				yes	SDS	
OxyTurf	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon					yes	SDS	
P1023 - Peracetic Acid Solution	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	Flammable	PTFE			Teflon/Kalrez Pump Only		yes	SDS	
P2 Buffer	Best	Good	Good	Good			neither	2375 by Tygon	PTFE				yes	SDS + Test	
PAA /H2O2 by Seaco	n/r	n/r	n/r	n/r		BEST	flammable	PTFE			Teflon/Kalrez Pump Only		yes	Test	
PAA Sanitizer FP	Do not use	Do not use	Do not use	Best			flammable	2375 by Tygon	PTFE				yes	SDS	
PACE HORTI-KLOR (revision 19)			Best				neither	2375 by Tygon					yes	sds	Aug-19-20
Pace Kleengrow		Best	Best				flammable	PTFE			Teflon-Kalrez fluid path		yes	SDS	
Pace Stip-It Pro				Best			neither	PTFE			Teflon-Kalrez upgrade r		yes	SDS	
Pad Safe				Best			neither	Tygon2375	PTFE				yes	SDS	
Palmitic Acid	Good	Good	Best	Best			neither	PTFE	Gas Grade Hose						
Panalane H-300E	do not use	do not use	do not use	do not use							all too viscous		yes	SDS	
PANOCTINE	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
Pantendiol	Do Not Use	Best	Do Not Use	Do Not Use			Combustible	2375 by Tygon	PTFE						
Paraffin Oil	Best	[n/r]	[n/r]	Best			neither	Gas Grade H	PTFE						
Paraplex, Polyester Plasticizer	Best	Good	Good	Best			neither	PTFE			May be too thick for GT		yes	test	
Paraquat	[n/r]	[n/r]	[n/r]	Best			neither	PTFE			Requires Closed System In US				
Paratherm HE Heat Transfer Fluid				Best			combustible	PTFE					yes	sds	

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Parathion Ethyl Methyl	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Parts Kleen II (ECOLICK)	Do Not Use	Do Not Use	Do Not Use	Best			Combustible	PTFE			Atmospheric Contaminant		yes	sds	
PAX XL 6	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE				yes	sds	
PB Free (L-528) (ABC Compounding)	n/r	n/r	best	n/r			Combustible	2375 by Tygon	PTFE				yes	SDS	
PB PENETRATING CATALYST, (BLASTER)				Best			flammable	PTFE					yes	sds	entered may
PBQ Inhibitor Solution (Polynt Composites)				Best			Combustible	PTFE	Viton				yes	SDS & Customer Specified	
PC KLEENGROW			Best				flammable	2375 by Tygon					yes	sds	Aug-19-20
PC STRIP-IT				Best			neither	2375 by Tygon					yes	sds	Aug-19-20
P-Cymene (1 Isopropyl 4 - methylbenzene)	[n/r]	[n/r]	[n/r]	Best			flammable	PTFE					yes	sds	
P-Dichlorobenzene	[n/r]	[n/r]	[n/r]	Best			flammable	PTFE							
Peanut Oil	Best	Do Not Use	[n/r]	Best			neither	PVC	2375 by Tygon						
Penair Mil-C-85590	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Pendulum herbicide (pendimethalin)	[n/r]	Good	[n/r]	Best			neither	2375 by Tygon	PTFE						
PENETRATE BEVERAGE SYSTEM CLEANER		Best					neither	2375 by Tygon					yes	sds	Aug-19-20
PENNANT MAGNUM	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Pennsan Quat 5	[n/r]	best	best	[n/r]			neither	2375 by Tygon	PTFE				yes	sds	
Penray Chlorinated Brake Cleaner 482C				Best	required		Neither	PTFE			Celcon Tap Required		yes	SDS	
Penray Non-Chlorinated Brake Cleaner 462C					required	Best	flammable	PTFE			Celcon Tap Required		yes	SDS	
PENRECO CONOSOL C-200	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	sds	
Pentane 2 Methyl	Best	[n/r]	[n/r]	[n/r]			flammable	Gas Grade H	PTFE						
Pentane 2-4 Dimethyl	Best	[n/r]	[n/r]	[n/r]			Flammable	Gas Grade H	PTFE						
Pentanedione 2,4		Best					flammable	PTFE			Teflon-Kalrez upgrade it		yes	SDS	
Pentane 3 Methyl	Best	[n/r]	[n/r]	[n/r]			Flammable	Gas Grade H	PTFE						
peppermint oil	do not use	do not use	do not use	best			neither	2375 by Tygon	PTFE				yes	Test	
Peracetic Acid - also known as Peroxyacetic Acid (PAA)											There are numbers of liquids which have Peroxyacetic acid in them with a range of stren				
Peracetic Acid Solution by Spectrum	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	flammable	PTFE			Teflon-Kalrez pump only		yes	sds	3/10/2015
PERACLEAN 15 (EVONIK)	Do Not Use	Do Not Use	Do Not Use	Do Not Use		BEST	Flammable	PTFE			Teflon-Kalrez pump only		yes	sds+mfg recommends	Sept 14-19
Peraclean® 5 (FL9898) (EVONIK) (JET) (JET AG)				Best			Flammable	2375 by Tygon	2376 by Tygon				yes	SDS	June-July 202
Peraspray ( Chemstation) (EVIRO TECH)		Good					neither	PTFE			Required Teflon Kalrez		yes	SDS	June-July 202
Perchem 1140-DOA	do not use	do not use	do not use	Best			neither	PTFE					yes	SDS	
Perchloric Acid 72%	Do Not Use	Good	Do Not Use	Best			neither	2375 by Tygon	PTFE		Test				
Perchloroethylene	Do Not Use	Do Not Use	Do Not Use	Best			Combustible	PTFE							
Performance COOLANT 32	Fair	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Per-Ox (AFCO 4325)	n/r	Fair	Good	Best			Flammable	2375 by Tygon	PTFE				yes	SDS + Test	
Peroxigard Concentrate (VIROX) (US)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	Gas grade hose				yes	SDS	
Peroxigard Ready to Use (VIROX)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE				yes	sds	
Peroxysan 5 (OSTREM)	Do not use	Do not use	Do not use	Best			Flammable	PTFE					yes	SDS	
Petroleum Ether (Naphtha)	Do Not Use	Do Not Use	Do Not Use	BEST			flammable	Gas Grade hose					yes		Sept 14-19
Petroleum	Best	Good	Do Not Use	Best			Flammable	Gas Grade H	PTFE						
Petroleum Ether				Best			flammable	PTFE					yes	sds	1/20/2017
PFSA Ionomer 500 Series (Asagi Glass Co., LTD)													SDS		3/15/2017
PFSA Ionomer 600 Series (Asagi Glass Co., LTD)	Good	Best	[n/r]	Best			neither	2375 by Tygon	PTFE						
pH REDUCER CITRIC ACID SOLUTION	Good	Best	[n/r]	Best			neither	2375 by Tygon	PTFE						
PH Stabilizer (ALVIN & OTT)		Best					neither	Tygon 2375	PTFE				yes	sds	Sept 14-19
PH3660 ( PTM&W Industries Inc)				Best			neither	2375 by Tygon	PTFE				yes	sds & mfg recommendat	Aug-19-20
Phenol (Carbolic Acid)	Caution	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE				yes	test	
PHENOL Concentrate (HYDROL)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE				yes	test	
Phenol Sulfonic Acid 65%				Best			neither	2375 by Tygon	PTFE				yes	test	
Phenyl Hydrazine	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			Test				
Phenylbenzene	Do Not Use	Caution	[n/r]	Best			Flammable	PTFE							
PHITICIDE				Best			neither	Tygon 2375	PTFE		CHECK VISCOSITY BEFO		yes	sds MFG recommended	entered may
Phorone	Caution	Good	[n/r]	Good			neither	2375 by Tygon	PTFE						
Phosphoric Acid (to 40% Solution)	Do Not Use	Good	Good	Best			neither	2375 by Tygon	PTFE						
Phosphoric Acid 40-100% Solution	Do Not Use	Good	Good	Best			neither	2375 by Tygon	PTFE						
Phosphoric Acid Crude	Do Not Use	Good	Good	Best			neither	2375 by Tygon	PTFE						
Phosphoric Acid-20%	Do Not Use	Good	Good	Best			neither	2375 by Tygon	PTFE						
Phosphoric Acid-45%	Do Not Use	Good	Good	Best			neither	2375 by Tygon	PTFE						
Phosphorous Trichloride Acid	Caution	Good	Best	Best			neither	2375 by Tygon	PTFE						

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Phostrol Fungicide				Best			neither	2375 by Tygon	PTFE		May be too thick for GT		yes	sds	
PHYTON 27	Best	Best	[n/r]	Best			neither	2375 by Tygon	PTFE						
Piccolastic A5 Hydrocarbon Resin, Polystyrene Resin	Best	Best	Best	Best			neither	2375 by Tygon	PTFE		Too thick for GT pumps		yes	test	
Pickling Solution (acid)	[n/r]	Do Not Use	Caution	Good			neither	2375 by Tygon	PTFE						
Picric Acid	Do Not Use	Good	[n/r]	Best			neither	2375 by Tygon	PTFE						
PINE CLEANER ( Spartan)				Best			neither	2375 by Tygon					yes	sds	Aug-19-20
Pine Oil	Good	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Pinene	Do Not Use	Good	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Antimony	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Arsenic	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Brass	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Bronze	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Cadmium	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Chrome	Caution	Best	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Copper	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Gold	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Indium	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Iron	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Lead	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Nickel	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Silver	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Tin	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plating Solutions: Zinc	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Plexi Glue	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither	neither	neither		a coating liquid, no pump		yes	sds	
PM Acetate (LIBERTY SOLVENT)	Do Not Use	Good	Do Not Use	Do Not Use			Flammable	PTFE			Teflon Kalrez fluid path		yes	test	
PNB (Dowanol, Glycol Ether)	Good	Best	Do Not Use	Good			neither	PTFE					yes	test	
POLY CHEM AERASTRIP 600 B&G (50/50 WATER)	Do Not Use	Good	Best	Do Not Use			neither	2375 by Tygon	PTFE		Teflon Kalrez fluid path		yes	test + sds	
Poly Sorbate 80	Best	Good	Do Not Use	Good			neither	2375 by Tygon	PTFE		Too thick for GT pumps				
Polyaluminum Chloride Solution (GEO SPECIALTY)	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE				yes	sds	
Polybutene	[n/r]	[n/r]	[n/r]	[n/r]			neither	neither	neither		Too thick for GT pumps		yes	note	
Polycat 5 (Evonik)	Do Not Use	Do Not Use	Do Not Use	Do Not Use		BEST	neither	PTFE			Teflon Kalrez pump only		yes	sds	entered May
Poly-Cure 503 (BORCHERS)				Best			Combustible	PTFE	Viton				yes	SDS & Mfg recommended	
Polyester Adipate											Too thick for GT pumps		yes	sds	
Polyethylene Glycol	Do Not Use	Best	Good	Best			neither	2375 by Tygon	PTFE						
POLYGLYCOL/ESTER BLEND	Fair	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Polyslip Coating P-106	[n/r]	[n/r]	[n/r]	Best		Required	flammable	PTFE			must have celcon tap		yes	sds	
Polyslip Coating T-503M	[n/r]	Fair	Best	[n/r]			flammable	PTFE					yes	sds	
Polyt-74	Good	Good	Best	Best			neither	PVC	2375 by Tygon				yes	test	
Polyvinyl Acetate Emulsion	Good	Best	[n/r]	fair			neither	2375 by Tygon	PTFE						
Poni Acid (AFCO 5380)	n/r	n/r	n/r	best			neither	2375 by Tygon	PTFE				yes	SDS	
Potassium Acetate	fair	Best	Best	fair			neither	2375 by Tygon	PTFE						
Potassium Borate	fair	Best	Best	fair			neither	2375 by Tygon	PTFE						
Potassium Bromate	fair	Best	Best	fair			neither	2375 by Tygon	PTFE						
Potassium Bromide	fair	Best	Best	fair			neither	2375 by Tygon	PTFE						
Potassium Chloride	fair	Best	Best	fair			neither	2375 by Tygon	PTFE						
Potassium Cupro Cyanide	fair	Best	Best	fair			neither	2375 by Tygon	PTFE						
Potassium Cyanide Solutions	fair	Best	Best	fair			neither	2375 by Tygon	PTFE						
Potassium Dichromate	fair	Best	Best	fair			neither	2375 by Tygon	PTFE						
Potassium Hex-Cem 15% (BORCHERS)		Good	Best				neither	PTFE					yes	SDS & Mfg recommended	
POTASSIUM HYDROXIDE		Best					neither	2375 by Tygon							Aug-19-20
Potassium Hydroxide 60%	fair	Best	Best	fair			neither	2375 by Tygon	PTFE						
Potassium Nitrate	fair	Best	Best	fair			neither	2375 by Tygon	PTFE						
Potassium Permanganate	fair	Best	Best	fair			neither	2375 by Tygon	PTFE						
Potassium Salts	fair	Best	Best	[n/r]			neither	2375 by Tygon	PTFE						
Potassium Sulfate	Best	fair	Best	Best			neither	2375 by Tygon	PTFE						
Power Blast Detergent				Best			neither	2375 by Tygon	PTFE				yes	sds	
Power Foam CL NP (AFCO 5333)	n/r	best	n/r	n/r			neither	2375 by Tygon	PTFE				yes	SDS	

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Specia	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
POWERKLENE VC	n/r	n/r	n/r	Best			flammable	PTFE					yes	sds	
Powersolv				Best			flammable	PTFE					yes	SDS	
POWERZONE	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Precision Press #2	Good	Do Not Use	[n/r]	Best			neither	Gas Grade H	PTFE						
Precision V1654 (vapor degreaser parts cleaner)		Good	Best				neither	PTFE					yes	sds	
Prelude	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Premium Lacquer Thinner (EMCO)	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE					yes	sds and test	entered May
Premium Lacquer Thinner 210 (FAMIS)	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	flammable	2375 by Tygon	PTFE		Teflon kalrez pump only		yes	sds	
PREP 720	Good	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
PRESS WASH 103 (CMG)	Caution	Do Not Use	Do Not Use	Best			flammable	Gas Grade H	PTFE				yes	test	
Press wash Conventional ink (Saphira)	Best	Do Not Use	Do Not Use	Good									yes	test	
Prestone 50/50 Prediluted EngineReady to use Coolant/Antifreeze			Best				neither	Tygon 2375	PTFE				yes	sds	8/5/2024
Prestone 50/50 Ready to use Antifreeze/ Coolant			Best				neither	Tygon 2375	PTFE				yes	sds	8/5/2024
Pretreat Plus 0100	[n/r]	[n/r]	[n/r]	Good			neither	2375 by Tygon	PTFE				yes	sds	
PRIMAL ASE-60	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
PRINCEP	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Principal (ECOLAB)	[n/r]	Best	Best	[n/r]			neither	2375 by Tygon	PTFE				yes	sds	
Printers Etch	[n/r]	[n/r]	[n/r]	Best			neither	PTFE					yes	test + sds	
PRISM SEMI-GLOSS FPC BLACK							flammable				Too thick for GT Pumps		yes	sds	June 04 2019
PRO PRODUCTS RID-O'RUST FORMULA 2000	Best	Good	Good	Best			neither	PVC	PTFE						
Pro Series Prozymes Pool (NATURAL CHEMISTRY)		Good	Good	Best			neither	Tygon2375	PTFE				yes	SDS & MFG Recommended	
Proclean	Fair	[n/r]	[n/r]	Best			neither	PTFE					yes	sds + test	
PROCLEAN * DEGREASER		Best					neither	2375 by Tygon					yes	sds	Aug-19-20
Proclean LS-202 (Prosys Finishing Technologies)				Best			neither	2375 by Tygon					yes	SDS	June-July 202
PROCLIN 300				Best			neither	2375 by Tygon			Testing 6/20 Hastelloy S		yes	sds	Aug-19-20
Progeny Herbicide	n/r	n/r	n/r	best			unknown	2375 by Tygon	PTFE				yes	sds	
Proguardium Optimum™ Disinfectant/sanitizer (Proguardium)		Best					neither	PVC					yes	SDS	June-July 202
PROKLENZ * NPH		Best					neither	2375 by Tygon					yes	sds	Aug-19-20
PROKLENZ * NPH HIGH PERFORMANCE NEUTRAL DETERGENT		Best					neither	2375 by Tygon					yes	sds	Aug-19-20
ProKlenz 100		Best					neither	Tygon 2375	PTFE				yes	sds	Sept 14-19
ProKlenz 120		Best					neither	Tygon 2375	PTFE				yes	sds	Sept 14-19
ProKlenz Booster (Steris)				Best			neither	2375 by Tygon	PTFE				yes	sds	3/10/2015
ProKlenz One		Best					neither	Tygon 2375	PTFE				yes	sds	Sept 14-19
ProKlenz Two		Best					neither	Tygon 2375	PTFE				yes	sds	Sept 14-19
Promosolve (Inventenc)		Best					neither	PTFE			Vapor Degreaser Recon		yes	MFG recommended	
Promosolve 70 ES (INVENTEC)				Best			neither	PTFE			Teflon-Kalrez fluid Path		yes	SDS	
Propane (Liquified) (LPG)	Best	Caution	Do Not Use	Best			flammable	Gas Grade H	PTFE						
Propanol Normal			Best				Flammable	Tygon2375	PTFE		Teflon-Kalrez upgrade r		yes	SDS	
propenoic Acid (Acrylic Acid)	Do Not Use	Best	Do Not Use	Do Not Use			neither	2375 by Tygon	PTFE						
propionic acid (methyl Acetic Acid)	Fair	Best	Good	fair			neither	PTFE							
Proprietary Solvent Ill-1, Anhydrous	Fair	Good	Fair	Best			flammable	2375 by Tygon	PTFE				yes	sds + Test	
Propyl Acetate	Do Not Use	Good	Best	Do Not Use			neither	PTFE							
Propyl Alcohol	Good	Best	Best	fair			flammable	2375 by Tygon	PTFE						
Propyl Nitrate	[n/r]	Good	Good	Do Not Use			neither	2375 by Tygon	PTFE						
Propylene	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
Propylene Glycol (methyl glycol)	Do Not Use	Best	Best	Good			neither	PVC	2375 by Tygon				yes	sds	
Propylene Glycol Tech (Univar)		Best					neither	PVC Hose	2375 by Tygon				yes	SDS	June-July 202
Propylene Oxide	n/r	Best					flammable	2375 by Tygon	PTFE						
PROSCUCUTOR	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Prothiofos	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Proxel GL	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE						
Proxel GLX	[n/r]	Best	Good	[n/r]			neither	2375 by Tygon	PTFE				yes	sds	
PROXITANE * AHC	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	Combustible	2375 by Tygon			Teflon-Kalrez pump only		yes	sds	Aug-19-20
Proxitane EQ Liquid Sanitizer	Do not use	Do not use	Do not use	Best			Flammable	2375 by Tygon	PTFE				yes	SDS	
Prozone SC01 Cleaner 5GA Box	Best	Do Not Use	Do Not Use	Do Not Use			neither	2375 by Tygon	PTFE				yes	sds + test	
PSA Purge Solvent	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE					yes	sds	
PSA529 55G-Drum (Momentive)				Best	yes		Flammable	PTFE			Not recommended Build		yes	sds	6/10/2024

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
P-Tertiary Butyl Catechol	[n/r]	Best	[n/r]	[n/r]			flammable	PTFE							
Purgon-MHP (UNITECH LUBRICANTS)			Best				neither	Tygon2375	PTFE		Teflon-Kalrez upgrade i		yes	SDS	
PURITY FG A W HYDROLIC FLUID, 32, 46, 68, 100	Best	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	sds + email	
PURITY FG EP GEAR FLUID 100	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	email	
PURITY FG EP GEAR FLUID 150, 220, 320, 1719	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither	Gas Grade H	PTFE		TOO THICK				
Pur-Ox				Best			neither	Tygon 2375	PTFE				yes	sds	11/11/2024
Purple Power Industrial Strength Cleaner/Degreaser	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE					yes	sds	
Purple Stuff			Best										yes	MFG Disclosure	
PVW-4 Flux Remover (Techspray)	Do Not Use	Do Not Use	Do Not Use	Do Not Use		BEST	neither	PTFE			Teflon-Kalrez pump only		yes	sds	Sept 14-19
Pyganic, MGK	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE							
PYLON	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE							
PYRENONE 25-5	Caution	Do Not Use	Do Not Use	Best			neither	PTFE			mosquito control				
Pyridine Oil	Do Not Use	Good	[n/r]	Do Not Use			neither	PTFE							
Pyroil Low VOC Non-Chlr Brake	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	Flammable	PTFE			Teflon-Kalrez pump only		yes	sds + test	
Pyroigneous Acid (wood vinegar)	fair	Caution	[n/r]	Best			neither	PTFE			Wash				
Pyrolubo	[n/r]	[n/r]	[n/r]	Best			neither	Gas Grade H	PTFE						
Q2 TECHNOLOGY ENVIRO SCRUB LM	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			PVC Hose OK				
Quakerclean 624 MPC	Do Not Use	Best	Do Not Use	Do Not Use			neither	2375 by Tyg	PTFE				yes	sds	
Quaternary Ammonium Chloride, Alcohol, Water (SPACE 49)		Best					neither	2375 by Tygon					yes	sds	
QUEL CIP HD	N/R	Best	N/R	n/r			neither	2375 by Tyg	PTFE				YES	SDS	
QUICK SILVER (mercury)	Do Not Use	Do Not Use	[n/r]	Best			neither	PTFE							
Quick Solv	Do Not Use	Do Not Use	Do Not Use	Best		required	Flammable	PTFE			celcon tap required		yes	sds	
QUINTEC FUNGICIDE		Best					neither	Tygon 2375	PTFE		May be too thick for GT		yes	sds MFG recommended	entered may
QUINTOZENE FLOWABLE	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tyg	PTFE						
Quorum Clear V	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tyg	PTFE				yes	sds	
Quorum Purple	[n/r]	Do Not Use	[n/r]	Best			neither	2375 by Tyg	PTFE				yes	sds	
Quorum Yellow LP	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tyg	PTFE				yes	sds	
RADCOLUBE FR282 (RADCO)				BEST			Neither	Gas Grade	PTFE				yes	sds + mfg recommended	5/1/2018
Radiator Brand brake cleaner	do not use	do not use	do not use	best							Requires Celcon tap due to heptane				
RADIATOR SUPPLY BRAKE CLEANER M739C	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE			Flammable				
RALLY 40WSP Fungicide				Best			neither	Tygon 2375	PTFE		CHECK VISCOSITY BEFO		yes	sds MFG recommended	entered may
RANMAN 4005C FUNGICIDE				Best			neither	Tygon 2375	PTFE		CHECK VISCOSITY BEFO		yes	sds MFG recommended	entered may
Rapeseed Oil	Do Not Use	Best	[n/r]	Best			neither	PVC	2375 by Tygon						
Raspberry Flavoring (Magnum Coffee)	Do Not Use	Best	[n/r]	Best									yes	test	
RAXIL C Flowable seed dressing	Best	[n/r]	[n/r]	[n/r]			neither	PVC	2375 by Tygon						
RB Degreaser	Good	Good	best	best			neither	2375 by Tygon					yes	sds + test	
RBB Buffer	Best	Good	Good	Good			Flammable	2375 by Tygon					yes	sds + test	
RD 531	Do Not Use	Best	Good	Do Not Use			neither	2375 by Tyg	PTFE		CHECK VISCOSITY BEFO		yes	SDS	
RD 531 ( chautauqua Metal finishing Company )		Best					neither	PTFE TEFLON					yes	sds	Aug-19-20
RD 531 (Chautauqua Metal finishing Company			Best				neither	Tygon2375	PTFE		Teflon-Kalrez upgrade r		yes	SDS	
RD-20	Do Not Use	Do Not Use	[n/r]	Best			neither	PVC	2375 by Tygon						
Red One Pickling Spray 240				Best			neither	Tygon2375	PTFE				yes	SDS	
Redi San RTU Hard Surface Sanitizer	Do Not use	Best	Do Not Use	Do Not Use			neither	2375 by Tyg	PTFE				yes	sds	
Reflex (Enviro Tech)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE				yes	sds	entered May
Refresh	[n/r]	[n/r]	[n/r]	Best			neither	PTFE					yes	sds	
REJEX	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither	neither	neither		A coating liquid that will		yes	sds	
Remove PW15	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE			may require celcon tap		yes	sds	
Remove PW2	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE			may require celcon tap		yes	sds	
Renolin WL 68 NW	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE				yes	sds	
Rescue Ready One Step by Virox	Do Not Use	Best	Good	good			neither	2375 by Tyg	PTFE				yes	sds	
Revolution (Aquatrols)	Do Not Use	Best	Good	Best			neither	2375 by Tyg	PTFE		Check viscosity - wetting agent				entered May
Reward Herbicide (Diquat dibromide)	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
Rhoma-Sol	[n/r]	[n/r]	[n/r]	Best			Combustible	2375 by Tyg	PTFE		Turns to gel on contact		yes	sds	
RHYME FUNGICIDE				Best			neither	Tygon 2375	PTFE		CHECK VISCOSITY BEFO		yes	sds + MFG recommended	entered may
Rid O' Rust Formula 2000	Good	Good	Good	Best			neither	2375 By Tyg	PTFE		CHECK VISCOSITY BEFO		yes	sds	
RIDOMIL GOLD COPPER							neither	Tygon 2375	PTFE		CHECK VISCOSITY BEFO		yes	sds MFG recommended	entered may
Ro-16	Good	Good	Best	Best			neither	Tygon 2375	PTFE				yes	sds + test	

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
RO-25	Good	Good	Good	Best			neither	2375 by Tygon	PTFE		May be corrosive to me		yes	test	
ROCIMA BT 2S MICROBICIDE (DOW)		Best					neither	2375 by Tygon					yes	sds	Aug-19-20
ROCIMA™BT NV2			Best				neither	2375 by Tygon					yes	sds	Aug-19-20
RODEO	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
ROGOR 400	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Roots 1-2-3	Do Not Use	Best	[n/r]	Best			neither	2375 by Tygon	PTFE						
ROSSTECH 147FD						BEST	flammable	PTFE			Teflon-Kalrez pump only		yes	TEST	entered may
ROUNDUP	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
ROUNDUP PRO	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
ROUNDUP QUIKPRO	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tygon	PTFE						
ROYAL SILVER SPRAY MILD				Best			flammable	PTFE					yes	sds MFG recommended	entered may
ROVRAL AQUAFLO	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
ROVRAL LIQUID	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
ROVRAL LIQUID S.D.	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
ROYCO 756D & 756E ROYAL LUBRICANTS	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	2375 by Tygon				yes	sds	
ROYCO 808 MIL PRF-7808				BEST			Neither	Gas Grade	PTFE				yes	sds	5/1/2018
RT100S G or D Big Blu	n/r	n/r	n/r	best			neither	PTFE					yes	sds	
RTU D2 Sanitizer (ZEP)	[n/r]	[n/r]	[n/r]	Best			flammable	2375 by Tygon	PTFE				yes	sds	
RTU Surface Sanitizer(Ecolab)	Do Not Use	Do Not Use	Best	Do Not Use			Flammable	2375 by Tygon	PTFE				yes	sds	
Rust Rescue 100 (CITRI SURF)	Best	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE				yes	sds	
RV Antifreeze	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tygon	PTFE						
Rydlyme				Best			neither	Tygon	2375 PTFE		Teflon coated screws are		yes	SDS	
S-3378 SOLVENT BLEND (Superior Industrial)				Best	required		Flammable	PTFE			Celcon tap required		yes	sds	5/1/2018
S-500 CF	[n/r]	[n/r]	[n/r]	Good			neither	Viton	PVC				yes	sds & mfg	
S-722	Do Not Use	good	Do Not Use	best			neither						yes	sds/test	
S-9118 Solvent Blend	[n/r]	[n/r]	Best	[n/r]			Flammable	2375 tygon	PTFE				yes	sds	
SAFETY KLEEN AMERICA'S CHOICE DIESEL	Do Not Use	Do Not Use	Do Not Use	Best									no		
Safety-Kleen 6770 Lacquer Thinner	Do Not Use	Do Not Use	Do Not Use	Best	required		Flammable	PTFE			Celcon tap/ Fluid Path		yes	plastic test	10/26/2016
Safety-Kleen Premium Solvent Thinner L.P. (Safe)	Best	Fair	Do Not Use	Good			flammable	PTFE					yes	test/sds	
Sage Brush 40	[n/r]	[n/r]	[n/r]	Best			neither	gas					yes	sds	
Saniclean	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE					yes	sds + product sheet	
SaniDate 12.0	n/r	n/r	n/r	n/r		BEST	Flammable	PTFE					yes	sds + test	
SaniDate 15.0	n/r	n/r	n/r	n/r		BEST	Flammable	PTFE					yes	sds + test	
SaniDate 5.0 Sanitizer/Disinfectant	n/r	n/r	n/r	Best			flammable	2375 by Tygon	PTFE				yes	sds	
SANI-PAK SP97000	n/r	n/r	n/r	Best			neither	2375 by Tygon	PTFE				YES	tds	21-Apr
SANI-PLEX 128M (QUIP)	n/r	n/r	Best	n/r			neither	2375 by Tygon	PTFE				yes	SDS	June-July 202
Sanitizer (Members Mark)	[n/r]	n/r	Best	n/r			neither	2375 by Tygon	PTFE				yes	SDS	
Sanitizer 141, Ethylhexyl Diphenyl	[n/r]	Best	best	Fair			neither	2375 by Tygon	PTFE				yes	test	
Sanitizer 160, Benzyl Butyl Phthalate	Do Not Use	Best	N/R	Best			neither	2375 by Tygon	PTFE				yes	test	
Saphira Alcohol Replacement 301	Best	Good	Fair	Fair			neither	2375 by Tygon	PTFE				yes	test	
Saphira Fountain Solution 201	Best	Do Not Use	Do Not Use	Good			flammable	PTFE					no		
Saphira Presswash Conventional Ink, Aliphatic H	n/r	n/r	n/r	Best			flammable	2375 by Tygon	PTFE				yes	sds	
SASOL ETHANOL SDA 40B 190 Proof	Best	Good	Good	Good			Combustible	2375 by Tygon	PTFE		Probably too thick to use		yes	sds	
Satin Silicone WA	Good	Good	Best	Best			neither	Tygon 2375	PTFE		300 cS viscosity		yes	sds+mfg recommends	Sept 14-19
SB-Antifoam 2504 (Shepard)	Best	Best	Best	Best		Best	neither	Tygon 2375	PTFE		300 cS viscosity		yes	sds and mfg. rec.	7/10/2024
SBT-710	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE				yes	test	
SC 300M Silicone Gel Encapsulant	[n/r]	[n/r]	[n/r]	Best			neither	Tygon 2375	PTFE		CHECK VISCOSITY BE		yes	sds MFG recommended	entered may
SCALA SC FUNGICIDE	n/r	n/r	n/r	Best			neither	2375 by Tygon	PTFE		CHECK VISCOSITY BE		yes	sds	
Scale Gone 70C	n/r	Good	n/r	Best			neither						yes	sds	
Schermcemol Co Ester	fair	Do Not Use	Do Not Use	Best			neither	2375 by Tygon	PTFE				yes	sds + test	
Sea Water				best			neither	2375 by Tygon	PTFE				no		entered may
Seamless Trowel Lube, Seamless Flooring System	Do Not Use	Do Not Use	Best	Best			neither	2375 by Tygon	PTFE				yes	test	
SEMEVIN 500 P	fair	best	fair	do not use									yes	sds + test	
Semicosil 936UV	fair	Best	fair	Do Not Use			neither	2375 by Tygon	PTFE				yes	sds + test	
SENCOR 480 SC	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tygon	PTFE						
Sequestrian 30 A	n/r	n/r	n/r	Best											
Service Pro Non-Chlorinated Brake Cleaner				Best	required		Flammable	PTFE			Celcon Tap Required /		yes	SDS	
Servpro 134 Orange (d limonene)				Best			neither	2375 by Tygon	PTFE				yes	email	
Servpro 138 Green (butyl cellosolve)		Best	best				neither	2375 by Tygon	PTFE				yes	email	
Servpro 208 Glass Cleaner, RTU (IPA, Butyl Cellosolve, Ammol)	Best	best	best				neither	2375 by Tygon	PTFE				yes	email	



Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Servpro 351 Wall and All Surface Cleaner (Alcohol + sodium Hy	best	best					neither	2375 by Tyg	PTFE				yes	email	
Servpro 352 Wall and All Plus (IPA, Butyl, Cellosolve, Ammoniu	best	best					neither	2375 by Tyg	PTFE				yes	email	
Severely Hydrotreated Petroleum Oil	n/r	n/r	n/r	Best			neither	gas grade hd	PTFE		According to Chemical		yes	sds	
Shell Tellus S2 M 32	Do Not Use	Do Not Use	Do Not Use	Best			neither						yes	sds	
SHEPHERD COBALT NITRATE SOLUTION 15%	Do Not Use	Do Not Use	Do Not Use	Best			neither	neither	neither						
SHEPHERD COPPER NITRATE SOLUTION 18%	Do Not Use	Do Not Use	Do Not Use	Best			neither	neither	neither						
SHEPHERD FERRIC NITRATE SOLUTION 10.5	[n/r]	[n/r]	[n/r]	[n/r]			neither	neither	neither						
SHEPHERD MAGNESIUM NITRATE SOLUTION	Do Not Use	Do Not Use	Do Not Use	Best			neither	neither	neither						
SHEPHERD NICKEL NITRATE SOLUTION 14%	Do Not Use	Do Not Use	Do Not Use	Best			neither	neither	neither						
SHEPHERD ZINC NITRATE SOLUTION 1826	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither	neither	neither	Teflon-Kalrez					
Sherwin Williams R7K119 Lacquer Thinner	[n/r]	Fair	[n/r]	Best			flammable	PTFE					yes	sds/test	
Sher-Wood Polypropylene Primer						Best	flammable	PTFE					yes	SDS	
Shoplifter Parts Cleaner	n/r	n/r	fair	Best			neither	PTFE					yes	sds + test	
Shureclean Plus	do not use	do not use	do not use	Best			unknown						yes	sds	
Signet Pot & Pan Detergent				Best			Neither	PTFE			Teflon-Kalrez upgrade it		yes	SDS & MFG Recommended	
Silcare silicone 41M15	Do Not Use	Do Not Use	Do Not Use	Best			unknown	PTFE					yes	test	
Silicate Esters	Best	Good	Do Not Use	Best			neither	2375 by Tyg	PTFE		May be too thick				
Silicone Oils	Best	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE				yes	sds	
Silquest A-1120 Silane	fair	Do Not Use	Do Not Use	Best			unknown						yes	sds	Sept 14-19
SILQUEST A-187 SILANE (Same as Dow Corning Si	[n/r]	Good	Good	[n/r]			neither	2375 by Tyg	PTFE		May be too thick		yes	sds	
Silshine 151 Silicone Fluid	Fair	Best	Good	Best			unknown				not recommended beca		yes	sds + test	
Silshine 151	fair	Best	Good	Best			unknown				not recommended beca		yes	sds + test	
Silver Nitrate	Good	Best	Do Not Use	Do Not Use			neither	PVC	2375 by Tygon						
Simple Green - all strengths	Do not use	Do not use	Best				Neither	Tygon2375	PTFE				yes	sds	Feb-17
Simple Green All-Purpose Cleaner	Do not use	Do not use	Best	Do not use			neither	2375 by Tyg	PTFE				yes	sds	
Simple Green Cleaner/Degreaser/Deodorizer	Do Not Use	Good	Best	Do Not Use			neither	2375 by Tyg	PTFE				yes	sds + test	
Simple Green Industrial Cleaner & Degreaser	Do Not Use	Good	Best	Do Not Use			neither	2375 by Tyg	PTFE				yes	sds	
SKYDROL 500 B-4 fire resistant hydraulic fluid	Do Not Use	Best	Do Not Use	Do Not Use			neither	2375 by Tyg	PTFE				yes	SDS	
Skydrol LD4 Fire Resistant Hydraulic Fluid		best					neither	2375 by Tyg	PTFE				yes	SDS and Mfg recommed	3/10/2015
SLCC-A (Drew Marine)				Best			neither	PTFE			Teflon Kalrez fluid path		yes	sds+mfg recommends	Sept 14-19
Slide Bulk Mold Cleaner 4				Best	required		flammable	PTFE			Celcon Tap Required		yes	SDS	
Slide Mold Shield "Dry" Rust Preventive Bulc				Best	required		flammable	PTFE			Celcon Tap Required		yes	SDS	
SLIX	Do Not Use	Good	good	Do Not Use			neither	2375 by Tyg	PTFE				yes	sds	
SMOKEZ H-10		Best	Best				neither	Tygon 2375	PTFE		Teflon Kalrez fluid path		yes	sds	June 04 2019
SNAP				Best			neither	Tygon2375	PTFE				yes	sds	Feb-17
Soda Ash (Sodium Carbonate)	Good	Best	Best	Best			neither	PVC	2375 by Tygon				yes	sds	
Sodium Acetate	Fair	Good	Best	Fair			neither	PVC	2375 by Tygon				yes	sds	
Sodium Acid Sulfite - Sodium Bisulfite 40%	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Sodium Bicarbonate (Baking Soda)	Good	Best	Best	Good			neither	PVC	2375 by Tygon						
Sodium Bisulfate	Good	Best	Best	Good			neither	PVC	2375 by Tygon						
Sodium Bisulfite	Good	Best	Best	Good			neither	PVC	2375 by Tygon						
Sodium Bisulfite Solution 40%	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Sodium Borate	Good	Best	Best	Good			neither	PVC	2375 by Tygon						
Sodium Carbonate	Good	Best	Best	Best			neither	PVC	2375 by Tygon				yes	SDS	
Sodium Chloride 0.9% Aq w/v Solution (S6566)-	Do Not Use	Do Not Use	Best	Do Not Use			neither	2375 by Tyg	PTFE				yes	SDS	
Sodium Cyanide	Good	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
Sodium Hydrogen Sulfite - Sodium Bisulfite 40%	Good	Best	Best	Good			neither	2375 by Tyg	PTFE				yes	sds	
Sodium Hydroxide (20% Solution)	Do Not Use	Best	Best	Do Not Use			neither	2375 by Tyg	PTFE				no		
Sodium Hydroxide (50% Solution)	Do Not Use	Best	Best	Do Not Use			neither	2375 by Tyg	PTFE				no		
Sodium Hydroxide (80% Solution)	Do Not Use	Best	Best	Do Not Use			neither	2375 by Tyg	PTFE				no		
Sodium Hypochlorite (12.5%)	Do Not Use	Do Not Use	fair	best			neither	2375 by Tyg	PTFE				yes	sds	
Sodium Hypochlorite (15%)	Do Not Use	Do Not Use	fair	best			neither	2375 by Tyg	PTFE				yes	sds	
Sodium Lauryl Ether Sulfate SLES	Good	Good	Do Not Use	Best			neither	2375 by Tyg	PTFE				yes	test	
Sodium Metaphosphate	Best	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
Sodium Metasilicate	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tyg	PTFE						
Sodium Nitrate	Good	Best	Best	Best			neither	2375 by Tyg	PTFE						
Sodium Perborate	Good	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
Sodium Peroxide	Good	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
Sodium Phosphate	Good	Best	Best	Best			neither	2375 by Tyg	PTFE						
Sodium Phosphate, Monobasic	Good	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
Sodium Phosphate, Tribasic	Good	Best	[n/r]	Best			neither	2375 by Tyg	PTFE						
Sodium Salts	Good	Best	[n/r]	[n/r]			neither	2375 by Tyg	PTFE						
Sodium Silicate	Good	Best	[n/r]	Good			neither	2375 by Tyg	PTFE						

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Sodium Sulfide	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Sodium Sulphate	Good	Best	Best	Good			neither	2375 by Tyg	PTFE						
Sodium Sulphite	Good	Best	[n/r]	Good			neither	2375 by Tyg	PTFE						
Sodium Thiosulphate (Hypo)	Good	Best	[n/r]	Good			neither	2375 by Tyg	PTFE						
Sodium Xylene Sulphonate	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
Soft Pink Hand Soap (Sattelite)			Best				neither	2375 by Tyg	PTFE				yes	SDS	June-July 202
Soil-off II (2)	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tyg	PTFE				yes	SDS	
Solusolv 2075	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tyg	PTFE				yes	sds + cust info	
Solution II (Omega Bio-Tech)															
	Good	Best	Good	Good			neither	2375 by Tyg	PTFE				yes	sds + test	
Solution III	Best	Best	Best	Best			neither	2375 by Tyg	PTFE				yes	sds + test	
Solvent 1288	Fair	[n/r]	[n/r]	[n/r]		BEST	Flammable	PTFE							
Solvent 140 (Dodge)				Best			neither	PTFE					yes	sds	6/27/2024
Solvent 142-66 (Ashland)	Do Not Use	Do Not Use	Do Not Use	Best	require	Best	flammable	PTFE			teflon kalrez fluid path u		yes	sds	entered May 2
Solvent CB27	Fair	[n/r]	[n/r]	[n/r]		BEST	Flammable	PTFE					yes	test	
SOPUS Products 601 M-12	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tyg	PTFE						
Sorbitan Monolaurate Polyoxethylene	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tyg	PTFE						
Sorbitol	Good	Good	Good	Good			neither	2375 by Tyg	PTFE		Must be heated to achie	yes		test	
SOVRAN FUNGICIDE				Best			neither	PTFE			CHECK VISCOSITY BE	yes		sds MFG recommended	entered may 3
soy sauce	Best	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
Soybean Oil	Best	Good	Good	Best			neither	2375 by Tyg	PTFE						
Soyquest Degreaser	n/r	n/r	n/r	best			unknown	2375 by Tyg	PTFE				yes	sds	
SP™ 607L BELT DRESSING						best	flammable	PTFE					yes	sds	Aug-19-20
SP™ 705L NON-CHLORINATED BRAKE & PARTS CLEANER						best	flammable	PTFE					yes	sds	Aug-19-20
Spartan Acid Blend FP				Best			neither	PTFE					yes	customer order	June-July 202
Spartan High Performance Alkaline FP		Best					neither	2375 by Tyg	PTFE				yes	customer order	June-July 202
Spectra Clean Purge			Best				flammable	PTFE					yes	SDS	
Spectrus NX1100 (Suez Water)	Best	Good	Do Not Use	Do Not Use			neither	PTFE			needs hastaloy springs	yes		SDS	
Spectrus OX 909 (Suez Water)		Best					neither	2375 by Tyg	PTFE				yes	SDS and Mfg recommed	3/10/2015
SPEEDZONE ST. AUGUS	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tyg	PTFE						
SPIN FLOWABLE	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tyg	PTFE		May be too thick for GT Pumps				
Spore-Klenz Concentrate				Best			flammable	Tygon2375	PTFE				yes	SDS	
Spor-Klenz Ready to Use	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE		Steris recommends cus	yes		sds	
Spray Nine 20L	Do Not Use	Do Not Use	Do Not Use	Do Not Use			neither				Not Good with Polypro	yes		sds + Mfg recommended	
Spray Nine All-In-One General Pressroom Clean	n/r	best	Best	n/r			neither	2375 by Tyg	PTFE				yes	sds	
Squeegee Squad Professional Window Soap			Best				neither	Tygon 2375	PTFE				yes	sds	8/5/2024
Squid Ink (SI-PZ4243-Flush)	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE				yes	sds	
SR256 (Sartomer)			best				neither	2375 by Tyg	PTFE				yes	sds + test	
SR500 05G-Pail Primer Solution (Momentive)				Best			Flammable	PTFE			not recommend : will bu	yes		sds	6/10/2024
SR506 (Sartomer)	Do Not Use	Do Not Use	Do Not Use	Do Not Use		BEST	neither	PTFE			Teflon-Kalrez Pump On	yes		sds + test	
SS Solvent	Do Not Use	Best	Do Not Use	Do Not Use			Flammable	PTFE			Teflon-kalrez fluid path	yes		test	
SS-0410 Solvent Blend (Superior)						Best	Flammable	PTFE					yes	sds	5/22/2024
STABROM 909 Biocide	Good	Good	Best	Best			neither	2375 by Tyg	PTFE				yes	sds + test	
Stadis (R) 450	[n/r]	[n/r]	[n/r]	Best	required		Flammable	PTFE			celcon tap required	yes		sds	
STAIN (MH)	Caution	fair	Do Not Use	Best			neither	gas hose	PTFE				yes	test	
Stannic Chloride	Best	Good	[n/r]	Best			neither	2375 by Tyg	PTFE						
Stannous Chloride	Best	Good	Best	Best			neither	2375 by Tyg	PTFE						
Starbright 415															
	Best	n/r	n/r	n/r			neither	2375 by Tyg	PTFE				yes	sds + Manufacturer recommends Nitrile	
Starfire AW 32, 46, 68	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	sds	entered May 2
Starfire RV & Marine Antifreeze -50	Do Not Use	Fair	Best	Do Not Use			Combustible	2375 by Tyg	PTFE				yes	sds	
Starfire Washer Solvent-20	n/r	n/r	Best	n/r			Flammable	2375 by Tyg	PTFE				yes	sds	
STC U (BULK) (BASF)		good	best				neither	2375 by Tyg	PTFE				yes	SDS	June-July 202
Steamite Plus			Best				Neither	Tygon2375	PTFE				yes	sds	Feb-17
Stearic Acid	Good	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE		Tygon 4040 For remote discharge nozzle, use Tygon 200SE FEP lined tubing				
STEN ERASE	Best	[n/r]	[n/r]	Best			Flammable	PTFE							
Stepanquat 8358	Fair	Good	Best	Fair			flammable	2375 by Tyg	PTFE				yes	sds + test	
Ster-BAC Quat		Good	Best				Neither	Tygon2375	PTFE				yes	sds + customer order	Feb-17
Stone Leigh 1832				Best			neither	Tygon2375	PTFE				yes	SDS	
StorOx Bactericide	Do Not Use	Caution	Caution	Best			neither	2375 by Tyg	PTFE						
StorOx Fungicide	Do Not Use	Good	Caution	Best			neither	2375 by Tyg	PTFE						
STRESS MASTER SI 0-28-26 1% SI FERTILIZER		Good	Best				neither	2375 by Tyg	PTFE				yes	sds	Aug-19-20
Strike 3				Best			neither	Tygon2375	PTFE				yes	SDS	

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Strong Acid			Best				neither	2375 by Tyg	PTFE				yes	test	
Styrene Monomer						Best	Flammable	PTFE		GT TE	CELCON TAP		SDS		Feb-17
Styrene Monomer					require	Best	flammable	PTFE			Celcon Tap required / S		yes	SDS	
Styrene Monomer (vinyl benzene)	Fair	Fair	Fair	Best			neither	PTFE			Need testing on PP		no		
STYRID (STONER)				Best			Flammable	PTFE	Viton				yes	SDS & Mfg recommended	
Sucrose Solution	Best	Good	Good	Best			neither	PVC	2375 by Tygon						
Sulfur Chloride	Caution	Do Not Use	[n/r]	Best			neither	PTFE			Polypro is no good				
Sulfuric Acid (10-89%)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE				yes	sds	
Sulfuric Acid (90-97%)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE		Teflon-Kalrez tap orings		no		9/13/2015
Sulfuric Acid (98%)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE		Must have Teflon Kalrez		yes	SDS and Mfg recommed	3/10/2015
Sulfurous Acid	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tyg	PTFE						
Sulphur Hexafluoride	Good	Best	[n/r]	good			neither	2375 by Tyg	PTFE						
Sulphur Liquors	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
Sulphuric Acid (10-89%)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE				yes	sds	
Sulphuric Acid (90-97%)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE		Teflon-Kalrez tap orings		no		9/13/2015
Sulphuric Acid (98%)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE		Must have Teflon Kalrez		yes	SDS and Mfg recommed	3/10/2015
Sunflower Oil	fair	Good	Good	best			neither	2375 by Tyg	PTFE				yes	sds + test	
SUPER BLUE	Do Not Use	Best	Good	Do Not Use			neither	2375 by Tyg	PTFE						
Super Charge (MEYER LABS)				Best			neither	PTFE					yes	SDS & MFG Recommended	
Super CIP 200 (AFCO 5235)	n/r	best	best	n/r			neither	2375 by Tyg	PTFE				yes	sds	
Super Clean 34	n/r	n/r	n/r	best			neither	2375 by Tyg	PVC				yes	sds	
SUPER SPEED STRIP LIQUID				Best			combustible	PTFE			hastelloy springs, teflon coated		yes	sds+mfg recommends	Sept 14-19
Superclean 127 Metal Cleaner	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE					yes	sds	
SUPRACIDE	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
SURF -80	Do Not Use	Best	Do Not Use	Do Not Use			neither	2375 by Tyg	PTFE						
Surf Side 37	Good	Good	Good	Good			neither	no info	no info		too thick for GT Pumps,		yes	sds + mfg recommended	3/10/2015
SURFLAN AS	Do Not Use	Do Not Use	[n/r]	Best			neither	2375 by Tyg	PTFE						
Surfynol 104DPM Surfactant	Do Not Use	Best	Caution	Do Not Use			flammable	2375 by Tyg	PVC		recommendations are q		yes	sds	
Surfynol CT-131 Grind Aid	Good	Best	Best	Good			neither	2375 by Tyg	PTFE				yes	sds/test	
Surfynol CT-324 Dispersant	Good	Best	Best	Good			neither	2375 by Tyg	PTFE				yes	sds/test	
SUR-KLEEN ALALINE CLEANER		Best	Best				neither	2375 by Tyg	PTFE				yes	sds	Aug-19-20
Surpass 100 (Biocide)	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE				yes	sds	
Susan Sensational Solutior				Best			neither	PTFE			Vapor Degreaser pump		yes	SDS	
Sweet Almond Oil	Do Not Use	Best	Good	do Not Use			neither	PVC	2375 Hose by Tygon				yes	sds	
SX7071			Best				Neither	PTFE					yes	sds/test	Feb-17
SX7104			Best				neither	PTFE					yes	sds/test	Feb-17
SYLTHERM XLT# Heat Transfer Fluid (DOW)				best			neither	2375 by Tyg	PTFE				yes	sds	
Syn Lube 46	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE						
SYNERGEX US by ECOLAB				best			flammable	PTFE			Teflon Kalrez fluid path		yes	sds	Aug-19-20
Synergy ISO 220 (Royal Purple)	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	sds	entered May 2
Synpower 75W-90 (Valvoline) Gear oil	[n/r]	[n/r]	[n/r]	Best			neither	gas grade hd	PTFE				yes	sds	
Synthetic Oil 176F (Nye Lubricants Inc)				Best			neither	Gas Grade	Viton hose				yes	SDS	June-July 202
Syntilo 9930	n/r	Best	Good	n/r			neither						yes	sds	
T-91 Degreaser LPS	Good	Good	Good	Best									yes	sds+ test	
Tannic Acid	fair	Good	good	Best			neither	PVC	2375 by Tygon						
Tartaric Acid	Good	Good	Best	Best			neither	PVC	2375 by Tygon						
Tattoo Colour Liquid, Black (Raidex GmbH)			Best				neither	PTFE					yes	sds	7/1/2024
TBAC - Tetrabutylammonium chloride	[n/r]	Best	Best	[n/r]			neither	PVC	2375 by Tygon						
TBC Inhibitor Solution (Polynt Composites)				Best			Flammable	PTFE	Viton				yes	SDS & Customer Specified	
TBHP-70-AQ - UNITED INITIATORS (Tert-Butyl)	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE					YES	SDS	
TBN Solvent No. 1 (Chem-Supply Australia)	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE					YES	SDS	
TBPND-75-AL (United Initiators)	[n/r]	[n/r]	[n/r]	Best			Flammable	PTFE					YES	SDS	
TCE Tetrachloroethylene	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE			Testing of PP required		yes	test	
T-DET A 1-73B (HARCROS)			Best				neither	PTFE					yes	SDS	
TDI - Toluene diisocyanate	Do Not Use	Best	Good	Fair			Flammable	PTFE					yes	test	
TDS-KS Compound	[n/r]	[n/r]	[n/r]	Best			neither	PVC	2375 by Tygo		too thick out of containe		YES	Product data sheet	
Tea Tree Hand Wash (ABC Compounding)	n/r	n/r	best	n/r			neither	2375 by Tygon					yes	sds	
Techni Matte Tin 89-TI Make Up	n/r	n/r	n/r	best			neither	2375 by Tyg	PTFE				yes	sds	
Techni Solder NF Tin Concentrate (400 G/L) Technic Inc				Best			neither	Viton Hose	PTFE				yes	SDS	June-July 202
Techni Strip AU RTU			Best				neither	PTFE					yes	sds	4/30/2024
TechniStrip NF52		Best					neither	PTFE					yes	SDS & MFG Recommended	
TECHSPRAY FLUX REMOVER nPB	Do Not Use	Best	Best	Good			Flammable	PTFE							
TECHTRIDE NPB-DG	Do Not Use	Best	Best	Good			Flammable	PTFE							

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Tecsol A Solvent, 95%	Do Not Use	Good	Best	Do Not Use			Flammable	2375 by Tyg	PTFE				yes	sds	
Tegosoft DEC (EVONIK)				Best			neither	Tygon2375	PTFE				yes	SDS	
Tera Bromoethane	Do Not Use	Fair	[n/r]	Best			Flammable	PTFE							
TERAFIRM				Best			neither	2375 by Tyg	PTFE		Has particulate matter in	yes	sds& MFG recommended	Aug-19-20	
Tergitol TMN-6 Surfactant (Dow)	Good	Best	Best	Best			neither	2375 by Tyg	PTFE			yes	sds+ test		
Tergitol™ NP-9 Surfactant	Good	Best	Best	Best			neither	2375 by Tyg	PTFE			yes	sds+ test		
TERGO METAL CLEANING FLUID (MicroCare)	do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE			Tef-Kal upgrade require	yes	SDS		
TERIC GN9				BEST			Neither	PTFE					sds		5/1/2018
Terpineol	Good	Do Not Use	Do Not Use	Best			Combustible	PTFE				yes	test		
TerraClean Soil Treatment	Do Not Use	Caution	Caution	Best			neither	2375 by Tyg	PTFE						
Tert-butyl Hydroperoxide	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE					YES	SDS	
Tert-Butyl Methyl Ether						Best	Flammable	PTFE					yes	SDS	
Tertiary Butyl Acetate	[n/r]	[n/r]	[n/r]	[n/r]			Flammable	PTFE			no information				
Tertiary Butyl Alcohol	Fair	Good	[n/r]	Best			Flammable	PTFE							
TETA - Triethylenetetramine	Good	Do Not Use	Do Not Use	Best				PTFE					YES	TEST	
Tetrabromoethane	Do Not Use	Fair	[n/r]	Best			Flammable	PTFE							
Tetrabromomethane	Do Not Use	Fair	[n/r]	Best			Flammable	PTFE							
Tetrabutyl Titanate	Good	Best	[n/r]	Best			Flammable	PTFE							
Tetrachloroethane	Do Not Use	Good	Do Not Use	Best			Flammable	PTFE							
Tetrachloroethylene	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE			Testing of PP required prior to use.				
Tetraethyl Lead	Good	Caution	[n/r]	Best			Flammable	2375 by Tyg	PVC						
Tetraethyl Orthosilicate			Best				flammable	PTFE			TEFLON COATED SCR	yes	sds		
TETRAGUARD ULTRA				Best			neither	Viton	PTFE				yes	sds	entered may 3
Tetrahydrofuran						Best	Flammable	PTFE					yes	SDS	
Tetrahydrofuran	Do Not Use	Do Not Use	Do not use	Do Not Use		Best	flammable	PTFE			Testing of PP required	yes	sds		
Tetrahydrofurfuryl Acrylate	Best	Good	Good	Best			neither	2375 by Tyg	PTFE				yes	sds	
Tetraline	Caution	Do Not Use	[n/r]	Best			Combustible	PTFE			Testing of PP required prior to use.				
Tetrasodium ethylenediaminetetraacetate	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tyg	PTFE						
Texanol (Univar)	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	neither	PTFE					yes	SDS	June-July 202
T-Force® Degreaser (CRC)	Do Not Use	Do Not Use	Do Not Use	best	Required		neither	PTFE			Celcon Tap Required	yes	test and sds		
THE CLASSIC 18-2-6 LIQUID FERTILIZER	Best	Do Not Use	[n/r]	Best			neither	2375 by Tyg	PVC						
Thermosolve (Inventec)		Best					neither	PTFE			Vapor Degreaser Recon	yes	MFG recommended		
Thinner 105 (AXALTA)						Best	flammable	PTFE					yes	SDS	
Thinner with Heptane/Acetone - Slocum Adhesive	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	flammable	PTFE					yes	test/sds	
Third Power	Do Not Use	Best	Do Not Use	Do Not Use			neither	2375 by Tyg	PTFE				yes	sds	
Titanium Tetrachloride	Caution	Do Not Use	[n/r]	Best			neither	PVC	2375 by Tygon						
TKO PHOSPHITE	Good	Good	Good	Best			neither	2375 by Tyg	PVC				yes	test	
TKO PHOSPHITE 0-29-29	Good	Good	Good	Best			neither	2375 by Tyg	PVC				yes	test	
TKO Phosphite Concentration	Good	Good	Good	Best			neither	PVC	2375 by Tygon				yes	test	
TNT Truck and Trailer Wash (ZEP)	[n/r]	Good	Best	[n/r]			neither	2375 by Tyg	PTFE				yes	sds	
Tolcide P570A	Best	Good	Good	Best			neither	2375 by Tyg	PTFE		Also known as Mictreat				
Toluene (ThermoFisher)	Do Not Use	Do Not Use	Do Not Use	best	Recommended		flammable	PTFE					no	Plastic Test	June-July 202
Toluene (Toledo Refining)	Do Not Use	Do Not Use	Do Not Use	best	Recommended		Flammable	PTFE			Celcon tap and Tef-Kal	yes	sds and test	entered May 2	
TOP COAT (AU SANCURE)	do Not Use	Fair	Fair	best	Recommended		flammable	PTFE			Celcon tap and Tef-Kal	yes	test		
TopGuard EQ Fungicide				best			neither	PTFE			CHECK VISCOSITY BE	yes	sds MFG recommended	entered may 3	
Topklean EL 20-A	[n/r]	[n/r]	[n/r]	Best			flammable	PTFE					yes	sds	
TORINO FUNGICIDE				Best			neither	Tygon 2375	PTFE		CHECK VISCOSITY BE	yes	sds MFG recommended	entered may 3	
Total Rubiatir 7900 15W30				Best			neither	Gas	PTFE				yes	SDS	
TOTRIL	[n/r]	[n/r]	[n/r]	Best			neither	PVC	2375 by Tygon						
TOUGH 450 EC	[n/r]	Best	[n/r]	[n/r]			neither	PVC	2375 by Tygon						
tough duty	fair	best	best	best			neither	2375 by Tyg	PTFE				yes	sds + test	
Tough Gard Anti-Splatter Liquid	Do Not Use	Best	Good	Best			neither	Tygon2375	PTFE				yes	SDS	
tough gard Anti-Splatter Liquid (TG101-01, TG10	n/a	best	n/a	n/a			neither	2375 by Tyg	PTFE				yes	test + email	
Tower Pack	Best	[n/r]	[n/r]	Best			neither	2375 by Tyg	PVC				yes	test	
TR-407 Truck and Industrial Cleaner (ALKOTA)	[n/r]	Best	[n/r]	[n/r]			neither	2375 by Tyg	PTFE				yes	sds	
Trans. MDL NA 80W90				Best			neither	PTFE					yes	SDS	
Transformer Oil	Best	Do Not Use	[n/r]	Do Not Use			neither	Gas Grade H	PTFE						
TRANSLINE	Do Not Use	Do Not Use	[n/r]	Best			neither	PVC	2375 by Tygon						
Transmission Fluid Type A	Best	Caution	[n/r]	Best			neither	Gas Grade H	PTFE						
Triacetin	Good	Best	[n/r]	Good			neither	2375 by Tyg	PTFE						
TRIACT	Do Not Use	Do Not Use	[n/r]	Best			neither	PVC	2375 by Tygon						
Triaryl Phosphate	Do Not Use	Good	[n/r]	Good			neither	PTFE							
Tribune Herbicide				Best			neither	PTFE					yes	sds	Feb-17

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update	
TributoxEthyl Phosphate	Caution	Best	[n/r]	Good			neither	2375 by Tyg	PTFE							
Tributyl Phosphate	Do Not Use	Good	[n/r]	Do Not Use			neither	PTFE								
Trichloroethylene	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE						Tef-Kal Tap upgrade Recommended. May need teflon o-rings after 1 year service. Limite		
Tricresyl Phosphate (Lindol)	Do Not Use	Do Not Use	Do Not Use	Best				PTFE	PTFE							
TRICURE AD				Best			neither	2375 by Tyg	PTFE				Possibaly Too thick - 50	yes	sds	Aug-19-20
TRIDAN	[n/r]	[n/r]	[n/r]	Best			neither	PVC	2375 by Tygon							
TriethanolAmine	Caution	Good	Best	Do Not Use			neither	PTFE								
Triethyl Phosphonoacetate	fair	fair	best	n/r									yes		test	
Trigonox 25-C75	do not use	do not use	do not use	Best			flammable	PTFE					yes		sds + test	
Triisopropanolamine	[n/r]	Good	[n/r]	[n/r]			neither	2375 by Tyg	PTFE							
Trilogy	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE				yes		sds	3/10/2015
TRIM MicroSol 485	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE				yes		sds	
TRIMEC 992	Do Not Use	Do Not Use	Do Not Use	Best			neither	Viton	PTFE					flush system regularly to avoid salt buildup		
Trimethoxyphenylsilane	[n/r]	[n/r]	[n/r]	Best			Flammable	PTFE								
Trinitrol Toluene (TNT)	Do Not Use	Fair	[n/r]	Do Not Use		Best	Flammable	PTFE					yes		sds	
Trioctyl Phosphate	Do Not Use	Best	Good	Do Not Use			Combustible	PTFE								
Triphenyl Phosphite (SIGMA-ALDRICH)		Good	Best				neither	Tygon2375	PTFE				yes		SDS & Mfg recommended	
Tripoly Phosphate	Fair	Best	[n/r]	[n/r]			Combustible	PTFE								
Triton™ CF-10 Surfactant (Dow)				Best			neither	2375 by Tyg	PTFE				yes		SDS	June-July 202
TruBlue Deoderizer	Do Not Use	Best	Good	Best			neither	2375 by Tyg	PTFE							
True Blitz (ZEP)	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	flammable	PTFE					yes		sds	
TrueGuard Brake Cleaner - Non-Chlorinated (KELLER-HEARTT)				Best			flammable	Gas Grade H	PTFE				yes		SDS and Mfg recommed	3/10/2015
TRUEX 70 SERIES	[n/r]	[n/r]	[n/r]	Best			neither	2375 by Tyg	PTFE							
TRUEX Series (JJ Chem)	Caution	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE							
TS-608 (ALKOTA)	[n/r]	Best	Best	[n/r]			neither	2375 by Tyg	PTFE				yes		sds	
TSO SC Conditioner	Do Not Use	Good	Best	Do Not Use			Flammable	PTFE					yes		sds	
Tubmate All Purpose	Do Not Use	Best	Do Not Use	Do Not Use			neither	2375 by Tyg	PTFE				yes		sds	
Tuff Stuff				Best			neither	Gas Grade Hose					yes		sds	8/6/2024
Tung Oil	Good	Do Not Use	Do Not Use	Best			Combustible	PTFE						This is a coating liquid and may build up over time in the fluid patt		
Turbine Oil	Best	Do Not Use	[n/r]	Best			neither	Gas Grade H	PTFE							
Turbo Oil	Best	[n/r]	[n/r]	[n/r]			neither	2375 by Tyg	PTFE							
Turf Ventures				Best			Combustible	Tygon2375						SDS		Feb-17
TURFLON ESTER	Do Not Use	Do Not Use	[n/r]	Best			neither	Gas Grade H	PTFE							
Turpentine	Good	Fair	[n/r]	Best			neither	PTFE	Gas Grade Hose							
tvSi-phon (Turf Ventures)	do not use	do not use	do not use	Best			neither	PTFE					yes			
TWEEN 20	do not use	do not use	do not use	Best			Neither	PTFE					yes		sds	5/1/2018
TWEEN 20-LQ-(AP)	do not use	do not use	do not use	Best			neither	PTFE					yes		sds - Teflon per factory but Viton will c	
Tween™ Series	do not use	do not use	do not use	Best			neither	PTFE					yes		sds - Teflon per factory but Viton will c	
ULD PB-100 CONTACT INSECTICIDE				Good			neither	Gas Grade H	PTFE				yes		sds	June 04 2019
ULTRA FINE OIL	Best	Do Not Use	[n/r]	Best			neither	Gas Grade H	PTFE							
Ultra Kleen Spray Equipment Solution	do not use	do not use	do not use	do not use		Best	flammable	PTFE					yes		sds	
Ultra-Quat (Birko)		Best	Best				neither	2375 by Tyg	PTFE				yes		SDS	June-July 202
Ultrasil 76 (nitric acid)	Do Not Use	Do Not Use	Do Not Use	Best			neither	2375 by Tyg	PTFE				yes		sds	
UNDILUTED PROKLENZ® NPH HIGH PERFORMANCE NEUTRAL DETERGENT				Best			neither	2375 by Tygon					yes		sds	Aug-19-20
Univac 177 (INLAND VACUUM INDUSTRIES)				Best			neither	Gas	PTFE				yes		SDS	
Univar 1000 Wash Thinner / Hose Flushings						Best	flammable	PTFE					yes		SDS	
Unsaturated Polyester	Do Not Use	Do Not Use	Do Not Use	Best			Combustible	PTFE					yes		sds	
Unsaturated Polyester IN Monomer (Polynt Com)	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE					yes		SDS	June-July 202
UPTAKE Spraying Oil				Best			neither	Gas	PTFE				yes		SDS	
UpTake Spraying Oil (Corteva)				Best			neither	PTFE					yes		sds	7/21/2023
Urea	Good	Best	Good	Best			neither	PVC	2375 by Tygon							
URINEX (JJ Chem)	Do Not Use	Best	Good	Do Not Use			neither	2375 by Tyg	PTFE							
USA Wash Ultimate Solvent Alternative	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE					yes		sds	
UV-396 (UV-300)	Do Not Use	Do Not Use	Best	Good			neither	PTFE					yes		test	
Valtron DP314				Best			neither	Tygon2375	PTFE				yes		SDS	
Valtron DP98009			Best				neither	Tygon2375	PTFE				yes		SDS	
Valvoline Professional Series Premium Auto Parts Cleaner						Best	flammable	PTFE					yes		sds	5/16/2024
Vanadate-Molybdate Reagen	Do not use	Do not use	Do not use	Do not use									yes		SDS	
Vanilla Extract (NIELSON MASSEY)			Best				flammable	Tygon2375	PTFE				yes		SDS	
Vanishing Oil 96/4 (moter oil (Super)	Best			Good			flammable	PTFE					yes		SDS	June-July 202
Vaporene	Do Not Use	Best	Do Not Use	Do Not Use			neither	PTFE								
VARN INTERNATIONAL ECOLO CLEAN 650	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE								
Varnish	Good	Do Not Use	[n/r]	Best			Combustible	PTFE								

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
VARSOL 3139 SOLVENT - ESSO IMPERIAL	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE					yes	sds	
VECTOBAC 12 AS Mosquito control	Good	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE						
Vegetable Oils	Good	Do Not Use	[n/r]	Best			neither	2375 by Tyg	PTFE						
Versagel ME 500 (Calumet)	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE					yes	SDS and Mfg recommed	3/10/2015
Vertrel XF Solvents (Dupont)	Do Not Use	Best	Best	Do Not Use			Combustible	PTFE					yes	sds	
VERTREL SDG (Dupont)	Do Not Use	Good	Do Not Use	Good			Combustible	PTFE			Specialty pump - EPDM		yes	test	
Vesene 100 Dow	[n/r]	[n/r]	[n/r]	Best			neither	PTFE							
Vesphene IISE Steris			Best				neither	Tygon2375	PTFE				yes	SDS	
Vessel 3 way Herbicide	Do Not Use	Do Not Use	Do Not Use	Best			neither	PTFE					yes	sds	
Vestamin IPD (EVONIK)		Best					neither	Tygon2375	PTFE				yes	SDS	
Vestamin TMD (EVONIK)		Best					neither	Tygon2375	PTFE				yes	SDS	
Vestamin® IPD		Best					Neither	PTFE					yes	sds	Feb-17
Vestamin® TMD		Best					neither	PTFE					yes	sds	Feb-17
VHB Buffer	Best	Good	Good	Good			neither	2375 by Tyg	PTFE				yes	sds + test	
Vigon EFM (Zestron)				Best			Flammable	PTFE					yes	sds and MFG recommen	entered may 3
Vigor OX 15 F & V (PEROXYCHEM)						Best	flammable	PTFE					yes	SDS	
VigorOx 15 F&V 15% (Peroxy Chem)	Do Not Use	Do Not Use	Do Not Use	Do Not Use		Best	flammable	PTFE					yes	sds	
VigorOx® Liquid Sanitizer & Disinfectant	Do not use	Do not use	Do not use	Best			flammable	PTFE			Teflon-Kalrez fluid path		yes	sds + test	
Vinegar	Caution	Best	Best	Caution			neither	PVC		2375 by Tygon					
Vinegar 12-30% (Fleishmann's)			Best			Best	neither	Tygon 2375	PTFE		Fluid path teflon kalrez		yes	sds	8/16/2024
Vinegar Ethanoic			Best				Combustible	2375 by Tyg	PTFE				yes	sds	
Vinegar, 20%	Do Not Use	Best	Best	Caution			neither	PVC		2375 by Tygon					
Vinyl Toluene	Do Not Use	Do Not Use	Do Not Use	Best			Combustible	PTFE							
Viscoatex	Do Not Use	Do Not Use	Best	Good			neither	PTFE					yes	test	
VIVANDO SC FUNGICIDE				Best			neither	Tygon 2375	PTFE		CHECK VISCOSITY BE		yes	sds and MFG recommen	entered may 3
VM&P Naphtha	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	PTFE					yes	sds	Feb-17
Vortexx Sanitizer	Do Not Use	Do Not Use	Do Not Use	Best			Flammable	Tygon 2375	PTFE		Teflon-Kalrez fluid path		yes	sds	
VP110				Best	yes		Flammable	PTFE					yes	sds and test	8/28/2024
VRE	[n/r]	[n/r]	[n/r]	[n/r]			neither	PTFE							
W 210 Sunsheen Black	Good	Fair	Do Not Use	Do Not Use			neither	PTFE					yes	test	
W 3635 E	Best	[n/r]	[n/r]	[n/r]			neither	PTFE					yes	email	
W 3671 B	Best	[n/r]	[n/r]	[n/r]			neither	PTFE					yes	email	
W210 Sunsheen Black	Good	Fair	Do Not Use	Do Not Use			neither	PTFE							
Wacker Siloxane VSI 2	good	Best	good	good			Flammable	Tygon 2375	PTFE				yes	sds and test	6/25/2024
Water	Best	Best	Best	Best			neither	PVC							
Way-Vos (Birko)	[n/r]	Best	Best	[n/r]			neither	Tygon 2375	PTFE				yes	sds	
WD 40	Good	Do Not Use	Do Not Use	Best			Combustible	Gas Grade H	PTFE				yes	test, review and proposal	
WEEDAR 64	Do Not Use	Do Not Use	[n/r]	Best			neither	Tygon 2375	PTFE						
WEED-HOE 108	Do Not Use	Do Not Use	[n/r]	Best			neither	Tygon 2375	PTFE						
Weld-Kleen 350 Anti-Spatter (CRC)				Best			neither	2375 by Tyg	PTFE				yes	SDS and Mfg recommed	3/10/2015
Wessco 37.263.27		Best					neither	PTFE		2375 by Tygon			yes	SDS and Mfg recommed	3/10/2015
WESSCO 37.263.27 UV Coating High Gloss	Do Not Use	Best	Good	Do Not Use			neither	PTFE		2375 by Tygon			yes	SDS	
Wex® (Conklin)			Best				neither	2375 by Tyg	PTFE				yes	SDS	June-July 202
White Oil	Best	Caution	[n/r]	Best			neither	Gas Grade H	PTFE						
White Pine Oil	Good	Caution	[n/r]	Best			neither	PTFE							
Wilkothane Thinner (Wilko Paint, Inc.)						Best	Flammable	PTFE					yes	sds	5/22/2024
Wine and Whiskey	Best	Best	Best	Best			neither	Tygon 2375	PTFE						
WiskCare 371 (Wisk)			Best				flammable	2375 by Tyg	PTFE				yes	SDS	June-July 202
Witch Hazel Extract (Certified Organic)			Best				Flammable	Tygon2375	PTFE				yes	SDS	
WOLF'S HEAD HYDRAULIC OIL	Good	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE						
Wonderbond Hardener M 318LY (HEXION)	Good	best	best	Good			neither	Tygon 2375	PTFE				yes	sds + test	
Wondercide Petrify	Do Not Use	Do Not Use	Do Not Use	Best			neither	Gas Grade H	PTFE				yes	sds	
Wood Oil	Best	Good	[n/r]	Best			neither	Gas Grade H	PTFE						
WOW! Stainless Steel cleaner and protectant (EZ Finishes)				Best			neither	2375 by Tyg	PTFE				yes	SDS	June-July 202
Wurth Baer Mid Temp Thinner (Whitaker)					yes	Best	Flammable	PTFE					yes	sds	5/28/2024
Wyanotte Sanifect D2 Plus AFCO 5531		Good	Best				flammable	2375 by Tygon					yes	sds	Aug-19-20
X77	Best	[n/r]	[n/r]	[n/r]			neither	PTFE							
Xanigo Marine Mold & Stain Remover				Best			neither	Tygon2375	PTFE		Teflon-Kalrez fluid Path upgrade required				
Xiameter A® PMX-200 Silicone Fluid 5 CS	do not use	do not use	good	Best			neither	PTFE					yes	sds + test	
Xiameter PMX-0245 Cyclopentasiloxane	do not use	do not use	do not use	Best			neither	PTFE					yes	sds + test	
XIAMETER PMX-1184 SILICONE FLUID	Good	Good	Best	Best			flammable	Tygon 2375	PTFE				yes	sds	
Xiameter PMX-200 Silicone Fluid 1 CS	do not use	do not use	do not use	Best			flammable	PTFE					yes	sds + test	
Xiameter PMX-200 Silicone Fluid 1.5 CS	do not use	do not use	do not use	Best			flammable	PTFE					yes	sds + test	

Liquid/Chemical	GT/SCP 100 Nitrile	GT/SCP 200 EPDM	GT/SCP 200S Santoprene	GT/SCP 300 Viton	Celcon	Teflon	Flammable	Hose Reconn	Hose R	Special	Notes	PP	We have the SDS/something	Tested or MFG Recommendation	date of insertion or update
Xiameter PMX-200 Silicone Fluid 100CS	do not use	do not use	do not use	Best			neither	PTFE					yes	sds + test	
XIAMETER PMX-200 SILICONE FLUID CS				Best			flammable	PTFE TEFLON					yes	sds	Aug-19-20
X-EXTRA IRON 6-0-0	Best	Do Not Use	[n/r]	Do Not Use			neither	Tygon 2375	PTFE						
XY-12 ( Ecolab)	do not use	Best	Best	do not use			flammable	2375 by Tyg	PTFE				yes	sds	Aug-19-20
XY-12 Sanitizer (sodium hypchlorite)	do not use	Best	Best	do not use			flammable	2375 by Tyg	PTFE				yes	sds	
Xylene / Xylol / Dimethyl Benzene	Caution	Do Not Use	Do Not Use	Good			flammable	PTFE							Testing required for Polypropylene
Yumate KC-770	[n/r]	[n/r]	[n/r]	Best			neither	Tygon 2375	PTFE				yes	sds	
Yumate KC-770				Best			neither						yes	SDS	
ZAMPRO FUNGICIDE				Best			neither	Tygon 2375	PTFE				yes	sds MFG recommended	entered may 3
Zelan R3		Good	[n/r]	Best			neither	Tygon 2375	PTFE				yes	sds	
Zeolites	Good	Best	[n/r]	Best			neither	Tygon 2375	PTFE						
ZEP 4089FS	[n/r]	Best	[n/r]	[n/r]			neither	Tygon 2375	PTFE						
ZEP Brake Wash	Caution	Do Not Use	Do Not Use	Best	required		flammable	PTFE					yes	sds	
ZEP Carb X	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE					yes	sds	
ZEP Concentrated Big John II_5GL				Best			flammable	PTFE					yes	SDS	
ZEP Corex	[n/r]	[n/r]	[n/r]	Best			neither								
ZEP Formula 50 R.T.U.	n/r	best	n/r	n/r			neither	Tygon 2375	hose				yes	sds	
ZEP FS Formula 4089 55 GL	n/r	best	n/r	n/r			neither	Tygon 2375	PTFE				yes	sds	
ZEP Lubenze Omni	Do Not Use	Do Not Use	Do Not Use	Best			neither	Tygon 2375	PTFE						
ZEP PDC- Plain Disinfectant Cleaner II	[n/r]	Best	[n/r]	[n/r]			neither	Tygon 2375	PTFE				yes	sds	
ZEP PLS Protective Lubricating Spray	Good	[n/r]	[n/r]	Best			neither	Gas Grade H	PTFE						
ZEP Protect-ALL - same as Armorall	Do Not Use	Best	Do Not Use	Do Not Use			neither	PTFE					yes	sds	
ZEP Slide 55 Gal				Best			Flammable	PTFE					yes	sds	Feb-17
ZEP T'N'T Truckwash	[n/r]	Best	[n/r]	[n/r]			neither								
ZEP Z-MAXX Brake Wash				Best			flammable	PTFE					yes	SDS	
ZEP-OFF	Do Not Use	Do Not Use	Do Not Use	Best			flammable	PTFE					yes	sds	
ZeroTol 2.0	do not use	do not use	do not use	best			flammable	Tygon 2375	PTFE						
ZeroTol Algaecide	Do Not Use	do not use	do not use	Best			flammable	Tygon 2375	PTFE				yes	sds	
ZeroTol Fungicide	Do Not Use	do not use	do not use	Best			flammable	Tygon 2375	PTFE				yes	sds	
ZeroTol® 2.0 (Biosafe)	do not use	do not use	do not use	Best			flammable	Tygon 2375	PTFE				yes	SDS	June-July 202
Zinc Acetate	Best	Good	[n/r]	Best			neither	Tygon 2375	PTFE						
Zinc Chloride	Best	Good	Good	Best			neither	PVC							
Zinc nitrate solution 17%	Do Not Use	Caution	Caution	Best			neither	Tygon 2375	PTFE				yes	sds	
ZINC OXIDE SOLUTION #1 (BASF)			best				neither	Tygon 2375	PTFE				yes	sds+mfg recommends	Sept 14-19
Zinc Salts	Best	[n/r]	Best	[n/r]			neither	PVC							
Zinc Sulfate	Best	Best	Best	Best			neither	PVC							
ZIRAM GRANUFLO FUNGICIDE				Best			neither	Tygon 2375	PTFE				yes	sds MFG recommended	entered may 3
Z-Maxx Brake Wash	Do Not Use	Do Not Use	Do Not Use	Best	required		flammable	PTFE					yes	sds	
ZYGLO PENETRANT ZL-67 - Magnaflux	Do Not Use	Good	Best	Best			neither	2375 by Tyg	PTFE				yes	sds & test	
Gamma Heptalactone CAS# 105-21-5		Best	Best				neither	2375 by Tyg	PTFE				yes	test	11/27/2024
C-6 Aldehyde (Hexanal) CAS # 66-25-1		Best	Best				neither	2375 by Tyg	PTFE				yes	test	11/27/2024
20 Methyl Butyric Acid CAS #116-25-1		Best	Best				neither	2375 by Tyg	PTFE				yes	test	11/27/2024
AC-777 Membrane Antiscalant NSF				Best			neither	2375 by Tyg	PTFE				yes	sds	11/27/2024
ACSDI Lubricating Oil (Air Compressor Supply) DiEster Blenc				Best			neither	Gas Grade H	PTFE				yes	SDS	12/18/2024
CP - 9001 aka ENVIROIL (Lubricating Oil)				Best			neither	Gas Grade H	PTFE				yes	SDS	12/18/2024
TRU SMOKE 45 (R2 FLAVOR TECHNOLOGY		Besy					neither	PTFE					yes	SDS	12/18/2024